

PRODUCT SPECIFICATIONS

NuDrain™ DN50 Series

PROPERTY	TEST	UNIT	NuDrain™ DN50-1	NuDrain™ DN50-2	NuDrain™ DN50-4/6
Core					
Compressive Strength	ASTM D-1621	kNm ² (psf)	1917 (40000)	1917 (40000)	1917 (40000)
Thickness	ASTM D-1777	mm (in)	5.6 (0.22)	5.6 (0.22)	5.6 (0.22)
In-Plane Flow	ASTM D-4716	l/min/m (gpm/ft)	106 (8.5)	106 (8.5)	106 (8.5)
Fabric					
Flow	ASTM D-4491	l/min/m ² (gpm/ft ²)	5500 (135)	5500 (135)	5500 (135)
Puncture	ASTM D-4833	kN (lb)	0.30 (65)	0.30 (65)	0.30 (65)
Apparent Opening Size (AOS)	—	mm (US Sieve)	0.212 (70)	0.212 (70)	0.212 (70)
Grab Tensile Strength	ASTM D-4632	kN (lb)	0.53 (120)	0.53 (120)	0.53 (120)
Packaging					
Roll Width	Measured	m (ft)	1.22 (4)	1.22 (4)	1.22 (4)
Roll Length	Measured	m (ft)	22.86 (75)	22.86 (75)	15.24 (50)
Roll Weight	Calculated	kg (lb)	31.75 (70)	36.29 (80)	24.95 (55)

Note: Nilex NuDrain™ DN50-1, DN50-2 and DN50-4/6 are identical in physical properties with the addition of a layer of filter to the backside of DN50-2, and a layer of heavy duty grey fabric bonded to the back side of DN50-4/6, providing protection and cushioning for waterproofing systems.

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.