

PRODUCT SPECIFICATIONS

NuDrain™ GRS

PROPERTY	TEST	UNIT	NuDrain™ GRS (Top Grey)	NuDrain™ GRS (Bottom Black)
Fabric				
Basis Weight	ASTM D-3776	gsm (oz/yd ²)	100 (2.95)	129 (3.80)
Grab Tensile Strength	ASTM D-4632	N (lbf)	333/311 (75/70)	400 (90)
Grab Elongation	ASTM D-5034	%	40	60
Thickness	ASTM D-1777	mm (in)	12 (0.49)	33 (1.3)
Trapezodial Tear	ASTM D-1117	N (lbf)	89 (20)	178 (40)
Water Flow Rate	ASTM D-4491	l/min/m ² (gal/min/ft ²)	946 (250)	530 (140)
Core				
Compressive Strength	ASTM D-1621	kNm ² (psf)	455 (9500)	
Thickness	ASTM D-1777	mm (in)	254 (1.0)	
Flow	ASTM D-4716	l/min/m (gal/min/ft)	372 (30)	
Water Retention	Measured	l/m ² (gal/ft ²)	45 (1.1)	
Packaging				
Roll Width	Measured	m (ft)	1.22 (4)	
Roll Length	Measured	m (ft)	15.24 (50)	
Roll Weight	Calculated	kg (lb)	38 (88)	

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.