

PRODUCT SPECIFICATIONS

Unearthing better results.

NuDrain™ SD Series

Property	Test	Unit	NuDrain™ SD60	NuDrain™ SD120	NuDrain™ SD180
Core					
Compressive Strength	ASTM D-1621	kNm ² (psf)	454 (9500)	454 (9500)	454 (9500)
In-Plane Flow	ASTM D-4716	l/min/m (gpm/ft)	373 (30)	373 (30)	373 (30)
Fabric					
Flow	ASTM D-4491	l/min/m ² (gpm/ft ²)	5698 (140)	5698 (140)	5698 (140)
Puncture	ASTM D-4833	kN (lb)	0.30 (65)	0.30 (65)	0.30 (65)
Apparent Opening Size (AOS)	—	mm (US Sieve)	0.212 (70)	0.212 (70)	0.212 (70)
Grab Tensile Strength	ASTM D-4632	kN (lb)	0.45 (100)	0.45 (100)	0.45 (100)
Packaging					
Roll Width	Measured	mm (in)	152.4 (6)	304.8 (12)	457.2 (18)
Roll Length	Measured	m (ft)	45.72 (150)	45.72 (150)	45.72 (150)

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.



nilex.com

EDMONTON T: 780.463.9535 TF: 1.800.667.4811	CALGARY T: 403.543.5454 TF: 1.888.543.5454	TORONTO T: 416.640.6002 TF: 1.877.640.6002	VANCOUVER T: 604.420.6433 TF: 1.800.663.0478	VERNON T: 250.260.3300 TF: 1.800.663.0478	ABBOTSFORD T: 604.420.6433 TF: 1.800.663.0478	SASKATOON T: 306.956.0088 TF: 1.888.543.5454	DENVER T: 303.766.2000
---	--	--	--	---	---	--	---------------------------