



NILEX CORPORATION
15171 East Fremont Drive
Centennial, Colorado 80112
(303) 766-2000 phone
(303) 766-1110 fax
www.nilex.com

Nilex Landscape Fabric

Nilex Landscape Fabric is a polypropylene nonwoven needlepunched fabric. This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable. Polypropylene is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geotextiles today. We wish to advise that the fabric provided to you meets the following typical values:

Typical Physical Properties

<u>Properties</u>	<u>Test Method</u>	<u>Typical Value</u> (English)	<u>Typical Value</u> (Metric)
Basic Weight	ASTM D-3776	3.3oz/sy	111 gm/m ²
Grab Tensile	ASTM D-4632	70/80 lbf MD/CD	311/356 N MD/CD
Grab Elongation	ASTM D-4632	45/43% MD/CD	45/43 % MD/CD
Trap. Tear Strength	ASTM D-4533	30/34 lbf MD/CD	133/151 N MD/CD
Water Flow Rate	ASTM D-4491	150 gal/min/sf	6105 L/min/m ²
AOS	ASTM D-4751	70	.250 mm
Puncture	ASTM D-4833	55 lb	244 N
Burst Strength	ASTM D-3786	178 psi	1226 kPa
Color		Gray	Gray

MD = Machine Direction, **CD** = Cross Direction

Manufacturing Process: Nonwoven needlepunched fabric

Material: Polypropylene

BENEFITS: Exceptional durability and strength, less bulky than woven fabrics, stays flexible, easy to cut and handle, maintains consistent properties in all directions, unequalled weed control while allowing for excellent water and air permeability.

Note: The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.