



NILEX CORPORATION  
15171 East Fremont Drive  
Centennial, Colorado 80112  
(303) 766-2000 phone  
(303) 766-1110 fax  
[www.nilex.com](http://www.nilex.com)

## Nilex NW120 Nonwoven Geotextile

Nilex NW120 is a superior quality, nonwoven geotextile produced by needlepunching together 100% polypropylene staple fibers in a random network to form a high strength dimensionally stable fabric. The polypropylene fibers are specially formulated to resist ultraviolet light deterioration, and are inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. Polypropylene is stable within a pH range pf 2 to 13. Nilex NW120 conforms to the physical property values listed below:

| Fabric Property                       | Test Method | Units               | MARV                            |
|---------------------------------------|-------------|---------------------|---------------------------------|
| Weight                                | ASTM D-3776 | oz/sy               | 12.0 (407g/ m <sup>2</sup> )    |
| Grab Tensile Strength                 | ASTM D-4632 | lbs                 | 300 (1.33kN)                    |
| Grab Elongation                       | ASTM D-4632 | %                   | 50                              |
| Trapezoidal Tear                      | ASTM D-4533 | lbs                 | 115 (0.511kN)                   |
| Puncture Strength                     | ASTM D-4833 | lbs                 | 180 (0.80kN)                    |
| Mullen Burst                          | ASTM D-3786 | psi                 | 600 (4134kPa)                   |
| Permittivity                          | ASTM D-4491 | sec <sup>-1</sup>   | 1.0                             |
| Water Flow Rate                       | ASTM D-4491 | gpm/ft <sup>2</sup> | 75 (3055 l/min/m <sup>2</sup> ) |
| AOS                                   | ASTM D-4751 | US Sieve            | 100 (0.150mm)                   |
| UV Resistance<br>(Retained, 500 hrs.) | ASTM D-4355 | % Strength          | 70                              |

Note: Values are MARV, reported in weaker principle direction. "MARV" indicates minimum average roll value calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.

Please do not hesitate to contact us at (303) 766-2000 if you have any questions regarding this certification.

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT FURNISHED HEREUNDER OTHER THAN AT THE TIME OF DELIVERY IT SHALL BE OF THE QUALITY AND SPECIFICATION STATED HEREIN. ANY IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED, AND, TO THE EXTENT THAT IT IS CONTRARY TO THE FOREGOING SENTENCE, ANY IMPLIED WARRANTY OF MERCHANTABILITY IS EXPRESSLY EXCLUDED. ANY RECOMMENDATIONS MADE BY SELLER CONCERNING THE USES OR APPLICATIONS OF SAID PRODUCT ARE BELIEVED RELIABLE AND SELLER MAKES NO WARRANTY OF RESULTS TO BE OBTAINED.