



NILEX CORPORATION
15171 East Fremont Drive
Centennial, Colorado 80112
(303) 766-2000 phone
(303) 766-1110 fax
www.nilex.com

Nilex NW60 Nonwoven Geotextile

Nilex NW60 is a superior quality, nonwoven geotextile produced by needlepunching together 100% polypropylene staple fibers in a random network to form a high strength dimensionally stable fabric. The polypropylene fibers are specially formulated to resist ultraviolet light deterioration, and are inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. Polypropylene is stable within a pH range of 2 to 13. Nilex NW60 conforms to the physical property values listed below:

Fabric Property	Test Method	Units	MARV
Weight	ASTM D-3776	oz/sy	6.0 (203g/ m ²)
Grab Tensile Strength	ASTM D-4632	lbs	160 (0.711kN)
Grab Elongation	ASTM D-4632	%	50
Trapezoidal Tear	ASTM D-4533	lbs	65 (0.289kN)
Puncture Strength	ASTM D-4833	lbs	90 (0.40kN)
Mullen Burst	ASTM D-3786	psi	315 (2170kPa)
Permittivity	ASTM D-4491	sec ⁻¹	1.6
Water Flow Rate	ASTM D-4491	gpm/ft ²	110 (4480 l/min/m ²)
AOS	ASTM D-4751	US Sieve	70 (0.212mm)
UV Resistance (Retained, 500 hrs.)	ASTM D-4355	% Strength	70

Note: Values are MARV, reported in weaker principle direction. "MARV" indicates minimum average roll value calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.

Please do not hesitate to contact us at (303) 766-2000 if you have any questions regarding this certification.

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT FURNISHED HEREUNDER OTHER THAN AT THE TIME OF DELIVERY IT SHALL BE OF THE QUALITY AND SPECIFICATION STATED HEREIN. ANY IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED, AND, TO THE EXTENT THAT IT IS CONTRARY TO THE FOREGOING SENTENCE, ANY IMPLIED WARRANTY OF MERCHANTABILITY IS EXPRESSLY EXCLUDED. ANY RECOMMENDATIONS MADE BY SELLER CONCERNING THE USES OR APPLICATIONS OF SAID PRODUCT ARE BELIEVED RELIABLE AND SELLER MAKES NO WARRANTY OF RESULTS TO BE OBTAINED.