



NILEX CORPORATION
15171 East Fremont Drive
Centennial, Colorado 80112
(303) 766-2000 phone
(303) 766-1110 fax
www.nilex.com

Nilex Silt Fence Fabric

Nilex Silt Fence Fabric a polypropylene woven fabric. It is manufactured at a facility that has achieved ISO 2002 certification for its systematic approach to quality. The construction of the geotextile makes the Nilex Silt Fence Fabric ideal for soil separation and stabilization. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non biodegradable.

Nilex Silt Fence Fabric conforms to the property values listed below:

<i>Property</i>	<i>Test Method</i>	<i>Units</i>	<i>Spec (MARV)</i>
Grab Tensile Strength (MD)	ASTM D 4632	lbs	128
Grab Tensile Strength (TD)	ASTM D 4632	lbs	128
Grab Tensile Elongation (MD)	ASTM D 4632	%	18
Grab Tensile Elongation (TD)	ASTM D 4632	%	15
WW Tensile Strength (MD)	ASTM D 4595	lbs/ ft	NA
WW Tensile Strength (TD)	ASTM D 4595	lbs/ ft	NA
Trapezoidal Tear Strength (MD)	ASTM D 4533	lbs	70
Trapezoidal Tear Strength (TD)	ASTM D 4533	lbs	73
Mullen Burst Strength	ASTM D 3786	psi	310
Puncture Strength	ASTM D 4833	lbs	68
Apparent Opening Size (AOS)	ASTM D 4751	sieve	30
Permittivity	ASTM D 4491	sec ⁻¹	0.09
Flow rate	ASTM D 4491	gpm/ ft ²	9
UV resistance (Xenon 500 h)	ASTM D 4355	% retained strength	80
Weight per UOM	ASTM D 5261	oz/ yd ²	3.7
Thickness	ASTM D 5199	mm	

NOTES

- 1.Values for machine (warp) and cross-machine(v(fill)),respectively,under dry or saturated conditions
- 2.The testing herein is based upon accepted industry practice as well as the test method listed. Test results reported herein do not apply samples other than those tested
- 3.MARV (mimimum average rolls values) are calculated as the typical minus two standard deviations.