



NILEX CORPORATION
15171 East Fremont Drive
Centennial, Colorado 80112
(303) 766-2000 phone
(303) 766-1110 fax
www.nilex.com

Nilex W300 Woven Geotextile

Nilex W300 is a superior quality, woven geotextile composed of polypropylene filaments that are formed into a stable network such that the filaments retain their relative position. The fabric is inert to biological degradation and naturally encountered chemicals, alkalies, and acids. Polypropylene is stable within a pH range of 2 to 13. Nilex W300 conforms to the physical property values listed below:

Fabric Property	Test Method	Units	MARV
Weight	ASTM D-5261	oz/sy	6.0 (203g/sm)
Grab Tensile Strength	ASTM D-4632	lbs	300 (1.33kN)
Grab Elongation	ASTM D-4632	%	15
Trapezoidal Tear	ASTM D-4533	lbs	100 (0.444kN)
Puncture Strength	ASTM D-4833	lbs	120 (.533kN)
Mullen Burst	ASTM D-3786	psi	600 (4134kPa)
Permittivity	ASTM D-4491	1/sec	0.05
Water Flow Rate	ASTM D-4491	gpm/ft ²	4 (163 l/min/sm)
AOS	ASTM D-4751	US Sieve	40 (0.425mm)
UV Resistance (Retained, 500 hrs.)	ASTM D-4355	% Strength	70

Note: Values are MARV, reported in weaker principle direction. "MARV" indicates minimum average roll value calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.

Please do not hesitate to contact us at (303) 766-2000 if you have any questions regarding this certification.

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT FURNISHED HEREUNDER OTHER THAN AT THE TIME OF DELIVERY IT SHALL BE OF THE QUALITY AND SPECIFICATION STATED HEREIN. ANY IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED, AND, TO THE EXTENT THAT IT IS CONTRARY TO THE FOREGOING SENTENCE, ANY IMPLIED WARRANTY OF MERCHANTABILITY IS EXPRESSLY EXCLUDED. ANY RECOMMENDATIONS MADE BY SELLER CONCERNING THE USES OR APPLICATIONS OF SAID PRODUCT ARE BELIEVED RELIABLE AND SELLER MAKES NO WARRANTY OF RESULTS TO BE OBTAINED.