

PRODUCT SPECIFICATIONS

Nilex Woven 1199

PROPERTY	TEST	UNIT	VALUE (MARV)
Origin of Materials			
U.S Manufactured		%	100
Mechanical			
Grab Tensile Strength	ASTM D-4632	N (lb)	1646 x 1112 (370 x 250)
Grab Elongation	ASTM D-4632	%	15 x 15
CBR Puncture*	ASTM D-6241	N (lb)	4226 (950)
Trapezoidal Tear	ASTM D-4533	N (lb)	445 x 267 (100 x 60)
Hydraulic			
Percent Open Area	CW-02215 MOD. ⁴	%	4
Apparent Opening Size	ASTM D-4751	mm (US Sieve)	0.212 (70)
Permittivity	ASTM D-4491	sec ⁻¹	0.28
Water Flow Rate	ASTM D-4491	l/m/m ² (gpm/ft ²)	733 (18)
Endurance			
UV Resistance	ASTM D-4355	% @ 500 hrs	90
Packaging			
Roll Size	Measured	m (ft)	1.83 x 91.5 (6 x 300) 3.66 x 91.5 (12 x 300)

*Note: Mullen Burst ASTM D-3786 and Puncture Strength ASTM D-4833 are no longer recognized by ASTM Committee D35 as an acceptable geotextile test method. Puncture Strength ASTM 4833 has been replaced with the Static (CBR) Puncture ASTM D-6241. For more information, refer to the ASTM website at www.astm.org

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.