

PRODUCT SPECIFICATIONS

Nilex Woven 2019

PROPERTY	TEST	UNIT	VALUE (MARV)
Mechanical			
Grab Tensile Strength	ASTM D4632	N (lb)	2003 x 1558 (450 x 350)
Grab Elongation	ASTM D4632	%	15 x 6
Wide Width Tensile Strength	ASTM D4595	kN/m (lb/ft)	52.5 x 52.5 (3600 x 3600)
Wide Width Tensile at 2% Strain	ASTM D4595	kN/m (lb/ft)	7.0 x 6.1 (480 x 420)
Wide Width Tensile at 5% Strain	ASTM D4595	kN/m (lb/ft)	20.3 x 25.4 (1392 x 1740)
Wide Width Tensile at 10% Strain	ASTM D4595	kN/m (lb/ft)	46.4 x 50.8 (3180 x 3480)
CBR Puncture*	ASTM D6241	N (lb)	7120 (1600)
Trapezoidal Tear	ASTM D4533	N (lb)	801 x 623 (180 x 140)
Hydraulic			
Apparent Opening Size	ASTM D4751	mm (US Sieve)	0.600 (#30)
Permittivity	ASTM D4491	sec ⁻¹	0.52
Water Flow Rate	ASTM D4491	l/m/m ² (gpm/ft ²)	1630 (40)
Endurance			
UV Resistance	ASTM D4355	% @ 500 hrs	80
Packaging			
Roll Size	Measured	m (ft)	4.6 x 91.5 (15 x 300)

*Note: Mullen Burst ASTM D3786 and Puncture Strength ASTM D4833 are no longer recognized by ASTM Committee D35 as an acceptable geotextile test method. Puncture Strength ASTM 4833 has been replaced with the Static (CBR) Puncture ASTM D6241. For more information, refer to the ASTM website at www.astm.org

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.