

GEOTEXTILES

NON-WOVENS

Property	Test Method	Unit	180R	270R	360R	420R
Weight	ASTM-D5261	g/m ²	84	108	164	212
Grab Tensile Strength	ASTM-4632	N	356	445	712	911
Grab Elongation	ASTM-D6432	%	50-105	50-105	50-105	50-105
Tear Resistance	ASTM-D4533	N	130	200	267	356
Puncture CBR ¹	ASTM-D6241	N	934	1320	1820	2380
Permittivity	ASTM-D4491	sec ⁻¹	2.00	2.20	1.50	1.4
Water Flow	ASTM-D4491	l/min/m ²	6095	6095	4480	4000
Apparent Opening Size (A.O.S.)	ASTM-D4751	mm	0.300	0.300	0.212	0.212
U.V. Resistance	ASTM-D4355	% @ 500h	70	70	70	70

Property	Test Method	Unit	600R	800R	1200R	370RS
Weight	ASTM-D5261	g/m ²	260	312	435	445
Grab Tensile Strength	ASTM-4632	N	1110	1330	1690	1000
Grab Elongation	ASTM-D6432	%	50-105	50-105	50-105	n/a
Tear Resistance	ASTM-D4533	N	444	511	644	n/a
Puncture CBR ¹	ASTM-D6241	N	3110	3780	4820	n/a
Permittivity	ASTM-D4491	sec ⁻¹	1.20	1.00	0.70	n/a
Water Flow	ASTM-D4491	l/min/m ²	3251	3055	2035	n/a
Apparent Opening Size (A.O.S.)	ASTM-D4751	mm	0.180	0.150	0.150	<0.075
U.V. Resistance	ASTM-D4355	% @ 500h	70	70	70	70

Note: 370RS is a Scrim-Nonwoven geotextile.

***Please contact Terrafix for higher Grab Tensile Strength geotextiles.**

WOVENS

Property	Test Method	Unit	24-15	200W	400W
Weight	ASTM-D5261	g/m ²	130	160	190
Grab Tensile Strength	ASTM-4632	N	900	1350	1417
Grab Elongation	ASTM-D6432	%	15	15	15
Tear Resistance	ASTM-D4533	N	337.5	540	540
Puncture CBR ¹	ASTM-D6241	N	3150	4185	4275
Permittivity	ASTM-D4491	sec ⁻¹	0.20	0.20	0.20
Water Flow	ASTM-D4491	l/min/m ²	815 Avg.	610 Avg.	610 Avg.
Apparent Opening Size (A.O.S.)	ASTM-D4751	mm	0.45 max	0.45 max	0.45 max
U.V. Resistance	ASTM-D4355	% @ 500h	80	80	80

Note:
All values are MARV. The information contained has been compiled by Terrafix and is, to the best of our knowledge, true, and accurate. This information is offered without warranty.
Final determination of suitability for use contemplated is the sole responsibility of the user. This information is subject to change without notice. 04-2021