



A nonwoven geotextile fabric supplied by Thrace-LINQ, Inc., is manufactured from Polypropylene staple fiber. The fibers are randomly oriented and form a cohesive / stabilized needle punched fabric, for use in Environmental applications. This fabric has been UV stabilized and is resistant to commonly encountered chemicals, mildew, and insects found in soil or environmental applications.

<i>PROPERTY</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		MARV		MARV	
Grab Tensile Strength	ASTM D-4632	1202	N	270	lbs
Grab Elongation	ASTM D-4632	50	%	50	%
Trapezoid Tear	ASTM D-4533	445	N	100	lbs
Puncture	ASTM D-4833	712	N	160	lbs
Puncture (CBR)	ASTM D-6241	3225	N	725	lbs
Mullen Burst	ASTM D-3786	3447	kPa	500	psi
Permittivity	ASTM D-4491	1.2	sec ⁻¹	1.2	sec ⁻¹
A.O.S.	ASTM D-4751	0.150	mm	100	U.S. Sieve
UV Stability (500 hrs)	ASTM D-4355	70	%	70	%
Water Flow Rate	ASTM D-4491	3463	lpm/m ²	85	gpm/ft ²
Weight	ASTM D-5261	339	g/m ²	10	oz/yd ²
Thickness	ASTM D-5199	2.794	mm	110	mils

<i>PACKAGING</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		Typical		Typical	
Roll sizes		3.81 x 109.7	m	12.5 x 360	ft
		4.57 x 91.4	m	15 x 300	ft
Roll Area		418	m ²	500	yd ²
		418	m ²	500	yd ²

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.