

1200EX

Thrace-LINQ® 1200EX is a nonwoven geotextile fabric manufactured from Polypropylene staple fiber. The fibers are randomly oriented and form a cohesive/stabilized needlepunched fabric, for use in many applications. This fabric has been UV stabilized and is resistant to commonly encountered chemicals, mildew, and insects, found in soil.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		MARV		MARV	
Weight	ASTM-D5261	407	g/m ²	12	oz/yd ²
Thickness	ASTM-D5199	3.048	mm	120	mils
Grab Tensile Strength	ASTM-D4632	1423	N	320	lbs
Grab Tensile Elongation	ASTM-D4632	50	%	50	%
Trapezoid Tear	ASTM-D4533	534	N	120	lbs
CBR Puncture	ASTM-D6241	4003	N	900	lbs
Permittivity	ASTM-D4491	0.9	sec ⁻¹	0.9	sec ⁻¹
WaterFlow Rate	ASTM-D4491	2648	l/min/m ²	65	gpm/ft ²
Apparent Opening Size (AOS)	ASTM-D4751	0.150	mm	100	USSieve
UV Stability @ 500 hrs	ASTM-D4355	70	%	70	%

- Notes:**
- Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.
 - Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

PACKAGING		METRIC				ENGLISH			
		Area	Width	Length	Est. Weight	Area	Width	Length	Est. Weight
		m ²	m	m	kg	yd ²	ft	ft	lbs
Roll Sizes		418	4.6	91.4	183	500	15	300	404

*Physical properties reflect industry standards. Roll Data may reflect higher values than those listed above.
Roll lengths and widths have a tolerance of +/- 1%.*

The property values listed above are effective 09/2012 and are subject to change without notice.

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date manufactured. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.