



A nonwoven geotextile fabric supplied by Thrace-LINQ, Inc., is manufactured from Polypropylene staple fiber. The fibers are randomly oriented and form a cohesive / stabilized needle punched fabric, for use in Environmental applications. This fabric has been UV stabilized and is resistant to commonly encountered chemicals, mildew, and insects found in soil or environmental applications.

<i>PROPERTY</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		MARV		MARV	
Grab Tensile Strength	ASTM D-4632	734	N	165	lbs
Grab Elongation	ASTM D-4632	50	%	50	%
Trapezoid Tear	ASTM D-4533	289	N	65	lbs
Puncture	ASTM D-4833	423	N	95	lbs
Puncture (CBR)	ASTM D-6241	1891	N	425	lbs
Mullen Burst	ASTM D-3786	2172	kPa	315	psi
Permittivity	ASTM D-4491	1.5	sec ⁻¹	1.5	sec ⁻¹
A.O.S.	ASTM D-4751	0.180	mm	80	U.S. Sieve
UV Stability (500 hrs)	ASTM D-4355	70	%	70	%
Water Flow Rate	ASTM D-4491	4482	lpm/m ²	110	gpm/ft ²
Weight	ASTM D-5261	204	g/m ²	6	oz/yd ²
Thickness	ASTM D-5199	1.905	mm	75	mils

<i>PACKAGING</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		Typical		Typical	
Roll sizes		3.81 x 109.7	m	12.5 x 360	ft
		4.57 x 91.4	m	15 x 300	ft
Roll Area		418	m ²	500	yd ²
		418	m ²	500	yd ²

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.