

A non-woven geotextile fabric supplied by Thrace-LINQ, Inc., is manufactured from Polypropylene staple fiber. The fibers are randomly oriented and form a cohesive / stabilized needle punched fabric for use in many applications, such as separation, drainage, filtration, etc. This fabric has been UV stabilized and is resistant to commonly encountered chemicals, mildew and insects found in soil.

| PROPERTY               | TEST PROCEDURE | METRIC |                    | ENGLISH |                     |
|------------------------|----------------|--------|--------------------|---------|---------------------|
|                        |                | MARV   |                    | MARV    |                     |
| Grab Tensile Strength  | ASTM D-4632    | 623    | N                  | 140     | lbs                 |
| Grab Elongation        | ASTM D-4632    | 50     | %                  | 50      | %                   |
| Trapezoid Tear         | ASTM D-4533    | 267    | N                  | 60      | lbs                 |
| CBR Puncture           | ASTM D-6241    | 1602   | N                  | 360     | lbs                 |
| UV Stability (500 hrs) | ASTM D-4355    | 70     | %                  | 70      | %                   |
| Permittivity           | ASTM D-4491    | 1.5    | sec <sup>-1</sup>  | 1.5     | sec <sup>-1</sup>   |
| Water Flow Rate        | ASTM D-4491    | 4686   | lpm/m <sup>2</sup> | 115     | gpm/ft <sup>2</sup> |
| A.O.S.                 | ASTM D-4751    | 0.212  | mm                 | 70      | U.S. Sieve          |

**Notes:**

- Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.
- Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

| PROPERTY  | TEST PROCEDURE | METRIC  |                  | ENGLISH |                    |
|-----------|----------------|---------|------------------|---------|--------------------|
|           |                | Typical |                  | Typical |                    |
| Weight    | ASTM D-5261    | 170     | g/m <sup>2</sup> | 5.0     | oz/yd <sup>2</sup> |
| Thickness | ASTM D-5199    | 1.778   | mm               | 70      | mils               |

| PACKAGING  | METRIC             |        |         | ENGLISH             |       |        |
|------------|--------------------|--------|---------|---------------------|-------|--------|
|            | AREA               | WIDTH  | LENGTH  | AREA                | WIDTH | LENGTH |
| Roll sizes | 418 m <sup>2</sup> | 3.81 m | 109.7 m | 500 yd <sup>2</sup> | 12.5' | 360'   |
|            | 418 m <sup>2</sup> | 4.57 m | 91.4 m  | 500 yd <sup>2</sup> | 15'   | 300'   |

*Physical properties reflect industry standards. Roll Data may reflect higher values than those listed above.*

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.