

GTF 4x6

A woven geotextile fabric, produced from high-tenacity polypropylene slit-film. This high-modulus fabric is ideally suited for reinforcement or containment applications, where filtration is critical. GTF 4x6 has been UV stabilized and packaged in conformance with ASTM D4873.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		MARV		MARV	
Grab Tensile Strength	ASTM D-4632	2670/3114	N	600/700	lbs
Wide Width Tensile (W/F)	ASTM D-4595	70/105	kN/m	400/600	lbs/in
Wide Width Tensile @ 5%	ASTM D-4595	17.5/38.5	kN/m	100/220	lbs/in
Grab Elongation	ASTM D-4632	15x15	%	15x15	%
Wide Width Elongation	ASTM D-4595	14/9	%	14/9	%
Trapezoid Tear	ASTM D-4533	801/1223	N	180/275	lbs
UV Stability (500 hrs)	ASTM D-4355	80	%	80	%
Permittivity	ASTM D-4491	0.260	sec ⁻¹	0.260	sec ⁻¹
Water Flow Rate	ASTM D-4491	810	lpm/m ²	20	gpm/ft ²
A.O.S.	ASTM D-4751	0.425	mm	40	U.S. Sieve

Notes:

- Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.
- Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		Typical		Typical	
Weight	ASTM D-5261		g/m ²		oz/yd ²
Thickness	ASTM D-5199		mm		mils

PACKAGING	METRIC			ENGLISH		
	AREA	WIDTH	LENGTH	AREA	WIDTH	LENGTH
Roll sizes	418 m ²	4.57 m	91.4 m	500 yd ²	15'	300'

Physical properties reflect industry standards. Roll Data may reflect higher values than those listed above.

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.