



A woven geotextile filter fabric, produced from high-tenacity polypropylene yarns. GTF 570 is typically used in Reinforcement applications. GTF 570 has been UV stabilized and packaged in conformance with ASTM D4873.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		MARV		MARV	
Grab Tensile Strength(W/F)	ASTM D-4632	2114/1958	N	475/440	lbs
Wide Width Tensile (W/F)	ASTM D-4595	70.1/70.1	kN/m	400/400	lbs/in
Grab Elongation	ASTM D-4632	12/6	%	12/6	%
Trapezoid Tear	ASTM D-4533	801 / 801	N	180 / 180	lbs
CBR Puncture	ASTM D-6241	8900	N	2000	lbs
UV Resistance (500 hrs)	ASTM D-4355	80	%	80	%
Permittivity	ASTM D-4491	0.400	sec ⁻¹	0.400	sec ⁻¹
Water Flow Rate	ASTM D-4491	1222	lpm/m ²	30	gpm/ft ²
A.O.S.	ASTM D-4751	0.600	mm	30	U.S. Sieve

Notes:

- Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.
- Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		Typical		Typical	
Weight	ASTM D-5261	492	g/m ²	14.5	oz/yd ²
Thickness	ASTM D-5199	1.160	mm	63	mils

PACKAGING	METRIC			ENGLISH		
	AREA	WIDTH	LENGTH	AREA	WIDTH	LENGTH
Roll sizes	418 m ²	4.57 m	91.4 m	500 yd ²	15'	300'

Physical properties reflect industry standards. Roll Data may reflect higher values than those listed above.

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.