



A woven geotextile fabric, produced from high-tenacity polypropylene slit-film. This high-modulus fabric is ideally suited for separation / stabilization and reinforcing applications. GTF 700 has been UV stabilized and packaged in conformance with ASTM D4873.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		MARV		MARV	
Grab Tensile Strength(W/F)	ASTM D-4632	3120	N	700	lbs
Wide Width Tensile (W/F)	ASTM D-4595	93/90	kN/m	533/502	lbs/in
Grab Elongation	ASTM D-4632	20/15	%	20/15	%
Trapezoid Tear	ASTM D-4533	1335/1112	N	300/250	lbs
CBR puncture	ASTM D-6241	7565	N	1700	lbs
UV Resistance (500 hrs)	ASTM D-4355	80	%	80	%
Permittivity	ASTM D-4491	0.060	sec ⁻¹	0.060	sec ⁻¹
Water Flow Rate	ASTM D-4491	208	lpm/m ²	5.1	gpm/ft ²
A.O.S.	ASTM D-4751	0.180	mm	80	U.S. Sieve

Notes:

- Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.
- Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		Typical		Typical	
Weight	ASTM D-5261	500	g/m ²	14.75	oz/yd ²
Thickness	ASTM D-5199	1.52	mm	60	mils

PACKAGING	METRIC			ENGLISH		
	AREA	WIDTH	LENGTH	AREA	WIDTH	LENGTH
Roll sizes	418 m ²	4.57 m	91.4 m	500 yd ²	15'	300'
	520 m ²	5.21 m	99.9 m	622 yd ²	17.1'	328'

Physical properties reflect industry standards. Roll Data may reflect higher values than those listed above.

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.