

# MINE-SHIELD GRID™ ROOF80

HIGH STRENGTH PET MINING GRID (FRAS COATED)



Mine-Shield Grid™ Roof80 is an innovative high-strength geogrid coated with durable FRAS (fire retardant anti-static coating) and is designed typically for mine roof applications. Corrosion resistant and light weight, this geogrid is manufactured with high-molecular weight, high-tenacity polyester yarns using a precision knitting process. It is dimensionally stable with a uniform aperture network that provides significant tensile reinforcement capacity in two directions. Featuring high tensile strength, stiffness and confinement.

Mine-Shield Grid™ Roof80 works to effectively prevent rock intrusions from mine roofs and ribs. It is engineered to withstand both harsh construction and aggressive soil environments and is unaffected by soil micro-organisms.

| TESTED PROPERTY                            | TEST METHOD    | UNIT ENGLISH<br>(METRIC) | VALUE ENGLISH<br>(METRIC) |              |
|--------------------------------------------|----------------|--------------------------|---------------------------|--------------|
|                                            |                |                          | MD                        | XD           |
| Ultimate Tensile Strength <sup>(1)</sup>   | ASTM D 6637    | lbs/ft (kN/m)            | 5,482 (80)                | 5,482 (80)   |
| Strain at Ultimate <sup>(1)</sup>          | ASTM D 6637    | %                        | 13                        | 13           |
| Secant Modulus at 5% Strain <sup>(1)</sup> | ASTM D 6637    | lbs/ft (kN/m)            | 30,287 (442)              | 30,287 (442) |
| Flammability Resistance                    | UL-94 Modified |                          | PASSES                    |              |
| Anti Static Resistance                     | MTI41-2005     |                          | PASSES                    |              |
| PHYSICAL PROPERTIES                        |                |                          |                           |              |
| Aperture Size <sup>(2)(3)</sup>            | Nominal        | mm (inch)                | 65 (2.56)                 | 65 (2.56)    |
| Mass/Unit Area <sup>(2)</sup>              | ASTM D 5261    | g/m² (oz/yd²)            | 650 (19.17)               |              |
| Roll Width                                 | Minimum        | m (ft)                   | 5.0 (16.4)                |              |
| Roll Length <sup>(4)</sup>                 | Minimum        | m (ft)                   | 300 (984.3)               |              |

Notes:

(1) Minimum Average Roll Values (MARV) – Calculated as (mean minus 2x standard deviation) as per ASTM D4759-02.

(2) Average.

(3) Aperture tolerance: within +/- 10% coefficient of variance

(4) Typical – Standard roll lengths are shown. The products may be fabricated to custom lengths to suite the contractor's requirements.

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

## Titan Environmental Containment

Toll free: 1-866-327-1957 | [info@titanenviro.com](mailto:info@titanenviro.com) | [TitanEnviro.com](https://TitanEnviro.com)

Rev. April 2025