

TITAN XR-PW

30mil POTABLE WATER GEOMEMBRANE LINER



XR Reinforced Geomembranes are the strongest, most durable geomembranes in use today. They are chemically resistant to acids and oils and are specifically engineered to provide protection against a wide range of climates. XR products are a reinforced woven synthetic fabric made from an ethylene interpolymers alloy (EIA). Whether used in very hot or extremely cold temperatures, XR geomembranes retain their flexibility and perform better than any other geomembrane available. This product is NSF61 approved for potable water applications.

Base Fabric Type: Polyester

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Thickness	ASTM D 751	mil (mm) min	30 (0.76)
Basic Fabric Weight (Nominal)	ASTM D 751	oz/yd ² (g/m ²)	6.5 (220)
Weight	ASTM D 751	oz/yd ² (g/m ²)	30.0 ± 2 (1017 ± 70)
Tear Strength (Trapezoid Tear)	ASTM D 4533	lbs (N) min	35/35 (156/156)
Breaking Yield Strength (Grab Tensile)	ASTM D 751	lbf (N) min	550/550 (2450/2450)
Low Temperature (4hr - 1/8" mandrel)	ASTM D 2136	Pass	@ -30°F (-34°C)
Dimensional Stability (100 °C/1 hour)	ASTM D 1204	%	0.5 @ max. each direction
Adhesion Heat Sealed Seam (Dielectric Weld)	ASTM D 751	lbf/in (daN/cm) min	20/2 (9/5)
Dead Load - Seam Shear Strength	ASTM D 751		2" (5 cm) seam, 4hr, 1" (2.5 cm) strip 210 lbf (935 N) @ 71 °F (21 °C) 105 lbf (465 N) @ 160 °F (70 °C)
Busting Strength (Ball Tip)	ASTM D 751	lbf (N)	750 (3340)
Hydrostatic Resistance (Method A)	ASTM D 751	psi (MPa) min	800 (5.52)
Blocking Resistance (180°F /82°C)	ASTM D 1204		#2 Rating Max
Adhesion – Ply	ASTM D 413	lb/in (daN/cm) min or Film Tearing Bond	7.5 (6.5/5)
Bonded Seam Strength (as modified by NSF 54)	ASTM D 751	lbs (N) min	550 (2450)
Abrasion Resistance(H-18 Wheel 1000g load)	ASTM D 3389		2000 cycles (min) before fabric exposure 50 mg/100 cycles max weight loss
Weathering Resistance (Carbon-arc)	ASTM G-23		8000 hrs (min) – No appreciable changes or stiffening or cracking of coating
Water Absorption (Section 12, 7 days)	ASTM D 471		0.025 kg/m ² @ 70 °F/21 °C 0.14 kg/m ² max @ 212 °F/100 °C
Wicking	ASTM D 751		1/8" (0.3cm) Max
Puncture Resistance	ASTM D 4833	lbf (N) min	275 (1225)
Coefficient of Thermal Expansion/ Contraction	ASTM D 696		8 x 10 ⁻⁶ in/in ° F (1.4 x 10 ⁻⁵ cm/cm/°C) max

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

Titan Environmental Containment | Titan Environmental USA

Toll free: 1-866-327-1957 | info@titanenviro.com | TitanEnviro.com

Rev. March 2025