

GEOTEXTILES 3100T

Product Data Sheet

Issue: 01.TGT20 Date: 06.13 Page: 1 of 1

Product Grade				3100T
Mechanical Properties		Standard	Unit	Value
CBR Puncture Resistance		ASTM D1883	lbs	697
Probe Analysis		ASTM D4833	lbs	111
TexTest Air Permeability		ASTM D737	cfm	10.3
Sheet Grab Tensile Strength	(MD)	ASTM D4632	lbs	454
	(CD)			422
Sheet Trapezoid Tear	(MD)	ASTM D4533	lbs	127
	(CD)			94
Hydraulic Properties				
Water Permeability		ASTM D4491	cm/sec	0.009
Water Permittivity		ASTM D4491	sec ⁻¹	0.123
Apparent Opening Size (95%)		ASTM D4751	US Sieve	200
Physical Properties				
Thickness		ASTM D1777	mils	28
Weight		ASTM D5261	oz./yd ²	10
Endurance (MARV)				
UV Resistance @ 500 hrs		ASTM D4355	%	70

As part of its continual improvement process, Fiberweb, Inc. reserves the right to change the properties listed on this data sheet without prior notice.

* indicates a registered trademark of Fiberweb, Inc. or a Fiberweb Group company, many of which are registered in a number of countries around the world.