




US 105NWE

Environmental Nonwoven Geotextile



US 105NWE is a 4 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 105NWE is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13. US 105NWE meets the following M.A.R.V. values:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	ASTM D-5261	4 oz/y ²	135.6 g/m ²
Thickness ⁽¹⁾	ASTM D-5199	70 mils	1.778 mm
Grab Tensile Strength	ASTM D-4632	105 lbs	467 N
Elongation @ Break	ASTM D-4632	50 %	50 %
CBR Puncture	ASTM D-6241	305 lbs	1,357 N
Trapezoidal Tear	ASTM D-4533	45 lbs	200 N
Apparent Opening Size ^(1,2)	ASTM D-4751	70 US Sieve	0.21 mm
Permittivity ⁽¹⁾	ASTM D-4491	2 Sec ⁻¹	2 Sec ⁻¹
Permeability ⁽¹⁾	ASTM D-4491	0.55 cm/sec	0.55 cm/sec
Water Flow Rate ⁽¹⁾	ASTM D-4491	160 g/min/f ²	6,518 L/min/m ²
UV Resistance @ 500 Hours	ASTM D-4355	70 %	70 %

⁽¹⁾ At the time of manufacturing. Handling, storage, and shipping may change these properties.

⁽²⁾ Maximum average roll value (MaxARV).

US 105NWE Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 1,350'	31"	15'	620 lbs	2,250 y ²	27

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.