



US 135NW

Nonwoven Geotextile



US 135NW is a nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. Primarily used in drainage applications, this product prevents soil fines from entering the system extending drain life and performance and can also be used in lightweight separation applications. US 135NW meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight Typical	ASTM D-5261	5 oz/y ²	169.5 g/m ²
Grab Tensile Strength	ASTM D-5261	135 lbs	601 N
Elongation @ Break	ASTM D-4632	50 %	50 %
Mullen Burst ⁽³⁾	ASTM D-3786	250 psi	1,724 kPa
Pin Puncture ⁽³⁾	ASTM D-4833	75 lbs	334 N
CBR Puncture	ASTM D-6241	350 lbs	1,558 N
Trapezoidal Tear	ASTM D-4533	55 lbs	245 N
Apparent Opening Size ^(1,2)	ASTM D-4751	70 US Sieve	0.21 mm
Permittivity ^(1,2)	ASTM D-4491	1.6 Sec ⁻¹	1.6 Sec ⁻¹
Water Flow Rate ⁽¹⁾	ASTM D-4491	115 g/min/f ²	4,685 L/min/m ²
UV Resistance @ 500 Hours	ASTM D-4355	70 %	70 %

⁽¹⁾ At the time of manufacturing. Handling, storage, and shipping may change these properties.

⁽²⁾ Maximum average roll value (MaxARV).

⁽³⁾ Historical reference values. These properties are no longer recognized by ASTM or AASHTO for geosynthetics.

US 135NW Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
12.5' x 360'	15"	12.5'	215 lbs	500 y ²	175
15' x 300'	15"	15'	215 lbs	500 y ²	156

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.