





# US 150P

## Nonwoven Geotextile



US 150P is a nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 150P resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 150P meets the following M.A.R.V. values except where noted:



| PROPERTY                  | TEST METHOD        | ENGLISH               | METRIC                 |
|---------------------------|--------------------|-----------------------|------------------------|
| Weight                    | <u>ASTM D-5261</u> | 6 oz/y <sup>2</sup>   | 203.4 g/m <sup>2</sup> |
| Grab Tensile Strength     | <u>ASTM D-4632</u> | 150 lbs               | 668 N                  |
| Elongation @ Break        | <u>ASTM D-4632</u> | 50 %                  | 50 %                   |
| UV Resistance @ 500 Hours | <u>ASTM D-4355</u> | 70 %                  | 70 %                   |
| Asphalt Retention         | <u>ASTM D-6140</u> | 0.24 g/y <sup>2</sup> | 1.1 l/m <sup>2</sup>   |
| Melting Point             | <u>ASTM D-276</u>  | 300 F                 | 149 C                  |

## US 150P Shipping & Packaging Information

| SIZE         | DIAMETER | WIDTH | WEIGHT  | AREA               | ROLLS PER TRAILER |
|--------------|----------|-------|---------|--------------------|-------------------|
| 6.25' x 360' | 13"      | 6.25' | 90 lbs  | 250 y <sup>2</sup> | 300               |
| 10.5' x 360' | 13"      | 10.5' | 135 lbs | 420 y <sup>2</sup> | 178               |
| 12.5' x 360' | 13"      | 12.5' | 150 lbs | 500 y <sup>2</sup> | 240               |
| 15' x 360'   | 13"      | 15'   | 170 lbs | 600 y <sup>2</sup> | 198               |

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
US Fabrics assumes no liability in connection with the use of this information.