




US 230

Woven Filtration



NTPEP APPROVED - GTX-2019-01-284. US 230 is a woven monofilament filtration geotextile made of 100% high-tenacity polypropylene yarns. US 230 resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 230 will satisfy the requirements as outlined in AASHTO M-288-06 for Permanent Erosion Control & Subsurface Drainage (<15% fines) and meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength	ASTM D-4632	400 x 315 lbs	1,780 x 1,402 N
Elongation @ Break	ASTM D-4632	15 %	15 %
Wide Width Tensile Strength	ASTM D-4595	3,000 x 2,760 lbs/ft	43.78 x 48.28 kN/m
CBR Puncture	ASTM D-6241	1,150 lbs	5,118 N
Trapezoidal Tear	ASTM D-4533	150 x 165 lbs	668 x 734 N
Apparent Opening Size ^(1,2)	ASTM D-4751	40 US Sieve	0.425 mm
Permittivity ⁽¹⁾	ASTM D-4491	0.9 Sec ⁻¹	0.9 Sec ⁻¹
Permeability ⁽¹⁾	ASTM D-4491	0.07 cm/sec	0.07 cm/sec
Water Flow Rate ⁽¹⁾	ASTM D-4491	70 g/min/f ²	2,852 L/min/m ²
Percent Open Area	CW-02215	1 %	1 %
UV Resistance @ 500 Hours	ASTM D-4355	90 %	90 %

⁽¹⁾ At the time of manufacturing. Handling, storage, and shipping may change these properties.

⁽²⁾ Maximum average roll value (MaxARV).

US 230 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 300'	13"	15'	320 lbs	500 y ²	135

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.