



# US 2800

## Woven Geotextile



US 2800 is a woven geotextile made of 100% high-tenacity polypropylene yarns. US 2800 resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 2800 meets the following M.A.R.V. values except where noted:



| PROPERTY                                 | TEST METHOD                 | ENGLISH                 | METRIC                     |
|------------------------------------------|-----------------------------|-------------------------|----------------------------|
| Grab Tensile Strength                    | <a href="#">ASTM D-4632</a> | 320 x 320 lbs           | 1,424 x 1,424 N            |
| Elongation @ Break                       | <a href="#">ASTM D-4632</a> | 15 %                    | 15 %                       |
| Wide Width Tensile Strength              | <a href="#">ASTM D-4595</a> | 3,200 x 2,800 lbs/ft    | 46.6 x 40.8 kN/m           |
| Wide Width Tensile Strength @ 2 % Strain | <a href="#">ASTM D-4595</a> | 600 x 600 lbs/ft        | 0.813 x 0.813 kN/m         |
| CBR Puncture                             | <a href="#">ASTM D-6241</a> | 1,000 lbs               | 4,450 N                    |
| Trapezoidal Tear                         | <a href="#">ASTM D-4533</a> | 125 lbs                 | 556 N                      |
| Apparent Opening Size <sup>(1,2)</sup>   | <a href="#">ASTM D-4751</a> | 40 US Sieve             | 0.425 mm                   |
| Permittivity <sup>(1)</sup>              | <a href="#">ASTM D-4491</a> | 0.7 Sec <sup>-1</sup>   | 0.7 Sec <sup>-1</sup>      |
| Water Flow Rate <sup>(1)</sup>           | <a href="#">ASTM D-4491</a> | 50 g/min/f <sup>2</sup> | 2,035 L/min/m <sup>2</sup> |
| UV Resistance @ 500 Hours                | <a href="#">ASTM D-4355</a> | 80 %                    | 80 %                       |

<sup>(1)</sup> At the time of manufacturing. Handling, storage, and shipping may change these properties.

<sup>(2)</sup> Maximum average roll value (MaxARV).

## US 2800 Shipping & Packaging Information

| SIZE       | DIAMETER | WIDTH | WEIGHT  | AREA               | ROLLS PER TRAILER |
|------------|----------|-------|---------|--------------------|-------------------|
| 15' x 300' | 11"      | 15'   | 240 lbs | 500 y <sup>2</sup> | 175               |

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
US Fabrics assumes no liability in connection with the use of this information.