




US 450NWE

Environmental Nonwoven Geotextile



US 450NWE is a 20 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 450NWE is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13. US 450NWE meets the following M.A.R.V. values:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	ASTM D-5261	20 oz/y ²	678 g/m ²
Grab Tensile Strength	ASTM D-4632	450 lbs	2,003 N
Elongation @ Break	ASTM D-4632	50 %	50 %
CBR Puncture	ASTM D-6241	1,437 lbs	6,395 N
Trapezoidal Tear	ASTM D-4533	125 lbs	556 N
UV Resistance @ 500 Hours	ASTM D-4355	70 %	70 %

US 450NWE Shipping & Packaging Information

SIZE	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15 x 300	15'	675 lbs	500 y ²	27

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: [\(800\) 518-2290](tel:8005182290) | Fax: [\(513\) 271-4420](tel:5132714420) | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.