




US 4800

Woven Geotextile



NTPEP APPROVED - GTX-2019-01-291 US 4800 is a woven geotextile made of 100% high-tenacity polypropylene yarns. US 4800 resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 4800 meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength	ASTM D-4632	500 lbs	2,225 N
Elongation @ Break	ASTM D-4632	15 %	15 %
Wide Width Tensile Strength	ASTM D-4595	4,800 x 4,800 lbs/ft	70.05 x 70.05 kN/m
CBR Puncture	ASTM D-6241	1,250 lbs	5,563 N
Trapezoidal Tear	ASTM D-4533	180 lbs	801 N
Apparent Opening Size ^(1,2)	ASTM D-4751	30 US Sieve	0.595 mm
Permittivity ⁽¹⁾	ASTM D-4491	0.15 Sec ⁻¹	0.15 Sec ⁻¹
Water Flow Rate ⁽¹⁾	ASTM D-4491	10 g/min/f ²	407.4 L/min/m ²
UV Resistance @ 500 Hours	ASTM D-4355	70 %	70 %

⁽¹⁾ At the time of manufacturing. Handling, storage, and shipping may change these properties.

⁽²⁾ Maximum average roll value (MaxARV).

US 4800 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 300'	16"	15'	420 lbs	500 y ²	104

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.