




# US 600NWE

## Environmental Nonwoven Geotextile



US 600NWE is a 32 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 600NWE is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13. US 600NWE meets the following M.A.R.V. values:



| PROPERTY                  | TEST METHOD                 | ENGLISH              | METRIC                   |
|---------------------------|-----------------------------|----------------------|--------------------------|
| Weight                    | <a href="#">ASTM D-5261</a> | 32 oz/y <sup>2</sup> | 1,084.8 g/m <sup>2</sup> |
| Grab Tensile Strength     | <a href="#">ASTM D-4632</a> | 600 lbs              | 2,670 N                  |
| Elongation @ Break        | <a href="#">ASTM D-4632</a> | 50 %                 | 50 %                     |
| CBR Puncture              | <a href="#">ASTM D-6241</a> | 2,287 lbs            | 10,177 N                 |
| Trapezoidal Tear          | <a href="#">ASTM D-4533</a> | 270 lbs              | 1,201 N                  |
| UV Resistance @ 500 Hours | <a href="#">ASTM D-4355</a> | 70 %                 | 70 %                     |

## US 600NWE Shipping & Packaging Information

| SIZE     | DIAMETER | WIDTH | WEIGHT  | AREA               |
|----------|----------|-------|---------|--------------------|
| 15 x 150 | 25"      | 15'   | 550 lbs | 250 y <sup>2</sup> |

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
US Fabrics assumes no liability in connection with the use of this information.