



US 640

Woven Filtration

EROSION CONTROL




BULKHEAD



RIP-RAP



FILTRATION



US 640 is a woven monofilament filtration geotextile made of 100% high-tenacity polypropylene yarns. US 640 resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 640 has a Percent Open Area of 6% and resists clogging. US 640 meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength	ASTM D-4632	350 x 200 lbs	1,558 x 890 N
Elongation @ Break	ASTM D-4632	15 %	15 %
CBR Puncture	ASTM D-6241	800 lbs	3,560 N
Trapezoidal Tear	ASTM D-4533	100 x 70 lbs	445 x 312 N
Apparent Opening Size ^(1,2)	ASTM D-4751	40 US Sieve	0.425 mm
Permittivity ⁽¹⁾	ASTM D-4491	0.5 Sec ⁻¹	0.5 Sec ⁻¹
Water Flow Rate ⁽¹⁾	ASTM D-4491	60 g/min/f ²	2,444 L/min/m ²
Percent Open Area	CW-02215	6 %	6 %
UV Resistance @ 500 Hours	ASTM D-4355	90 %	90 %

⁽¹⁾ At the time of manufacturing. Handling, storage, and shipping may change these properties.

⁽²⁾ Maximum average roll value (MaxARV).

⁽³⁾ Historical reference values. These properties are no longer recognized by ASTM or AASHTO for geosynthetics.

US 640 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
6' x 300'	9"	6'	89 lbs	200 y ²	488
12' x 300'	9"	12'	175 lbs	400 y ²	250

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.