




US 670

Woven Filtration



NTPEP APPROVED - GTX-2019-01-285. US 670 is a woven, monofilament filtration geotextile made of 100% high-tenacity polypropylene yarns. A Percent Open Area of 4% gives it excellent hydraulic properties, while reducing the chances of clogging. US 670 resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 670 will satisfy the requirements as outlined in AASHTO M-288-06 for Permanent Erosion Control & Subsurface Drainage Class 2 & 3 (>15% fines) and meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength	ASTM D-4632	370 x 250 lbs	1,647 x 1,113 N
Elongation @ Break	ASTM D-4632	15 %	15 %
Wide Width Tensile Strength	ASTM D-4595	2,700 x 1,740 lbs/ft	39.4 x 25.4 kN/m
CBR Puncture	ASTM D-6241	950 lbs	4,228 N
Trapezoidal Tear	ASTM D-4533	100 x 60 lbs	445 x 267 N
Apparent Opening Size ^(1,2)	ASTM D-4751	70 US Sieve	0.21 mm
Permittivity ⁽¹⁾	ASTM D-4491	0.28 Sec ⁻¹	0.28 Sec ⁻¹
Permeability ⁽¹⁾	ASTM D-4491	0.01 cm/sec	0.01 cm/sec
Water Flow Rate ⁽¹⁾	ASTM D-4491	18 g/min/f ²	733.4 L/min/m ²
Percent Open Area	CW-02215	4 %	4 %
UV Resistance @ 500 Hours	ASTM D-4355	90 %	90 %

⁽¹⁾ At the time of manufacturing. Handling, storage, and shipping may change these properties.

⁽²⁾ Maximum average roll value (MaxARV).

US 670 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
12' x 300'	9"	12'	210 lbs	400 y ²	209
6' x 300'	9"	6'	105 lbs	200 y ²	419

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.