





US 90P

Nonwoven Geotextile



US 90P is a nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. Primarily used in asphalt overlay applications, US 90P will act as a moisture barrier and will retard reflective cracking when installed properly. US 90P resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 90P meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	ASTM D-5261	3.8 oz/y ²	128.82 g/m ²
Grab Tensile Strength	ASTM D-4632	90 lbs	401 N
Elongation @ Break	ASTM D-4632	50 %	50 %
CBR Puncture	ASTM D-6241	275 lbs	1,224 N
Trapezoidal Tear	ASTM D-4533	35 lbs	156 N
UV Resistance @ 500 Hours	ASTM D-4355	70 %	70 %
Asphalt Retention	ASTM D-6140	0.24 g/y ²	1.1 l/m ²
Melting Point	ASTM D-276	300 F	149 C

US 90P Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
6.25' x 360'	12"	6.25'	90 lbs	250 y ²	300
10.5' x 360'	12"	10.5'	135 lbs	420 y ²	178
12.5' x 360'	12"	12.5'	150 lbs	500 y ²	240
15' x 360'	12"	15'	170 lbs	600 y ²	198

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.