




US HT400

High Modulus Woven Geotextile



US HT400 is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. US HT400 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals. US HT400 meets the following M.A.R.V. values except where noted:

PROPERTY	TEST METHOD	ENGLISH	METRIC
Interaction Coefficient ³	<u>ASTM D-6706</u>	0.89	0.89
Wide Width Tensile Strength @ 2 % Strain	<u>ASTM D-4595</u>	600 x 1,020 lbs/ft	8.76 x 14.89 kN/m
Wide Width Tensile Strength @ 5 % Strain	<u>ASTM D-4595</u>	1,800 x 2,256 lbs/ft	26.27 x 32.92 kN/m
Tensile Modulus @ 2% Strain	<u>ASTM D-4595</u>	53,000 lbs/ft(XD)	773.48 kN/m(XD)
Tensile Modulus @ 5% Strain	<u>ASTM D-4595</u>	46,500 lbs/ft(XD)	678.62 kN/m(XD)
Apparent Opening Size ^(1,2)	<u>ASTM D-4751</u>	40 US Sieve	0.425 mm
Permittivity ⁽¹⁾	<u>ASTM D-4491</u>	1.09 Sec ⁻¹	1.09 Sec ⁻¹
Water Flow Rate ⁽¹⁾	<u>ASTM D-4491</u>	80 gal/min/f ²	3,260 L/min/m ²
UV Resistance @ 500 Hours	<u>ASTM D-4355</u>	90 %	90 %

(1) At the time of manufacturing. Handling, storage, and shipping may change these properties.

(2) Maximum average roll value (MaxARV).Maximum average roll value (MaxARV)

(3) Interaction Coefficient value is for Sand (SP) or Gravel (GW) based on testing conducted by SGI Testing Services.

US HT400 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 300'	15"	15'	345 lbs	500 y ²	112

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.