




Synteon SC46K

Woven High Strength Polyester



Synteon SC46K is composed of high molecular weight, high tenacity multifilament polyester yarns that are woven into a stable network placed under tension. Synteon SC46K is inert to biological degradation and is resistant to naturally encountered chemicals, alkalis and acids.



PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Tensile Strength	ASTM D-4595	46,150 lbs/ft	673.5 kN/m
Tensile Strength @ 5 % Strain	ASTM D-4595	19,000 lbs/ft	277.3 kN/m
(LTDS) Long Term Design Strength	GRI-GT7	23,546 lbs/ft	343.6 kN/m
Partial Factor -Environmental Effects Environment, 3 < pH < 9	GRI-GG7, GRI-GG8	1.1 RFd	1.1 RFd
Reduction Factor - Creep	ASTM D-5262/D-6992	1.51 RFcr	1.51 RFcr
Partial Factor -Installation Damage (sand/silt/clay)	ASTM D-5818	1.18 RFid	1.18 RFid

Synteon SC46K Shipping & Packaging Information

SIZE	WIDTH	AREA
16.4' x 300'	16.4'	546.67 y ²

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.