



## REINFORCING SUCCESS

# PRODUCT DATA SHEET WINFAB® 100SFDT-36/06/1.5

**WINFAB® 100SFDT-36/06/1.5** is a preassembled silt fence unit composed of **WINFAB® 100SFDT** silt fence fabric with draw tape as well as the components listed in the chart below.

| ASSEMBLED UNIT PROPERTY | TEST METHOD | TYPICAL ENGLISH            | TYPICAL METRIC                   |
|-------------------------|-------------|----------------------------|----------------------------------|
| Post Size               | Measured    | 1.5 x 1.5 x 48 in Nominal  | 38.1 x 38.1 x 1,219.2 mm Nominal |
| Post Spacing            | Measured    | 6 ft                       | 1.83 m                           |
| Post Composition        | -           | Hardwood with Pencil Point |                                  |
| Fabric Height           | Measured    | 36 in                      | .914 m                           |
| Unit Length             | Measured    | 100 ft                     | 30.48 m                          |

**WINFAB 100SFDT** is a silt fence fabric manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. It resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals. It meets or exceeds the requirements of AASHTO M288 for unsupported silt fence and ASTM D6461 table 1.

| PROPERTY                  | TEST METHOD | MARV ENGLISH          | MARV METRIC            |
|---------------------------|-------------|-----------------------|------------------------|
| Tensile Strength (Grab)   | ASTM D4632  | 124 x 105 lbs         | 551.6 x 467.3 N        |
| Elongation (Grab)         | ASTM D4632  | 15% x 15%             | 15% x 15%              |
| Trapezoidal Tear Strength | ASTM D4533  | 65 x 65 lbs           | 289.1 x 289.1 N        |
| CBR Puncture              | ASTM D6241  | 300 lbs               | 1,335 N                |
| UV Resistance (500 hrs)   | ASTM D4355  | 70%                   | 70%                    |
| Apparent Opening Size*    | ASTM D4751  | 30 US Std. Sieve      | 0.60 mm                |
| Permittivity              | ASTM D4491  | .05 sec <sup>-1</sup> | .05 sec <sup>-1</sup>  |
| Water Flow Rate           | ASTM D4491  | 4 gpm/ft <sup>2</sup> | 163 lpm/m <sup>2</sup> |

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

WINFAB® &  are trademarks of Willacoochee Industrial Fabrics, Inc.

©2023 Willacoochee Industrial Fabrics Inc.

**WINFAB | [www.winfabusa.com](http://www.winfabusa.com)**  
1 Nashville Mills Rd. Nashville GA 31639  
Ph: (912) 534-5757 • Fax: (912) 534-5533

