




REINFORCING SUCCESS

WINFAB® 2098R is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.

WINFAB® 2098R resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals. It meets or exceeds the requirements of AASHTO M288 for unsupported silt fence and ASTM D6461 table 2.



PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D4632	370 x 250 lbs	1,646 x 1,112 N
Elongation (Grab)	ASTM D4632	15% x 15%	15% x 15%
Trapezoidal Tear Strength	ASTM D4533	65 x 65 lbs	289 x 289 N
Mullen Burst	ASTM D3786	450 psi	3,103 kPa
Index Puncture	ASTM D4833	130 lbs	578 N
UV Resistance (500 hrs)	ASTM D4355	80%	80%
Apparent Opening Size*	ASTM D4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D4491	1 sec ⁻¹	1 sec ⁻¹
Water Flow Rate	ASTM D4491	75 gpm/ft ²	3,055 lpm/m ²

*Maximum Average Roll Value

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	36 in x 330 ft 36 in x 2,250 ft 42 in x 1500 ft	.91 m x 914.4 m .91 m x 100.6 m 1.07 x 457.2 m

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

WINFAB® &  are trademarks of Willacoochee Industrial Fabrics, Inc.

©2021 Willacoochee Industrial Fabrics Inc.

WINFAB | www.winfabusa.com
1 Nashville Mills Rd. Nashville GA 31639
Ph: (912) 534-5757 • Fax: (912) 534-5533

