



# PRODUCT DATA SHEET

## WINFAB® 800NE

### WINFAB® 800NE-USA

**WINFAB® 800NE & WINFAB® 800NE-USA** needle-punched nonwoven geotextile is manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

**WINFAB® 800NE & WINFAB® 800NE-USA** needle-punched nonwoven geotextile resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.



DRAINAGE



FILTRATION



CUSHION / PROTECTION



SEPARATION

| PROPERTY                | TEST METHOD | MARV ENGLISH              | MARV METRIC               |
|-------------------------|-------------|---------------------------|---------------------------|
| Weight                  | ASTM D5261  | 8.0 oz/yd <sup>2</sup>    | 272 g/m <sup>2</sup>      |
| Thickness               | ASTM D5199  | 100 mils                  | 2.5 mm                    |
| Grab Tensile Strength   | ASTM D4632  | 225 x 225 lbs             | 1001 x 1001 N             |
| Grab Tensile Elongation | ASTM D4632  | 50% x 50%                 | 50% x 50%                 |
| Trapezoid Tear Strength | ASTM D4533  | 90 x 90 lbs               | 400 x 400 N               |
| CBR Puncture Strength   | ASTM D6241  | 600 lbs                   | 2669 N                    |
| UV Resistance (500 hrs) | ASTM D4355  | 70%                       | 70%                       |
| Apparent Opening Size*  | ASTM D4751  | 80 US Std. Sieve          | 0.180 mm                  |
| Permittivity            | ASTM D4491  | 1.26 sec <sup>-1</sup>    | 1.26 sec <sup>-1</sup>    |
| Permeability            | ASTM D4491  | 0.30 cm/sec <sup>-1</sup> | 0.30 cm/sec <sup>-1</sup> |
| Water Flow Rate         | ASTM D4491  | 100 gpm/ft <sup>2</sup>   | 4074 lpm/m <sup>2</sup>   |

\*Maximum Average Roll Value

### Domestic Procurement Preference

**WINFAB® 800NE-USA** is compliant with the Build America, Buy America (BABA) Act, Pub. L. No. 117-58, div. G §§ 70901-52. To ensure BABA documentation is appropriately captured and maintained throughout the manufacturing process, BABA (along with any other regulatory requirements) must be specified at the time of quotation and order to WINFAB. The inclusion of a “-USA” suffix on the end of the style name indicates the product is BABA certifiable.

| PROPERTY        | TEST METHOD | TYPICAL ENGLISH      | TYPICAL METRIC     |
|-----------------|-------------|----------------------|--------------------|
| Roll Dimensions | Measured    | 15 ft x 690 ft       | 4.6 m x 210.3 m    |
| Roll Area       | Measured    | 1150 yd <sup>2</sup> | 963 m <sup>2</sup> |

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The information listed above are subject to change without notice. Build America, Buy America Act, Pub. L. No. 117-58 certification is conditional for WINFAB 800NE, and is not a guarantee. Date Issued: 9.29.2023

WINFAB® &  WINFAB® are trademarks of Willacoochee Industrial Fabrics, Inc.

©2023 Willacoochee Industrial Fabrics Inc.

WINFAB | [www.winfabusa.com](http://www.winfabusa.com)  
1 Nashville Mills Rd. Nashville GA 31639  
Ph: (912) 534-5757 • Fax: (912) 534-5533

