



## PRODUCT DATA SHEET WINFAB CL Coir Log

**WINFAB CL** coir log is a type of Sediment Retention Fiber Roll (SRFR) manufactured using coir fibers for infill. The encasing of the wattle is made of natural, biodegradable coir fiber netting that is tubular in nature, flexible, and used to keep the dense coir fiber matrix in place to achieve sediment and flow control when in application.

**WINFAB CL** contains coir fibers are fungus-free, weed-free, and free of growth or germination inhibiting substances. The SRFR is designed to remain in place until fully established vegetation and root systems are present and can survive on their own. SRFRs not removed from jobsites will degrade in place.

| PROPERTY                 | TYPICAL ENGLISH       |
|--------------------------|-----------------------|
| Minimum Density          | 7 pcf +/- 10%         |
| Minimum Weight           | 5 lb +/- 10% per foot |
| Net Openings             | 2" x 2"               |
| Net Strength             | 90 lb                 |
| Wattle Dimension (D x L) | 12" x 10'             |

### Installation Guidelines

Installation of SRFRs are common on slopes, in channels, or around inlet/outlet drainage structures. Coir fiber based SRFRs do not require a shallow trench, and are typically installed lying flat on bare soil or over rolled erosion control products. The SRFR should be located so that it lies perpendicular to the flow of water. Care should be given to insure that the ends of the SRFR are overlapped a minimum of 6" to retain water and prevent its release from around the end of the SRFR. For proper spacing between SRFRs, follow project specifications.

SRFRs should be secured to the ground for stability. The most common method uses wooden stakes spaced every 2 linear feet along the length of the SRFR. Stake placement should be intertwined with the outer net only (on the downstream side only) and penetrating the ground a minimum of 16". Always make sure that at the end of SRFRs are overlapped, and that the overlapped areas are not in the middle of critical flow areas. If the SRFR is being installed on a hard surface, other securing devices should be used instead of wood stakes. The selection of the proper securing device for hard surfaces will depend upon the weight of the SRFR being used, the velocity of the water present, etc. Project specifications should always be reviewed for further installation guidance.

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The information listed above are subject to change without notice.

Date Issued: 2.6.2024

WINFAB® &  WINFAB® are trademarks of Willacoochee Industrial Fabrics, Inc.

©2023 Willacoochee Industrial Fabrics Inc.