

**WINFAB S2BD**

Product Data Sheet

Product Description: WINFAB S2BD Double Biodegradable Net Straw Blanket is a temporary rolled erosion control product (RECP) with a functional longevity of up to 12 months. The information below summarizes the product's typical physical properties at the time of manufacturing.

Size (WxL):	8' x 112.5'	16' x 112.5'	8' x 562.5'	16' x 562.5'
	Other custom sizes may be available upon request.			
Two Nets: Top & Bottom	Natural organic net with 0.5" x 1.0" net openings. Other net types, such as polypropylene and rapidly degrading, are available upon request.			
Stitch Spacing:	Degradable stitching is spaced 1.5 inches apart.			
Matrix:	Evenly distributed with 100% agricultural cured weed-free straw placed at a rate of 0.5 lbs/yd ² between two nets and stitched together.			
Packaging:	All rolls are wrapped tightly with stretch wrap to protect the RECP from the weather and elements.			

Typical Index & Performance Properties: The estimated values presented below are representative of results performed by third party laboratories who are NTPEP-contracted laboratories and are accredited through the Geosynthetic Accreditation Institute – Laboratory Accreditation Program.

TEST METHOD - DESCRIPTION	PARAMETERS	TEST RESULTS
ASTM D 6475 - Mass per Unit Area	Index Test	8.45 oz/sq.yd.
ASTM D 6818 - Ultimate Tensile Strength / Strain (MD & TD)	Index Test	15.8 lb/in 10.8 lb/in
ASTM D 6525 - Thickness	Index Test	302 mils
ASTM D 6567 - Ground Cover / Light Penetration	Index Test	88.5 % / 11.5 %
ASTM D 1117 & ECTC-TASC 00197 - Water Absorption	Index Test	476 %
ASTM D 7101 - Determination of Un-vegetated RECP Ability to Protect Soil from Rain Splash and Associated Runoff under Bench-Scale Conditions	50 mm (2 in.) / hr for 30 min. 100 mm (4 in.) / hr for 30 min. 150 mm (6 in.) / hr for 30 min.	Soil Loss Ratio ^{a,b} = 38.42 Soil Loss Ratio ^{a,b} = 22.33 Soil Loss Ratio ^{a,b} = 9.71
ASTM D 7207 - Determination of Un-vegetated RECP Ability to Protect Soil from Hydraulically-Induced Shear Stresses Under Bench-Scale Conditions	Shear: 1.14 psf for 30 min. Shear: 2.05 psf for 30 min. Shear: 2.73 psf for 30 min. Soil loss curve intercept =	Soil Loss ^b = 68.3 g Soil Loss ^b = 328.3 g Soil Loss ^b = 688.3 g 2.32 psf @ 1/2-in soil loss
ASTM D 7322 - Determination of Temporary Degradable RECP Performance in Encouraging Seed Germination and Plant Growth	Top soil; Fescue (Kentucky 31) 21 day incubation; 27±2° & approximately 45±5% RH	553 % (germination improvement)

a. Weight is based on a dry fiber weight at the time of manufacturing.

b. The soil loss ratio is as reported by NTPEP (soil loss bare soil / soil loss with RECP = 1/C-Factor where the soil loss is based on regression analysis.)

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The information listed above are subject to change without notice.

WINFAB &  WINFAB[®] are trademarks of Willacoochee Industrial Fabrics, Inc.

©2022 Willacoochee Industrial Fabrics Inc.



WINFAB | www.winfabusa.com
1 Nashville Mills Rd. Nashville GA 31639
Ph: (912) 534-5757 • Fax: (912) 534-5533

