Important information

The tables “Chemical resistance of plastics”, “Plastics and their properties” and “Viscosity of liquids" as well as the information about chemical resistance given in the particular product descriptions have been drawn up based on information provided by various raw material manufacturers. These values are based solely on laboratory tests with raw materials. Plastic components produced from these raw materials are frequently subject to influences that cannot be recognized in laboratory tests (temperature, pressure, material stress, effects of chemicals, construction features, etc.). For this reason the values given are only to be regarded as being guidelines. In critical cases it is essential that a test is carried out first. No legal claims can be derived from this information; nor do we accept any liability for it. A knowledge of the chemical and mechanical

Copyright

This table has been published and updated by Bürkle GmbH, D-79415 Bad Bellingen as a work of reference. This Copyright clause must not be removed. The table may be freely passed on and copied, provided that

Extensions, additions and translations

If your own experiences with materials and media could be used to extend this table then we would be pleased to receive any additional information. Please send an E-Mail to info@buerkle.de. We would also like to receive translations into other languages. Please visit our website at http://www.buerkle.de from time to

Thanks

Our special thanks to Franz Kass (Franzkass@aol.com), who has completed and extended these lists with great enthusiasm and his excellent specialist knowledge.

Publisher

Bürkle GmbH
Rheinauen 5
D-79415 Bad Bellingen
Tel +49 (76 35) 8 27 95-0
Fax +49 (76 35) 8 27 95-31
info@buerkle.de
http://www.buerkle.de

Version 2.0 (01.04.2003)

http://www.buerkle.de/en/knowhow/information/chemical-resistance.html

						thermoplastics												fluoroplastics				elastomers			metals			
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Acetaldehyde	C_2H_4O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	Acetic aldehyde; Ethanal; Ethyl aldehyde
Acetaldehyde	C_2H_4O	000075-07-0	techn. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Acetamide	C_2H_5NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	
Acetic acid	$C_2H_4O_2$	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	
Acetic acid	$C_2H_4O_2$	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	
Acetic acid	$C_2H_4O_2$	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	
Acetic acid chloride	-> see: Acetyl chloride																												
Acetic acid sodium salt	-> see: Sodium acetate																												
Acetic aldehyde	-> see: Acetaldehyde																												
Acetic anhydride	$C_4H_6O_3$	000108-24-7	techn. pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	
Acetic chloride	-> see: Acetyl chloride																												
Acetone	C_3H_6O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	Propanone, 2-; Dimethyl ketone; Methyl ketone
Acetonitrile	C_2H_3N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	Methyl cyanide; Cyanomethane; Ethanenitrile
Acetonyl chloride	-> see: Chloroacetone																												
Acetophenone	C_8H_8O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene
Acetyl chloride	C_2H_3ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	Acetic chloride; Ethanoyl chloride; Acetic acid chloride
Acetylene	C_2H_2	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	Ethine; Ethyne
Acetyloxybenzoic acid, 2-	-> see: Acetylsalicylic acid																												
Acetylsalicylic acid	$C_9H_8O_4$	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	Acetyloxybenzoic acid, 2-;
Acrylonitrile	C_3H_3N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide
Adipic acid	$C_6H_{10}O_4$	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	Hexanedioic acid; Butanedicarboxylic acid, 1,4-
Alanine, L-	$C_3H_7NO_2$	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)	Aminopropanoic acid, L-2; aminopropanoic acid, alpha-
Allspice	—	—	ground	?		0/0	0/0	(2)	4/4		0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	
Allyl acetate	$C_5H_8O_2$	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)	
Allyl alcohol	C_3H_6O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	Vinyl carbinol; Propenyl alcohol
Allyl chloride	C_3H_5Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	Chloro-1-propene, 3-; Chloropropylene, 3-
Allyl mustard oil	C_4H_5NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	oleum sinapis
Almond oil, sweet	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1	
Alumina acidic	$C_3H_7AlO_5 \times H_2O$	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1	
Aluminium fluoride	AlF_3	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	
Aluminum ammonium sulfate dodecahydrate	$(NH_4)Al(SO_4)_2$	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	
Aluminum chloride	$AlCl_3$	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	
Aluminum chloride	$AlCl_3$	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	
Aluminum chloride	$AlCl_3$	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	
Aluminum hydroxide	$Al(HO)_3$	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Aluminum nitrate	$Al(NO_3)_3$	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	
Aluminum oxide, alpha-	Al_2O_3	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Aluminum potassium sulfate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	
Aluminum potassium sulfate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	
Aluminum sodium sulfate	$NaAl(SO_4)_2$	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)	
Aluminum sulfate	$Al_2(SO_4)_3$	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	
Aluminum sulfate	$Al_2(SO_4)_3$	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	
Aminic acid	-> see: Formic acid																												
Aminoacetic acid	-> see: Glycine																												
Aminoethanol	C_2H_7NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Aminopropanoic acid, alpha	-> see: Alanine, L-																												
Ammonium acetate	$C_2H_7NO_2$	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	
Ammonium bicarbonate	CH_5NO_3	001066-33-7	saturated	Xi		1/1	1/1	1/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	(3)	0/0	1/1	1/1	1/1	
Ammonium bisulfide	$(NH_4)HS$	012124-99-1	each	T, C		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	(2)	0/0	(2)	(1)	(1)	Ammonium hydrogen sulfide; Ammonium hydrosulfide; Ammonium
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	50 %	Xn		1/1	1/1	1/0	3/0	0/0	1/0	(2)	1/1	1/1	1/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	aqueous	Xn		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	
Ammonium chloride	$(NH_4)Cl$	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	sal ammoniac

						thermoplastics												fluoroplastics			elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Ammonium chloride	$(NH_4)Cl$	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	sal ammoniac
Ammonium difluoride	F_2H_5N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0	
Ammonium ferric sulfate	$(NH_4)Fe(SO_4)_2$	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0	
Ammonium ferrous sulfate	$(NH_4)_2Fe(SO_4)_2$	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)	
Ammonium fluoride	$(NH_4)F$	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	
Ammonium fluoride	$(NH_4)F$	012125-01-8	aqueous	T. C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	
Ammonium glycolate	$C_2H_7NO_3$	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)	Acetic acid
Ammonium heptamolybdate	$(NH_4)_6Mo_7O_{24}$	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	
Ammonium mercaptan	-> see: Ammonium bisulfide																													
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	Nitric acid; Ammonium salt
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	
Ammonium nitrite	$(NH_4)NO_2$	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)	
Ammonium oxalate	$C_2H_8N_2O_4$	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	
Ammonium persulfate	$(NH_4)_2S_2O_8$	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	
Ammonium persulfate	$(NH_4)_2S_2O_8$	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	
Ammonium phosphate, Mono-	$(NH_4)H_2PO_4$	007722-76-1	each	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	
Ammonium polyphosphate (APP)	$(NH_4PO_3)_n$	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)	
Ammonium rhodanide	-> see: Ammonium thiocyanate																													
Ammonium salt	-> see: Ammonium nitrate																													
Ammonium sulfate	$(NH_4)_2SO_4$	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	
Ammonium sulfate	$(NH_4)_2SO_4$	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	
Ammonium sulfide	$(NH_4)_2S$	012135-76-1	each	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	Diammonium sulfide;
Ammonium sulfide	$(NH_4)_2S$	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	
Ammonium sulfocyanide	-> see: Ammonium thiocyanate																													
Ammonium thiocyanate	CH_4N_2S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)	Ammonium sulfocyanide; Ammonium rhodanide; Thiocyanic acid,
Amomum	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	
Amyl acetate, normal	$C_7H_{11}O_2$	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	
Amyl alcohol, n-	-> see: Pentanol, 1-																													
Amyl chloride	$C_5H_{11}Cl$	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	
Amyl cinnamic aldehyde	$C_{14}H_{18}O$	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)	odoriferous substance
Aniline	C_6H_7N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	
Aniline hydrochloride	$C_6H_3ClN_6$	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4	
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	
Anisole	C_7H_8O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	
Antifreeze agent (car)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	glycol-water-mixture
Antimony pentachloride	$SbCl_5$	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	
Antimony trichloride	$SbCl_3$	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	
Antimony trichloride	$SbCl_3$	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4	
Antimony trichloride	$SbCl_3$	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)	
Arsenic acid	H_3AsO_4	022538-92-7	aqueous	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	
Arsenic acid	H_3AsO_4	022538-92-7		T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	0/0	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	
Arsenic pentoxide	As_2O_5	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)	
Ascorbic acid	$C_6H_8O_6$	000050-81-7	aqueous	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	1/1	(1)	(1)	
Atropine sulfate	$C_{34}H_{48}N_2SO_{10}\text{-}H_2O$	000055-48-1		T+		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	
Azabenzene	-> see: Pyridine																													
Azacyclohexane	-> see: Piperidine																													
Azine	-> see: Pyridine																													
Azole	-> see: Pyrrole																													
Barium carbonate	$BaCO_3$	000513-77-9	saturated	Xn		1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	small solubility - no chemical effect expected

						thermoplastics												fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Barium chloride	$BaCl_2$	010361-37-2	saturated	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	
Barium chloride	$BaCl_2$	010361-37-2	aqueous	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	
Barium dibromide	$BaBr_2$	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	saturated	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	aqueous	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	
Barium sulfide	BaS	021109-95-5	saturated	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	
Battery acid	H_2SO_4	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	Sulfuric acid;
Beef tallow	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	
Beef tallow emulsion	—	—	sulfonated	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	
Beer	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	
Beeswax	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)	
Benzaldehyde	C_7H_6O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	artificial almond oil
Benzene	C_6H_6	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	Cyclohexatriene; Benzol
Benzene chloride	-> see: Chlorobenzene																												
Benzenesulfonic acid	$C_6H_6SO_3$	000098-11-3	saturated	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	
Benzoic acid	$C_7H_6O_2$	000065-85-0	saturated	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	
Benzoic acid	$C_7H_6O_2$	000065-85-0	aqueous	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	
Benzoic acid chloride	-> see: Benzoyl chloride																												
Benzoyl chloride	C_7H_5ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	Benzenecarbonyl chloride; Benzoic acid chloride
Benzyl acetate	$C_9H_{10}O_2$	000140-11-4		Xn/Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1	
Benzyl alcohol	C_7H_8O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	
Benzyl benzoate	$C_{14}H_{12}O_2$	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	
Benzyl chloride	C_7H_7Cl	000100-44-7	100 %	T/Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	
Benzyl ether	$C_{14}H_{14}O$	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	
Bismuth chloride	$BiCl_3$	007787-60-2		Xi		1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0	
Bismuth nitrate, basic	$Bi_5O(HO)_9(NO_3)_4$	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0	
Bisulfite solution	$NaHSO_3$	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	
Bisulfite solution, containing $S0_2$	$NaHSO_3$	??	saturated	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1	
Bitter almond oil	C_7H_6O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	mainly: benzaldehyde
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)	
Bone oil	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1	
Boric acid	H_3BO_3	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	
Boric acid	H_3BO_3	010043-35-3	aqueous	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	
Brake fluid	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)	
Bromic acid	$HBrO_3$	007789-31-3	concentrated	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	
Bromine	Br_2	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	
Bromine pentafluoride	BrF_5	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)	
Bromine steams	Br_2	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	
Bromine trifluoride	BrF_3	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)	
Bromine water	Br_2+H_2O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	
Bromobenzene	C_6H_5Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	
Bromochloromethane	CH_2BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	
Bromotrifluoromethane	$CBrF_3$	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	
Butadiene, 1,3-	C_4H_6	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	
Butanal	-> see: Butyraldehyde																												
Butane	C_4H_{10}	000106-97-8	techn. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	
Butanedicarboxylic acid, 1,4-	-> see: Adipic acid																												
Butanetriol	$C_4H_{10}O_3$	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	isomer not indicated in the source
Butanol	-> see: Butyl alcohol, normal																												
Butene	C_4H_8	—	techn. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	isomer not indicated in the source
Butoxybutane, 1-	-> see: Butyl ether, (Di-) n-																												
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)	
Butyl acetate, normal	$C_6H_{12}O_2$	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	
Butyl acrylate	$C_7H_{12}O_2$	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	

						thermoplastics													fluoroplastics			elastomers			metals			
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Butyl alcohol, normal	$C_4H_{10}O$	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	Propyl carbinol; Butanol
Butyl alcohol, sec-	$C_4H_{10}O$	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	Butanol, -2; Methyl ethyl carbinol; Butylene hydrate
Butyl alcohol, tert-	$C_4H_{10}O$	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	
Butyl aldehyde	-> see: Butyraldehyde																												
Butyl carbinol, n-	-> see: Pentanol, 1-																												
Butyl ether, (Di-) n-	$C_8H_{18}O$	000142-96-1	techn. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	Butoxybutane, 1-;
Butyl ethylene	-> see: Hexene, 1-																												
Butyl stearate	$C_{22}H_{44}O_2$	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	
Butylamine	$C_4H_{11}N$	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Butylene glycol	$C_4H_{10}O_2$	—	techn. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	isomer not indicated in the source
Butylene hydrate	-> see: Butyl alcohol, sec-																												
Butylphenol	$C_{10}H_{14}O$	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	isomer not indicated in the source
Butylphenol, p-tert	$C_{11}H_{16}NO$	000098-54-4	techn. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	
Butyraldehyde	C_4H_8O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	Butanal; Butyl aldehyde
Butyric acid	$C_4H_8O_2$	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0	
Calcium bicarbonate	$Ca(HCO_3)_2$	—	saturated	—		1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	
Calcium bisulfite	$Ca(HSO_3)_2$	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	
Calcium bisulfite	$Ca(HSO_3)_2$	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	
Calcium bromide	$CaBr_2$	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	
Calcium carbide	CaC_2	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	carbid, reacts with water to acetylene - highly flammable!
Calcium carbonate	$CaCO_3$	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Calcium chlorate	$Ca(ClO_3)_2$	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	
Calcium chloride	$CaCl_2$	010043-52-4	alkoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	
Calcium chloride	$CaCl_2$	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	
Calcium hydroxyde	CaH_2O_2	001305-62-0	aqueous	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	
Calcium hydroxyde	CaH_2O_2	001305-62-0	concentrated	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	bleaching powder
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	bleaching powder
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	
Calcium oxide	CaO	001305-78-8	powder	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1	
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	small solubility - no chemical effect expected
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	small solubility - no chemical effect expected
Calcium sulfate	$CaSO_4$	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	plaster
Calcium sulfide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	
Calcium sulfide	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	
Calciumacetat	$C_4H_6CaO_4$	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	
Camphor	$C_{10}H_{16}O$	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0		
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	from cinnamomum camphora
Caprylic alcohol	$C_8H_{18}O$	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)	
Caraway	—	—	ground	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)	
Carbazole	$C_{12}H_9N$	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	
Carbolineum	—	008001-58-9	aqueous	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	Creosote;
Carbon dioxide	CO_2	000124-38-9	saturated	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1	
Carbon dioxide, damp	CO_2	000124-38-9	techn. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	
Carbon dioxide, dry	CO_2	000124-38-9	techn. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	
Carbon disulfide	CS_2	000075-15-0		F+, T	X	4/4	4/4	3/0	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/3	1/1	1/0	1/1	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
Carbon tetrabromide	CBr_4	000558-13-4		Xn, Xi		0/0	0/0	(3)	4/4	0/0	0/0	(3)	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	
Carbon tetrachloride (TETRA)	CCl_4	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1L	1/1L	
Carbon tetrafluoride	CF_4	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	
Carbonyl chloride	-> see: Phosgene																												
Carnauba wax	—	008015-86-9		—		1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)	
Castor oil	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	

						thermoplastics												fluoroplastics				elastomers				metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Caustic potash	-> see: Potassium hydroxide																												
Cedar wood oil	—	008000-27-9		?		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)	
Cesium bromide	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0	
Cetyl alcohol	$C_{16}H_{34}O$	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1	
Chalk	$CaCO_3$	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	calcium carbonate
Chloral hydrate	$C_2H_3Cl_3O_2$	000302-17-0	techn. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	
Chloramine-T	$C_7H_7ClNaNSO_2$	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	
Chloric acid	$HClO_3$	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	
Chloric acid	$HClO_3$	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	
Chloric acid	$HClO_3$	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	
Chloric acid, sodium salt	-> see: Sodium chlorate																												
Chlorine	Cl_2	007782-50-5	10 % wet	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	
Chlorine	Cl_2	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0
Chlorine	Cl_2	007782-50-5	steam	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0
Chlorine dioxide	ClO_2	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4	
Chlorine trifluoride	ClF_3	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)	
Chlorine water	$Cl_2 \times H_2O$	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	
Chloro acetophenone, p-	C_8H_7ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0	
Chloro-1-propene, 3-	-> see: Allyl chloride																												
Chloro-2-propanone, 1-	-> see: Chloroacetone																												
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	
Chloroacetone	C_3H_5ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	Chloro-2-propanone, 1-; Acetonyl chloride; Monochloroacetone
Chlorobenzene	C_6H_5Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	1/1	1/1	Benzene chloride; Chlorobenzol; Monochlorobenzene (MCB); Phenyl
Chlorodifluoroethane	$C_2H_3ClF_2$	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0	
Chlorodifluoromethane	$CHClF_2$	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0	R 22
Chloroethane, 1-	-> see: Monochloroethane																												
Chloroethyl alcohol, 2-	C_2H_5ClO	000107-07-3	techn. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	
Chloroethylene	-> see: Vinyl chloride (VCM)																												
Chlorofluorocarbons (CFC)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0	resistance depends on type
Chlorofluoromethane	CH_2ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0	
Chloroform	$CHCl_3$	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	1/1	1/1	
Chloroformyl chloride	-> see: Phosgene																												
Chloronaphthalene, 1-	$C_{10}H_7Cl$	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0	
Chloropentafluoroethane	C_2ClF_5	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	
Chloroprene	C_4H_5Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0	
Chloropropylene, 3-	-> see: Allyl chloride																												
Chlorosulfonic acid	$ClHSO_3$	007790-94-5	techn. pure	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	
Chlorotoluene	C_7H_7Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	isomer not indicated in the source
Chlorotrifluoromethane	$CClF_3$	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	
Chromic acid	CrO_3	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	Chromium trioxide;
Chromic acid	CrO_3	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	
Chromic acid	CrO_3	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	
Chromic potassium sulfate	$KCr(SO_4)_2 \times 12H_2O$	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	
Chromic-sulfuric acid	$CrO_3 + H_2SO_4$	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	
Chromium salts	—	—	each	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K	
Chromium trioxide	-> see: Chromic acid																												
Cinnamaldehyde	C_9H_8O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)	
Cinnamon	—	—	ground	?		0/0	0/0	(2)	1/0	(2)	0/0	(2)	(2)	3/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	
Cinnamon oil	—	008007-80-5		Xn, Xi		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	
Citric acid	$C_6H_8O_7$	000077-92-9	10 %	Xi		1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	50 %	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	
Citric acid	$C_6H_8O_7$	000077-92-9	saturated	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	
Citrus juices	—	—	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1	

						thermoplastics													fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Cleaning agents	—	—		?		1/1	1/1	1/0	1/1	1/1	0/0		1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	(2)	0/0	1/1	1/1	1/1	
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	polychlorinated Biphenyls, PCB; Bayer
Coal gas, without benzene	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	
Cobalt dichloride	$CoCl_2$	007646-79-9	aqueous	Xn		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0	
Cocoa	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	
Cocoa butter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	
Coconut butter	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	
Coconut fatty alcohol	—	068425-37-6	techn. pure	(Xi)		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	
Coconut oil	—	008001-31-8	techn. pure	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	
Cod-liver oil	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	
Colza oil	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1	
Compressed air	—	—	oleagineus	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1	
Condy's crystals	-> see: Potassium permanganate																												
Copper acetate	$C_4H_6CuO_4$	004180-12-5	aqueous	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	verdigris
Copper sulfate	$CuSO_4 \times 5H_2O$	007758-99-8	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	blue stone
Cotton oil	—	008001-29-4	techn. pure	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1	
Creosote	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	
Creosote	-> see: Carbolineum																												
Cresol (-mixtures)	C_7H_8O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	
Crotonaldehyde	C_4H_6O	004170-30-3	techn. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	
Crude oil	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)	
Cumene	C_9H_{12}	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
Cupric chloride	$CuCl_2$	007447-39-4	saturated	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	
Cupric nitrate	$Cu(NO_3)_2$	003251-23-8	saturated	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	
Cupric nitrate	$Cu(NO_3)_2$	003251-23-8	aqueous	O, Xn		0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	
Cuprous chloride	CuCl	007758-89-6	aqueous	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	
Cuprous cyanide	CCuN	000544-92-3	saturated	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1	
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	possibility of discoloration
Cyanoethylene	-> see: Acrylonitrile																												
Cyanomethane	-> see: Acetonitrile																												
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	appliances for dyeing-mill; BASF
Cyclohexane	C_6H_{12}	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	
Cyclohexanol	$C_6H_{12}O$	000108-93-0	techn. pure	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	
Cyclohexanone	$C_6H_{10}O$	000108-94-1	techn. pure	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	
Cyclohexatriene	-> see: Benzene																												
Cymene, p-	$C_{10}H_{14}$	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
DDT (emulsion)	$C_{14}H_9Cl_5$	000050-29-3		T		0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	
Decahydronaphthalene	$C_{10}H_{18}$	000091-17-8		Xn		1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	
Decane	$C_{10}H_{22}$	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)	
Dehydroacetic acid	$C_8H_8O_4$	000520-45-6		Xn		0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)	
Densodrin W	—	—	aqueous	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0	appliance for moisture-proofing of leather; BASF
Desiccator fat	—	—		—		0/0	1/3	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)	
Desmodur 44	$C_{15}H_{10}N_2O_2$	000101-68-8		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)	
Developer for fotos	—	—		?		1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0	
Developer liquids	—	—		?		1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	
Dextrin	$(C_6H_{10}O_5)_n \times H_2O$	009004-53-9	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Diacetone alcohol	$C_6H_{12}O_2$	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)	
Diamine	-> see: Hydrazine																												
Diaminoethane	$C_2H_8N_2$	000107-15-3	techn. pure	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	
Diammonium sulfide	-> see: Ammonium sulfide																												
Diamyl phthalate	$C_{18}H_{26}O_4$	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	
Dibenzyl sebacate	$C_{24}H_{26}O_4$	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)	plasticiser
Dibromoethane, 1,2-	-> see: Ethylene dibromiden (EDB)																												
Dibromotetrafluoroethane	$C_2Br_2F_4$	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0	

						thermoplastics													fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Dibutyl phthalate, n-	$C_{16}H_{22}O_4$	000084-74-2	FR, 80℃	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	pla sticiser
Dibutyl phthalate, n-	$C_{16}H_{22}O_4$	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/1	plasticiser
Dibutyl sebacate	$C_{18}H_{34}O_4$	000109-43-3	techn. pure	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	plasticiser
Dibutylamine	$C_8H_{19}N$	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	techn. pure	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	
Dichlorobenzene, 1,2-	$C_6H_4Cl_2$	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	
Dichlorobenzene, 1,4-	$C_6H_4Cl_2$	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	
Dichlorodifluoromethane	CCl_2F_2	000075-71-8	techn. pure	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	
Dichlorodifluoromethane	CCl_2F_2	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	
Dichloroethane	$C_2H_4Cl_2$	—		F, T	X	3/3	2/4	3/0	4/4	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	isomer not indicated in the source
Dichloroethylene	$C_2H_2Cl_2$	—	techn. pure	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	isomer not indicated in the source
Dichlorofluoromethane	$CHCl_2F$	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0	
Dichlorohexafluorocyclobutane	$C_4Cl_2F_6$	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0	
Dichloroisopropyl ether	$C_6H_{12}Cl_2O$	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0	isomer not indicated in the source
Dichloropropane	$C_3H_6Cl_2$	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	isomer not indicated in the source
Dichlorotetrafluoroethane	$C_2Cl_2F_4$	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	
Dicyclohexyl phthalate	$C_{20}H_{26}O_4$	000084-61-7	techn. pure	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)	plasticiser
Dicyclohexylamine (DCHA)	$C_{12}H_{23}N$	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Diesel fuel	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	
Diesel fuel for heating	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	
Diesel oil	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	
Diethanolamine (DEA)	$C_4H_{11}NO_2$	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	
Diethyl ethyl	$C_4H_{10}O$	000060-29-7	techn. pure	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	
Diethyl ketone	-> see: Pentanone, 3-																													
Diethyl malonate	$C_7H_{12}O_4$	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)	(1)	
Diethyl sebacate	$C_{14}H_{26}O_4$	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)	plasticiser
Diethyl succinate	$C_8H_{14}O_4$	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)	
Diethylamine	$C_4H_{11}N$	000109-89-7	techn. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	
Diethylbenzene	$C_{10}H_{14}$	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
Diethylene glycol	$C_4H_{10}O_3$	000111-46-6		T		1/1	1/1	3/0	2/3	0/0	1/1	(2)	1/1	2/2	2/2	3/4	0/0	1/1	1/1	1/1	1/1	(2)	1/0	1/0	3/0	0/0	1/1	(1)	(1)	
Diethylene glycolether	—	—		(Xn)		1/1	1/1	3/0	3/4	0/0	1/1	(2)	1/1	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	3/0	(3)	3/3	0/0	(1)	(1)	(1)	
Difluoroethane	$C_2H_2F_2$	000075-37-6		(E), F+		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0	
Difluoromethane	CH_2F_2	000075-10-5		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0	
Diglycolic acid	$C_4H_6O_5$	000110-99-6	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/1	4/4	0/0	3/4	1/4	1/4	
Diglycolic acid	$C_4H_6O_5$	000110-99-6	30 %	Xn, Xi		1/1	1/1	(3)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/1	4/4	0/0	3/4	1/4	1/4	
Diisobutyl ketone	$C_9H_{18}O$	000108-83-8	techn. pure	Xi	X	1/4	1/3	(3)	(3)	(4)	(4)	1/0	1/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/3	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Diisobutylene (DIB)	C_8H_{10}	025167-70-8		F	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	1/2	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	1/0	3/3	0/0	1/1	1/1	1/1	
Diisopropyl ether	$C_6H_{14}O$	000108-20-3	techn. pure	F	X	3/4	3/4	4/4	(4)	1/0	(4)	(1)	3/4	4/4	1/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	
Di-isopropyl ketone	$C_7H_{14}O$	000565-80-0		F	X	0/0	0/0	(3)	(3)	(4)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(1)	(1)	(1)	
Dimethyl ether	C_2H_6O	000115-10-6	gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	
Dimethyl formamide (DMF)	C_3D_7NO	000068-12-2		T		1/1	1/3	1/0	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	(1)	(1)	
Dimethyl ketone	-> see: Acetone																													
Dimethyl phthalate (DMP)	$C_{10}H_{10}O_4$	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	plasticiser
Dimethyl sulfoxide (DMSO)	C_2H_6SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	
Dimethylacetone	-> see: Pentanone, 3-																													
Dimethylamine	C_2H_7N	000124-40-3	techn. pure	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Dimethylaniline	$C_8H_{11}N$	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	isomer not indicated in the source
Dinitro ethylene glycol	$C_2H_4(NO_3)_2$	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	
Dinonyl phthalate (DNP)	$C_{26}H_{42}O_4$	000084-76-4	techn. pure	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)	plasticiser
Dioctyl adipate	$C_{22}H_{42}O_4$	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	plasticiser
Dioctyl phthalate (DOP)	$C_{24}H_{38}O_4$	000117-81-7	techn. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)	plasticiser
Dioctyl sebacate	$C_{26}H_{50}O_4$	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)	plasticiser
Dioxane	$C_4H_8O_2$	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	

						thermoplastics												fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Diphenyl ether	$C_{12}H_{10}O$	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	
Diphenylamine	$C_{12}H_{11}N$	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	mixture with diphenyl and diphenyl ether; Bayer
Dipropyl ketone	$C_7H_{14}O$	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)	
Dipropylene glycol	$C_6H_{14}O_3$	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)	
Dipropylene glycol (mono)methyl ether	$C_4H_{10}O_2$	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	isomer not indicated in the source
Disodium phosphate	Na_2HPO_4	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	
Dispersion of rubber	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)	latex
Dithionous acid, disodium salt	-> see: Sodium hydrosulfite																												
Divinylene oxide	-> see: Furan																												
Dope, viscous ~	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K	
Emulsions for fotos	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0	
Ephetin	—	—	10% in water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Epichlorhydrin	C_3H_5ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	
Epoxypropane, 1,2-	-> see: Propylene oxid																												
Ethanal	-> see: Acetaldehyde																												
Ethanedioic acid	-> see: Oxalic acid																												
Ethanenitrile	-> see: Acetonitrile																												
Ethanoyl chloride	-> see: Acetyl chloride																												
Ethoxybenzene	$C_8H_{10}O$	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Ethyl phenyl ether; Phenyl ethyl ether; Phenetole
Ethyl acetate	$C_4H_8O_2$	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	
Ethyl acrylate	$C_5H_8O_2$	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Ethyl alcohol	C_2H_6O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	
Ethyl alcohol	C_2H_6O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	
Ethyl alcohol	C_2H_6O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	
Ethyl aldehyde	-> see: Acetaldehyde																												
Ethyl benzoate	$C_9H_{10}O_2$	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	
Ethyl butyrate	$C_6H_{12}O_2$	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)	
Ethyl chloride	-> see: Monochloroethane																												
Ethyl chloroacetate	$C_4H_7ClO_2$	000105-39-5	techn. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	
Ethyl cyanoacetate	$C_5H_7NO_2$	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	
Ethyl formate	$C_3H_6O_2$	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)	
Ethyl lactate	$C_5H_{10}O_3$	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)	
Ethyl mercaptan	C_2H_6S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	
Ethyl phenyl ether	-> see: Ethoxybenzene																												
Ethyl silicate	$C_8H_{20}SiO_4$	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)	
Ethylbenzene	C_8H_{10}	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	
Ethylene	C_2H_4	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	
Ethylene dibromiden (EDB)	$C_2H_4Br_2$	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	Dibromoethane, 1,2-;
Ethylene glycol	$C_2H_6O_2$	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	
Ethylene glycol monobutyl ether	$C_4H_{10}O_2$	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	
Ethylene glycol monoethyl ether	$C_4H_{10}O_2$	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Ethylene glycol monoethyl ether acetate	$C_6H_{12}O_3$	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	
Ethylene glycol monomethyl ether	$C_3H_8O_2$	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Ethylene glycol monomethyl ether oleate	$C_{21}H_{40}O_3$	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)	Kapsolat; Methoxyethyl oleate; Methyl cellosolveat oleate; plasticiser
Ethylene oxide	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	
Ethylenediaminetetraacetic acid (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	
Ethyne	-> see: Acetylene																												
Eucalyptus oil	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)	
Exhaust gases, alkaline	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)	
Exhaust gases, containing carbon dioxide	—	—	small	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	(1)	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	
Exhaust gases, containing hydrochloric acid	—	—	each	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	

						thermoplastics												fluoroplastics			elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Exhaust gases, containing hydrogen fluoride	—	—	small	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	
Exhaust gases, containing nitrose	—	—	small	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)	
Exhaust gases, containing sulfur dioxide	—	—	small	?		1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	
Exhaust gases, containing sulfur trioxide	—	—	small	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	
Exhaust gases, containing sulfuric acid	—	—	each	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	
Fat, animal	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	
Fat, mineral	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1	
Fat, vegetable	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	
Fats, edible oil	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	
Fatty alcohol sulfonates	—	—	aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	detergents
Ferric chloride	$FeCl_3$	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	saturated	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	
Ferric sulfate	$Fe_2(SO_4)_3$	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	
Ferrous chloride	$FeCl_2$	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	
Ferrous sulfate	$FeSO_4$	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	
Ferrous sulfate	$FeSO_4$	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	
Ferrous sulfate	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	
Fire-damp	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	mainly methane
Fixer for fotos	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0	
Fluid 101, 100℃	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0	Brake fluid, based on polyglycoles
Fluorides	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K	
Fluorine	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/3	1/2	1/2	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	
Fluorobenzene	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0	
Fluorocarbons	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	0/0	(1)	0/0	0/0	resistance depends on type
Formaldehyde solution ~~/раствор /формальдегида~~	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	
Formaldehyde solution ~~/раствор /формальдегида~~	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	
Formaldehyde solution ~~/раствор /формальдегида~~	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	
Formamide	CH_3NO	000075-12-7	techn. pure	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	273	4/4	0/0	1/1	1/1	1/1	
Formic acid	CH_2O_2	000064-18-6	50 %	C		1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	Hydrogen carboxylic acid; Methanoic acid; Aminic acid; Formylic acid
Formic acid	CH_2O_2	000064-18-6	98-100 %	C		1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	
Formic acid	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	
Freon 11	-> see: Trichlorofluoromethane																												
Freon 11	-> see: Trichlorofluoromethane																												
Freon 112	-> see: Tetrachlorodifluoroethane																												
Freon 112	-> see: Tetrachlorodifluoroethane																												
Freon 113	-> see: Trichlorotrifluoroethane																												
Freon 113	-> see: Trichlorotrifluoroethane																												
Freon 114	-> see: Dichlorotetrafluoroethane																												
Freon 114	-> see: Dichlorotetrafluoroethane																												
Freon 114 B2	-> see: Dibromotetrafluoroethane																												
Freon 114 B2	-> see: Dibromotetrafluoroethane																												
Freon 115	-> see: Chloropentafluoroethane																												
Freon 115	-> see: Chloropentafluoroethane																												
Freon 12	-> see: Dichlorodifluoromethane																												
Freon 12	-> see: Dichlorodifluoromethane																												
Freon 13	-> see: Chlorotrifluoromethane																												
Freon 13	-> see: Chlorotrifluoromethane																												
Freon 13 B1	-> see: Bromotrifluoromethane																												
Freon 13 B1	-> see: Bromotrifluoromethane																												
Freon 14	-> see: Carbon tetrafluoride																												
Freon 14	-> see: Carbon tetrafluoride																												
Freon 142b	-> see: Chlorodifluoroethane																												
Freon 142b	-> see: Chlorodifluoroethane																												

						thermoplastics														fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Freon 152a	-> see: Difluoroethane																												
Freon 152a	-> see: Difluoroethane																												
Freon 21	-> see: Dichlorofluoromethane																												
Freon 21	-> see: Dichlorofluoromethane																												
Freon 218	-> see: Octafluoropropane																												
Freon 218	-> see: Octafluoropropane																												
Freon 22	-> see: Chlorodifluoromethane																												
Freon 22	-> see: Chlorodifluoromethane																												
Freon 31	-> see: Chlorofluoromethane																												
Freon 31	-> see: Chlorofluoromethane																												
Freon 32	-> see: Difluoromethane																												
Freon 32	-> see: Difluoromethane																												
Freon C 318	-> see: Perfluorocyclobutane																												
Freon C 318	-> see: Perfluorocyclobutane																												
Freon C316	-> see: Dichlorohexafluorocyclobutane																												
Freon C316	-> see: Dichlorohexafluorocyclobutane																												
Frigen 12	-> see: Dichlorodifluoromethane																												
Frigen 12	-> see: Dichlorodifluoromethane																												
Frigen 21	-> see: Dichlorofluoromethane																												
Frigen 21	-> see: Dichlorofluoromethane																												
Frigen 22	-> see: Chlorodifluoromethane																												
Frigen 22	-> see: Chlorodifluoromethane																												
Fructose	$C_6H_{12}O_6$	000057-48-7	each	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	
Fruit pulp	—	—		—		1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	
Fruit wine	—	—		—		1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1	
Fuel + 20% ethyl alcohol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1	
Fuel + 20% methyl alcohol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1	
Fuel, Normal	—	—		F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1	
Fuel, piston engine (JP)	—	—		(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	
Fuel, Super	—	—		F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1	
Furalmethanal, 2-	-> see: Furfural																												
Furan	C_4H_4O	000110-00-9		F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Furfuran; Divinylene oxide; Oxacyclopentadiene
Furancarboxyaldehyde, 2-	-> see: Furfural																												
Furfural	$C_5H_4O_2$	000098-01-1		T		1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	Furancarboxyaldehyde, 2-; Furaldehyde, 2-; Furalmethanal, 2-
Furfuryl alcohol	$C_5H_6O_2$	000098-00-0	techn. pure	Xn		1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	
Gallic acid	$C_7H_6O_5 \times H_2O$	000149-91-7		Xi		1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1	
Gas liquor	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0	
Gas oil	—	—		(Xn)		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)	
Gas, natural	—	—		F+	X	0/0	0/0	01/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	mainly methane
Gasoline	—	008006-61-9		(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)	
Gasoline	C_5H_{12} - $C_{12}H_{26}$	086290-81-5		F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	fuel, lead-free
Gearbox oil, EP (Hypoid), 110°C	—	—		?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1	
Gelatin	—	009000-70-8	each	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Genantin	—	—		Xn		0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	antifreeze agent , based on glycol; Clariant
Ginger	—	—	ground	?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	
Glucose	$C_6H_{12}O_6$	000050-99-7	each	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glue (bone glue)	—	—	each	—		1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	
Glycerol	$C_3H_8O_3$	000056-81-5	each	Xi		1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	Glycerin; Propanetriol, 1,2,3-; Trihydroxypropane, 1,2,3-
Glycine	$C_2H_5NO_2$	000056-40-6	10 %	—		1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	Glycocol; Aminoacetic acid
Glycolic acid	$C_2H_4O_3$	000079-14-1	37 %	Xn		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	
Glycolic acid	$C_2H_4O_3$	000079-14-1	70 %	C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	
Glysantin	—	—		Xn		1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	antifreeze agent , based on glycol; BASF
Gum tragacanth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	
HD-Oil motor oil, without aromatics	—	—		?		1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1	

						thermoplastics												fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1	
Henkel-P3-solution	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1	cleaner
Heptane, normal	C_7H_{16}	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	
Heptanol, 1-	$C_7H_{16}O$	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)	
Heptanone	$C_7H_{14}O$	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)	isomer not indicated in the source
Hexachlorbenzene (HCB)	C_6Cl_6	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0	
Hexachlorocyclohexane (alpha-BHC)	$C_6H_6Cl_6$	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0	
Hexahydropyridine	-> see: Piperidine																												
Hexaldehyde, n-	$C_6H_{12}O$	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Hexamethylenetetramine	$C_6H_{12}N_4$	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	Methenamine; Hexamine; Urotropin
Hexane, n-	C_6H_{14}	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	
Hexanedioic acid	-> see: Adipic acid																												
Hexanetriol	$C_6H_{14}O_3$	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	isomer not indicated in the source
Hexene, 1-	C_6H_{12}	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	Butyl ethylene; Hexylene
Hexyl alcohol	$C_6H_{14}O$	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	
Honey	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	
Hydraulic fluids, HFA	—	—	50℃	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0	
Hydraulic fluids, HFB	—	—	50℃	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0	
Hydraulic fluids, HFC	—	—	60℃	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0	
Hydraulic fluids, HFD-R	—	—	100℃	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0	
Hydraulic fluids, HFD-S	—	—	100℃	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0	
Hydraulic oil (based on mineral oil)	—	—		?		0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1	
Hydrazine	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	Diamide; Diamine; Nitrogen hydride
Hydrazine hydrate	N_2H_6O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	
Hydrocyanic acid, sodium salt	-> see: Sodium cyanide																												
Hydrogen	H_2	001333-74-0	techn. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	
Hydrogen bromide	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	
Hydrogen bromide	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	
Hydrogen bromide	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	
Hydrogen carboxylic acid	-> see: Formic acid																												
Hydrogen chloride	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4	
Hydrogen chloride	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	
Hydrogen chloride	HCl	007647-01-0	concentrated	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	
Hydrogen chloride	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	salt acid
Hydrogen chloride (gas)	HCl	007647-01-0	anhydrous	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	
Hydrogen cyanide	HCN	000074-90-8	techn. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0	
Hydrogen fluoride	HF	007664-39-3	anhydrous	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	
Hydrogen fluoride	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	0/0	0/0	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0	
Hydrogen fluoride	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4	
Hydrogen fluoride	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	4/4	4/4	
Hydrogen fluoride	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	
Hydrogen peroxide	H_2O_2	007722-84-1	30 %	C		1/1	1/2	4/4	1/1	1/0	1/2	4/4	1/3	1/2	1/1	1/1	0/0	1/0	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	(3)	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	100 %	O, C		1/4	1/4	4/4	0/0	0/0	0/0	4/4	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(3)	(1)	(1)	
Hydrogen peroxide	H_2O_2	007722-84-1	90 %	O, C		1/1	1/2	4/4	1/1	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/3	4/4	0/0	(3)	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	3 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	1/0	1/1	1/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	3/4	0/0	(3)	1/1	1/1	
Hydrogen sulfide	H_2S	007783-06-4	saturated	F+, T+	X	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	3/0	1/0	1/3	3/3	1/0	0/0	1/0	1/1	1/1	1/0	(3)	4/4	0/0	1/1	1/1	1/1	
Hydroquinone	$C_6H_6O_2$	000123-31-9	saturated	Xn		0/0	1/3	4/4	(3)	1/0	0/0	(3)	1/0	4/4	0/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	4/4	4/4	0/0	(1)	1/0	1/0	Hydroquinol; Quinol
Hydroxyaluminium di(acetate)	$C_4H_7AlO_5$	000139-12-8	aqueous	Xn		1/1	1/1	1/1	(1)	1/0	1/1	1/0	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	(1)	1/0	(3)	3/0	0/0	1/1	1/1	1/1	
Hydroxylamine disulfate	$H_8N_2SO_6$	010039-54-0	12 %	Xn		1/1	1/1	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	
Hydroxylamine disulfate	$H_8N_2SO_6$	010039-54-0	each	Xn		1/1	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	
Hydroxymethyl furfural, 5- (HMF)	$C_6H_6O_3$	000067-47-0		Xi		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	
Imidole	-> see: Pyrrole																												
Iodine pentafluoride	JF_5	007783-66-6		(T, C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0	
Iodine, tincture of	I_2	007553-56-2		Xn	(X)	1/3	1/3	4/4	3/4	0/0	1/1	1/1	1/2	3/3	0/0	4/4	4/4	3/3	1/1	0/0	1/1	1/1	2/0	1/1	3/3	0/0	1/0	2/0L	1/0L	
Iodoform	CHJ_3	000075-47-8	100 %	Xn		3/0	3/0	(3)	3/0	0/0	0/0	(2)	3/0	3/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(2)	1/0	1/0	(3)	0/0	(3)	(1)	(1)	Triiodomethane;
Isoamyl alcohol	$C_5H_{12}O$	000123-51-3		Xn	X	0/0	0/0	(2)	3/0	1/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	1/3	0/0	(1)	!/1	1/1	3/0	2/4	3/3	0/0	(1)	(1)	(1)	
Isobutanol	$C_4H_{10}O$	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	0/0	3/4	1/1	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	Methyl-1-propanol, 2-; Isopropyl carbinol; Isobutyl alcohol

						thermoplastics													fluoroplastics			elastomers			metals			
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Isobutyl acetate	$C_6H_{12}O_2$	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	Methylpropyl acetate, 2-; Methylpropyl ethanoate, Beta-
Isobutyl alcohol	-> see: Isobutanol																											
Isobutyltrimethylmethane	-> see: Trimethylpentane, 2,2,4-																											
ISO-Fluid	—	—	liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	
ISO-Fluid A	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)	
ISO-Fluid B	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)	
ISO-Fluid C	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)	
ISO-Fluid D	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)	
Iso-octane	-> see: Trimethylpentane, 2,2,4-																											
Isopropyl acetate	$C_5H_{10}O_2$	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Isopropyl alcohol	C_3H_8O	000067-63-0	techn. pure	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	4/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	
Isopropyl carbinol	-> see: Isobutanol																											
Isopropyl chloride	C_3H_7Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	
Jam	—	—		—		1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	
Juices	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	
Kapsolat	-> see: Ethylene glycol monomethyl ether oleate																											
Kerosene	—	008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	lamp oil
Kerosene	—	—	techn. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	
Lactames	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)	cyclic amides
Lactic acid	$C_3H_6O_3$	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	lactol
Lactose	$C_{12}H_{22}O_{11}$	000063-42-3	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	
Lanolin	—	008006-54-0	techn. pure	—		3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	
Lard	—	—		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1	
Latex	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	dispersion of rubber
Laurel	—	—	ground	?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	
Lauryl alcohol	$C_{12}H_{26}O$	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	
Lauryl chloride	$C_{12}H_{25}Cl$	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0	
Lavender oil	—	008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)	
Lead acetate	$C_4H_6PbO_4$	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	
Lead acetate	$C_4H_6PbO_4$	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	
Lead nitrate	$Pb(NO_3)_2$	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	
Lead nitrate	$Pb(NO_3)_2$	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	
Lead stearate	$C_{36}H_{70}PbO_4$	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	small solubility - no chemical effect expected
Lead sulfate	$PbSO_4$	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	small solubility - no chemical effect expected
Lead tetraethyl (TEL)	$C_8H_{20}Pb$	000078-00-2	techn. pure	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	
Lemon juice	—	—		—		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1	
Lemon oil	—	084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)	mainly limonene
Lemongrass oil	—	008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)	
Ligroin	—	008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	petroleum ether
Lime chloride	[3 x CaCl(OCl) + Ca	—	aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	chloride of lime, bleach
Lime chloride	[3 x CaCl(OCl) + Ca	—		O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	chloride of lime, bleach
Limonene, DL-	$C_{10}H_{16}$	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	
Linseed oil	—	008001-26-1	techn. pure	—		1/1	1/3	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	
Liqueurs	—	—		—		1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	
Lithium bromide	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0	
Lube oils	—	—		?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	
Lysol	—	—		T		0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(3)	1/1	1/1	disinfectant, cresol + soap
Machine oil	—	—	100 %	?		0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	
Magnesium bromide	$MgBr_2$	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0	
Magnesium carbonate	$MgCO_3$	000546-93-0	saturated	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	$MgCl_2$	007786-30-3	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	
Magnesium chlorite	$Mg(ClO_2)_2$	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	
Magnesium hydroxide	$Mg(HO)_2$	001309-42-8	saturated	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	
Magnesium iodide	MgJ_2	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0	
Magnesium nitrate	$Mg(NO_3)_2$	010377-60-3	saturated	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	Nitric acid, magnesium salt;
Magnesiumsulfat	$MgSO_4$	007487-88-9	each	—		1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	
Maize-germ oil	—	008001-30-7	techn. pure	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	corn oil
Maleic acid	$C_4H_4O_4$	000110-16-7	saturated	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	
Maleic acid	$C_4H_4O_4$	000110-16-7	aqueous	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	
Menthol	$C_{10}H_{20}O$	000089-78-1	solid	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0	

						thermoplastics												fluoroplastics			elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Mercuric chloride	$HgCl_2$	007487-94-7	aqueous	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	
Mercuric cyanide	C_2HgN_2	000592-04-1	saturated	T+		1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/0	
Mercuric nitrate	$Hg(NO_3)_2$	010045-94-0	saturated	(T+)		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	
Mercury	Hg	007439-97-6	pure	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1	
Mesityl oxide	$C_6H_{10}O$	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methacetone	-> see: Pentanone, 3-																													
Methacrylic acid	$C_4H_6O_2$	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0	
Methane	CH_4	000074-82-8	techn. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	
Methanoic acid	-> see: Formic acid																													
Methenamine	-> see: Hexamethylenetetramine																													
Methoxy butanol	$C_5H_{12}O_2$	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!/0	0/0	(1)	(1)	(1)	isomer not indicated in the source
Methoxyethane	C_3H_8O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	Methyl ethyl ether;
Methoxyethyl oleate	-> see: Ethylene glycol monomethyl ether oleate																													
Methyl acetate	$C_3H_6O_2$	000079-20-9	techn. pure	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	
Methyl acrylate	$C_4H_6O_2$	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl alcohol метанол	CH_4O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	
Methyl amine	CH_5N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	
Methyl benzene	C_7H_8	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	
Methyl bromide	CH_3Br	000074-83-9	techn. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	
Methyl butanol	$C_5H_{12}O$	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)	isomer not indicated in the source
Methyl butyl ketone	$C_6H_{12}O$	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl cellosolveat oleate	-> see: Ethylene glycol monomethyl ether oleate																													
Methyl chloride	CH_3Cl	000074-87-3	techn. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	1/1L	1/1L	
Methyl cyanide	-> see: Acetonitrile																													
Methyl dichloroacetate	$C_3H_4Cl_2O_2$	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	
Methyl ethyl carbinol	-> see: Butyl alcohol, sec-																													
Methyl ethyl ether	-> see: Methoxyethane																													
Methyl ethyl ketone (MEK)	C_4H_8O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl ethylene oxide	-> see: Propylene oxid																													
Methyl formate	$C_2H_4O_2$	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl isobutyl ketone	$C_6H_{12}O$	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl isopropyl ketone	$C_5H_{10}O$	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl ketone	-> see: Acetone																													
Methyl methacrylate	$C_5H_8O_2$	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	
Methyl propyl ketone	$C_5H_{10}O$	000107-87-9		(F)	X	1/2	2/3	(2)	4/4	(4)	3/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	(1)	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl salicylate	$C_8H_8O_3$	000119-36-8		Xn, Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/0	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	2/0	(3)	4/4	0/0	(2)	(1)	(1)	synthetic oil of wintergreen
Methyl sulfuric acid	CH_4SO_4	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	0/0	4/4	2/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	
Methyl sulfuric acid	CH_4SO_4	000077-78-1	aqueous	(C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	
Methyl-1-propanol, 2-	-> see: Isobutanol																													
Methylchloroacetate	$C_3H_5ClO_2$	000096-34-4	techn. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	
Methylcyclohexane	C_7H_{14}	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	1/1	0/0	1/1	0/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	
Methylcyclopentane	C_6H_{12}	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
Methylene chloride	CH_2Cl_2	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/0	1/1L	1/1L	
Methylglycol acetate	$C_5H_{10}O_3$	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methyloxirane	-> see: Propylene oxid																													
Methylpropyl acetate, 2-	-> see: Isobutyl acetate																													
Milk	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	
Mineral oil	—	008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	
Mineral water	—	—		—		1/1	1/1	(1)	1/0	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	
Molasses	—	—		—		1/1	1/1	1/0	(1)	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	1/0	
Molasses wort	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)	
Monochlorobenzene (MCB)	-> see: Chlorobenzene																													
Monochloroethane	C_2H_5Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	1/1L	1/1L	Ethyl chloride; Chloroethane, 1-
Morpholine	C_4H_9NO	000110-91-8	techn. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	
Motor oil	—	—		?		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	
Mowilith D	—	—		?		1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	dispersion of polyvinyl acetate; Clariant
Muscat	—	—	ground	?		0/0	0/0	(2)	4/4	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	
Mustard	—	—		—		0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L	
Naphtha	—	008032-32-4		(Xn)		1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	petroleum ether
Naphthalene	$C_{10}H_8$	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	
Naphthalene (in alcohol)	—	—		F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	
Neon	Ne	007440-01-9		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1	
Nickel acetate	$C_4H_6NiO_4$	000373-02-4	aqueous	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0	

						thermoplastics													fluoroplastics				elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Nickel dichloride	$NiCl_2$	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	
Nickel dichloride	$NiCl_2$	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	
Nickel sulfate	$NiSO_4$	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	
Nickel sulfate	$NiSO_4$	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	
Nickelous nitrate	$Ni(NO_3)_2$	013138-45-9	saturated	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	
Nicotine	$C_{10}H_{14}N_2$	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	
Nicotinic acid	$C_6H_5NO_2$	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	
Nitric acid	HNO_3	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	
Nitric acid	HNO_3	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	
Nitric acid	HNO_3	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	
Nitric acid	-> see: Ammonium nitrate																												
Nitric acid, magnesium salt	-> see: Magnesium nitrate																												
Nitric acid, potassium salt	-> see: Potassium nitrate																												
Nitro benzoic acid	$C_7H_5NO_4$	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0	isomer not indicated in the source
Nitro reducer	—	—		?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)	solvent cleaner mixture
Nitrobenzene	$C_6H_5NO_2$	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	
Nitroethane	$C_2H_5NO_2$	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Nitrogen	N_2	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1	
Nitrogen hydride	-> see: Hydrazine																												
Nitrogen tetroxide	N_2O_4	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)	
Nitroglycerine	$C_3H_5(NO_3)_3$	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	
Nitrohydrochloric acid	HNO_3 + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	aqua regia: mixture of hydrochloric acid and nitric acid
Nitropropane	$C_3H_7NO_2$	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	isomer not indicated in the source
Nitrose gases	—	—	diluted	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	nitrogen monoxide + nitrogen dioxide
Nitrotoluene	$C_7H_7NO_2$	001321-12-6	techn. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	
Nitrous acid, sodium salt	-> see: Sodium nitrite																												
Nitrous oxide	N_2O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)	nitric oxide
Nonanol	-> see: Nonyl alcohol																												
Nonyl alcohol	$C_9H_{20}O$	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)	Nonanol; Pelargonic alcohol; Octyl carbinol
Nutmeg oil	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)	
Octafluoropropane	C_3F_8	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0	
Octane	C_8H_{18}	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	
Octyl carbinol	-> see: Nonyl alcohol																												
Octyl cresol ?	$C_{15}H_{24}O$	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	isomer not indicated in the source
Oils and fats, vegetable	—	—		—		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	
Oils, essential	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	
Oleic acid	$C_{18}H_{34}O_2$	000112-80-1	techn. pure	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	
Oleic acid methyl ester	$C_{19}H_{36}O_2$	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)	
Oleum	$H_2SO_4 \times SO_3$	008014-95-7	10 % SO_3	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1	fuming sulfuric acid
Oleum steams	—	—	small	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	sulfur trioxide
Olive oil	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	
Orange juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)	
Orange oil	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)	mainly +-limonene
Orange oil, bitter	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)	
Oxacyclopentadiene	-> see: Furan																												
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7	aqueous	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	Ethanedioic acid;
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	
Oxygen	O_2	007782-44-7	techn. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	
Ozone	O_3	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	
Ozone-air-mixture	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	
Palm kernel oil	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	
Palm oil	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	
Palmitic acid	$C_{16}H_{32}O_2$	000057-10-3	techn. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1	
Paraffin-emulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	
Paraffins	C_nH_{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	
Paraformaldehyde	$(CH_2O)_nH_2O$	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)	Polyoxymethylene;
Peanut oil	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	
Pelargonic alcohol	-> see: Nonyl alcohol																												

						thermoplastics												fluoroplastics			elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	antibiotic
Pentachlorbiphenyl	$C_{12}H_5Cl_5$	—		Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0	
Pentamethyleneimine	-> see: Piperidine																												
Pentane, normal	C_5H_{12}	000109-66-0		F	X	1/3	1/3	1/0	1/0	1/1	(3)	1/0	(3)	3/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1	
Pentanethiol, 1-	$C_5H_{12}S$	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)	
Pentanol, 1-	$C_5H_{12}O$	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	Amyl alcohol, n-; Butyl carbinol, n-; Pentyl alcohol, n-
Pentanone, 3-	$C_5H_{10}O$	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	Diethyl ketone; Dimethylacetone; Methacetone
Pentyl alcohol, n-	-> see: Pentanol, 1-																												
Pepper	—	—	ground	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	
Perchloric acid	$HClO_4$	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	
Perchloric acid	$HClO_4$	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	
Perchlorobutadiene	C_4Cl_6	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	
Perchloroethylene	-> see: Tetrachloroethylene																												
Perfluorocyclobutane	C_4F_8	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)	
Permanganic acid, potassium salt	-> see: Potassium permanganate																												
Petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	
Petroleum ether	—	008032-32-4	techn. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	
Phenacetin	$C_{10}H_{13}NO_2$	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)	
Phenethyl alcohol	$C_8H_{10}O$	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)	
Phenetole	-> see: Ethoxybenzene																												
Phenol (фенол)	C_6H_6O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	
Phenol (фенол)	C_6H_6O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	
Phenolic resin mass	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	
Phenyl chloride	-> see: Chlorobenzene																												
Phenyl methyl ketone	-> see: Acetophenone																												
Phenylethanone, 1-	-> see: Acetophenone																												
Phenylhydrazine	$C_6H_8N_2$	000100-63-0	techn. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	
Phenylhydrazine hydrochloride	$C_6H_8N_2$-HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)	
Phenylsulfonate	—	070528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Phosgene	$COCl_2$	000075-44-5	liquid	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	Carbonyl chloride; Chloroformyl chloride
Phosgene	$COCl_2$	000075-44-5	gaseous	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	3/0	0/0	(3)	3/4	3/4	
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)	salts of phosphoric acid
Phosphine	PH_3	007803-51-2	concentrated	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	
Phosphoric acid	H_3PO_4	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	
Phosphoric acid	H_3PO_4	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	
Phosphoric acid	H_3PO_4	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	
Phosphorus oxychloride	PCl_3O	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	
Phosphorus oxychloride	PCl_3O	010025-87-3		T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	
Phosphorus pentachloride	PCl_5	010026-13-8		T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L	
Phosphorus pentoxide	P_4O_{10}	001314-56-3	techn. pure	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	
Phosphorus trichloride	PCl_3	007719-12-2		T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	0/0	
Phthalic acid	$C_8H_6O_4$	000088-99-3	saturated	Xi		1/1	1/1	3/3	(3)	1/0	0/0	1/0	1/1	1/0	0/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	
Phthalsäuremonoamylester ?	$C_{13}H_{16}O_4$	??		(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)	
Picric acid	$C_6H_3N_3O_7$	000088-89-1	1 % aqueous	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	
Pine oil	—	008023-99-2		?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	pinus sylvestris
Pineapple juice	—	—		—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	(1)	(1)	
Pink	—	—	ground	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	
Piperidine	$C_5H_{11}N$	000110-89-4		F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Hexahydropyridine; Azacyclohexane; Pentamethyleneimine
Plasticiser	—	—		?		1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)	
Polish remover	—	—		?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	
Polyester resins	—	—		(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	
Polyethylene glycol	HO-$(C_2H_4O)_n$-H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	
Polyoxymethylene	-> see: Paraformaldehyde																												
Polyran M25 N	—	—	80℃	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)	lubricating oil
Polyran M400	—	—	80℃	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	(3)	0	0	(1)	(1)	lubricatin g oil
Polysolvan O	$C_6H_{12}O_3$	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	solvent cleaner, butyl glycolate; Celanese AG
Potassium acetate	$C_2H_3KO_2$	000127-08-2	aqueous	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	
Potassium bisulfate	$KHSO_4$	007646-93-7	aqueous	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	
Potassium bisulfate	$KHSO_4$	007646-93-7		C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	
Potassium bitartrate	$C_4H_5KO_6$	000868-14-4	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	
Potassium borate	KBO_2	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	

						thermoplastics													fluoroplastics			elastomers		metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Potassium borate	KBO_2	012228-88-5	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	saturated	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	aqueous	O, T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	
Potassium bromide	KBr	007758-02-3	each	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/0L	1/0L	
Potassium carbonate	K_2CO_3	000584-08-7	saturated	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	aqueous	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	saturated	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	aqueous	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	
Potassium chloride	KCl	007447-40-7	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	
Potassium chromate	K_2CrO_4	007789-00-6	saturated	T		1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	
Potassium chromate	K_2CrO_4	007789-00-6	aqueous	T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	
Potassium cyanide	KCN	000151-50-8	saturated	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	
Potassium cyanide	KCN	000151-50-8	aqueous	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	saturated	T		1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	aqueous	T		0/0	0/0	3/0	1/0	3/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	
Potassium ferricyanide	$C_6FeK_3N_6$	013746-66-2	each	Xn		1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	
Potassium ferrocyanide	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	saturated	—		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1	
Potassium ferrocyanide	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	diluted	—		1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	
Potassium fluoride	KF	007789-23-3		T		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	
Potassium hydrogen carbonate	$CHKO_3$	000298-14-6	saturated	—		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	
Potassium hydroxide	KHO	001310-58-3	10 %	C+		1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	Caustic potash; Potassium hydrate; Potassium lye
Potassium hydroxide	KHO	001310-58-3	30 %	C+		1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	50 %	C+		1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	concentrated	C+		1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	1 %	Xi		1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	
Potassium hypochlorite	KClO	007778-66-7	diluted	(O, C)		1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	
Potassium iodate	KJO_3	007758-05-6		O		0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	
Potassium iodide	KJ	007681-11-0	saturated	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	
Potassium iodide	KJ	007681-11-0	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	
Potassium lye	-> see: Potassium hydroxide																													
Potassium nitrate	KNO_3	007757-79-1	50 %	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	Saltpeter; Nitric acid, potassium salt
Potassium nitrate	KNO_3	007757-79-1	aqueous	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	saturated	O, Xn		1/1	1/1	(1)	1/0	(1)	1/0	1/1	1/1	0/0	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	aqueous	O, Xn		1/1	1/1	(1)	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	
Potassium permanganate	$KMnO_4$	007722-64-7	aqueous	O, Xn		0/0	0/0	4/4	1/0	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	Permanganic acid, potassium salt; Condy's crystals;
Potassium permanganate	$KMnO_4$	007722-64-7		O, Xn		1/3	1/1	4/4	1/0	(2)	1/1	1/1	1/1	1/3	0/0	1/3	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	
Potassium persulfate	$K_2(SO_4)_2$	007727-21-1	each	O, Xn		1/1	1/1	4/4	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/0	1/0	
Potassium sulfate	K_2SO_4	007778-80-5	aqueous	Xn		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Potassium sulfide	K_2S	001312-73-8	diluted	(C)		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	(1)	(1)	2/0	0/0	3/4	1/1	1/1	
Potassium sulfite	K_2SO_3	010117-38-1	saturated	(Xi)		1/1	1/1	(1)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/0	
Potassium thiosulfate	$K_2S_2O_3$	010233-00-8	saturated	Xi		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	3/3	0/0	(1)	(1)	(1)	
Precipitated silica	SiO_2	001343-98-2	each	—		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	
Prontosil	—	—		(Xn)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	0/0	0/0	for chemotherapy; Bayer - no more availyble
Propane	C_3H_8	000074-98-6	liquid	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/0	0/0	1/0	1/0	3/0	1/0	0/0	(1)	1/1	1/1	4/4	1/0	(2)	0/0	1/1	1/1	1/1	
Propane	C_3H_8	000074-98-6	gaseous	F+	X	3/4	4/4	1/0	3/4	1/0	4/4	1/1	2/4	4/4	3/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	
Propanetriol, 1,2,3-	-> see: Glycerol																													
Propanone, 2-	-> see: Acetone																													
Propargyl alcohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	
Propenenitrile, 2-	-> see: Acrylonitrile																													
Propenyl alcohol	-> see: Allyl alcohol																													
Propionic acid	$C_3H_6O_2$	000079-09-4	50 %	C		1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	
Propionic acid	$C_3H_6O_2$	000079-09-4		C		1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	
Propyl acetate, normal	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Propyl alcohol	C_3H_8O	000071-23-8		F	X	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	
Propyl carbinol	-> see: Butyl alcohol, normal																													
Propyl nitrate	$C_3H_7NO_3$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)	
Propylamine, n-	C_3H_9N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Propylene	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
Propylene glycol	$C_3H_8O_2$	000057-55-6		—		1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	
Propylene oxid	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	Epoxypropane, 1,2-; Methyloxirane; Methyl ethylene oxide
Pydraul C (312, 540)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)	based on phosphoric ester; Monsanto
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)	based on phosphoric ester; Monsanto
Pyridine	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	Azine; Azabenzene

						thermoplastics													fluoroplastics			elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Pyrogallic acid	$C_6H_6O_3$	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	
Pyroligneous oil	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)	
Pyrrole	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Azole; Imidole
Quinine	$C_{20}H_{24}N_2O_2$	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	
Quinol	-> see: Hydroquinone																												
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	for moisture-proofing of textiles; BASF
Resorcinol	$C_6H_6O_2$	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0	
Resorcinol	$C_6H_6O_2$	000108-46-3	saturated	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0	
Roaster off-gas	—	—	each	(T)		0/0	0/0	(2)	0/0	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	
Rose oil	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)	
Rum ether	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)	
Sagrotan	—	—	liquid	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)	disinfectant; Schülke & Mayr
Salicyl acid	$C_7H_6O_3$	000069-72-7	saturated	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	
Salicyl acid	$C_7H_6O_3$	000069-72-7	powder	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	
Salicylaldehyde	$C_7H_6O_2$	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)	
Salt spring	NaCl	007647-14-5	saturated	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	
Salt water, sea water	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	
Saltpeter	-> see: Potassium nitrate																												
Saturated steam condensate	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1	
Sea water	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	
Silicofluoric acid	H_2SiF_6	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	
Silicone greases	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1	
Silicone oil	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	polysiloxane
Silver acetate	$C_2H_3AgO_2$	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	
Silver cyanide	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	
Silver nitrate	$AgNO_3$	007761-88-8	aqueous	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	lunar caustic
Silver nitrate	$AgNO_3$	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	lunar caustic
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	0/0	(1)	(1)	based on phosphoric ester; Solutia
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	0/0	(1)	(1)	based on phosphoric ester; Solutia
Soaps, liquid	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0	
Soapy solution	—	—	each	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	
Sodium acetate	$C_2H_3NaO_2$	000127-09-3	each	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	Acetic acid sodium salt;
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	aqueous	Xn		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	
Sodium bicarbonate	$NaHCO_3$	000144-55-8	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Sodium bisulfate	$NaHSO_4$	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	
Sodium bisulfate	$NaHSO_4$	007681-38-1	each	(C)		1/1	1/1	1/0	1/0	0/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	
Sodium bisulfite	$NaHSO_3$	007631-90-5	aqueous	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	saturated	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	
Sodium bromate	$NaBrO_3$	007789-38-0	each	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	
Sodium bromide	NaBr	007647-15-6	each	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	
Sodium carbonate	Na_2CO_3	000497-19-8	saturated	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8		Xi		1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	each	O, Xn		1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	Chloric acid, sodium salt;
Sodium chlorate	$NaClO_3$	007775-09-9	aqueous	O, Xn		0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	
Sodium chloride	NaCl	007647-14-5	each	—		1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	
Sodium chloride	NaCl	007647-14-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	
Sodium chlorite	$NaClO_2$	007758-19-2	diluted	(O, Xn)		1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	
Sodium chromate	$NaCrO_4$	007775-11-3	diluted	T		1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	
Sodium cyanide	CNNa	000143-33-9	saturated	T		1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	Hydrocyanic acid, sodium salt;
Sodium cyanide	CNNa	000143-33-9	aqueous	T		1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	
Sodium dichromate	$Na_2Cr_2O_7$	010588-01-9		T		0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	
Sodium dithionite	-> see: Sodium hydrosulfite																												
Sodium dodecylbenzene sulfonate	$C_{18}H_{29}NaSO_3$	025155-30-0		Xn		1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)	
Sodium ferrocyanide	$C_6FeNa_4N_6$	013601-19-9		Xn		1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)	
Sodium fluoride	NaF	007681-49-4	saturated	T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	
Sodium hydrosulfite	$Na_2S_2O_4$	007775-14-6	10 %	Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1	Sodium dithionite; Dithionous acid, disodium salt; Sodium sulfoxylate;
Sodium hydrosulfite	$Na_2S_2O_4$	007775-14-6		Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1	
Sodium hydroxide (гидроксид натрия)	NaHO	001310-73-2	concentrated	C		1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	caustic soda, sodium hydrate, soda lye
Sodium hydroxide	NaHO	001310-73-2	30 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye

						thermoplastics													fluoroplastics			elastomers		metals			
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Sodium hydroxide (гидроксид натрия)	NaHO	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye
Sodium hydroxide	NaHO	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye
Sodium hydroxide	NaHO	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye
Sodium hydroxide	NaHO	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	caustic soda, sodium hydrate, soda lye
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide
Sodium hypochlorite	NaClO	007681-52-9	12,5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide
Sodium iodide	NaJ	007681-82-5	each	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	
Sodium metabisulfite	$Na_2S_2O_5$	007681-57-4	each	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	
Sodium nitrate	$NaNO_3$	007631-99-4	saturated	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	chile saltpeter
Sodium nitrate	$NaNO_3$	007631-99-4	aqueous	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	chile saltpeter
Sodium nitrite	$NaNO_2$	007632-00-0	saturated	O, T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	Nitrous acid, sodium salt;
Sodium nitrite	$NaNO_2$	007632-00-0	aqueous	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1	
Sodium oxalate	$C_2Na_2O_4$	000062-76-0	saturated	Xn		1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)	
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	saturated	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0	
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	aqueous	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0	
Sodium perchlorate	$NaClO_4$	007601-89-0	saturated	O, Xn		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	
Sodium peroxide	Na_2O_2	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	2?2	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	
Sodium peroxide	Na_2O_2	001313-60-6	saturated	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	
Sodium persulfate	$Na_2S_2O_8$	007775-27-1	saturated	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	saturated	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Sodium polyphosphates	$(NaPO_3)_6$	068915-31-1	saturated	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0	
Sodium silicate	$Na_2Si_3O_7$	001344-09-8	each	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1	
Sodium silicate	$Na_2Si_3O_7$	001344-09-8	saturated	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	1/1	1/1	1/1	waterglass
Sodium stearate	$C_{18}H_{35}NaO_2$	000822-16-2	aqueous	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1	
Sodium sulfate	Na_2SO_4	007757-82-6	saturated	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/1	
Sodium sulfate	Na_2SO_4	007757-82-6	aqueous	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Sodium sulfate	Na_2SO_4	007757-82-6		—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	1/1	1/1	1/1	
Sodium sulfide	Na_2S	001313-82-2	saturated	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)	
Sodium sulfide	Na_2S	001313-82-2	aqueous	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2	
Sodium sulfite	Na_2SO_3	007757-83-7	saturated	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	Sulfurous acid, disodium salt;
Sodium sulfoxylate	-> see: Sodium hydrosulfite																												
Sodium thiosulfate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	each	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	fixer natron, "sodium hyposulfite"
Sodium thiosulfate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	saturated	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	fixer natron, "sodium hyposulfite"
Sodium thiosulfate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	aqueous	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	fixer natron, "sodium hyposulfite"
Soft soap	—	—	diluted	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)	
Soya oil	—	008001-22-7		—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	
Spermaceti	—	008002-23-1		—		0/0	1/3	(1)	1/1	1/0	0/0		1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	
Spindle oil	—	—		?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	
Spinning bath acid	—	—	100mg CS_2/l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	
Spirit (of wine)	C_2H_6O	—		F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	ethyl alcohol
Spirits	C_2H_6O	—		—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	ethyl alcohol 40 %
Spirits of Turpentine	—	008006-64-2		Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	
Spirits of wine	C_2H_6O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	ethyl alcohol
Spirits of wine	C_2H_6O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	ethyl alcohol
Spruce oil	—	008008-80-8		?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)	pinus sylvestris
Stannic chloride	$SnCl_4$	007646-78-8	aqueous	C		1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4	
Stannous chloride	$SnCl_2$	007772-99-8	aqueous	(C, Xn)		1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	
Stannous chloride	$SnCl_2$	007772-99-8	saturated	C, Xn		1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	
Starch solution	$(C_6H_{10}O_5)_n$	—	each	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Starch syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Stauffer grease, thick	—	—		(—)		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	
Steam	H_2O	—	up to 150℃	?		4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0/0	1	0	1	3	4/4	0	(1)	1/1	1/1	
Stearic acid	$C_{18}H_{36}O_2$	000057-11-4	crystals	Xi		1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	
Strontium bromide	$SrBr_2$	010476-81-0		Xi		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0	
Strychnine	$C_{21}H_{22}N_2O_2$	000057-24-9		T+		1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)	
Styrene	C_8H_8	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	
Succinic acid	$C_4H_6O_4$	000110-15-6	50 %	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	

						thermoplastics												fluoroplastics			elastomers		metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Succinic acid	$C_4H_6O_4$	000110-15-6	saturated	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	
Sugar acid	—	—	saturated	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0	
Sugar beet juice	—	—		—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)	
Sugar syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Sulfur	S_8	007704-34-9	techn. pure	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	flower of sulfur
Sulfur (mono)chloride	S_2Cl_2	010025-67-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	1/1L	1/1L	
Sulfur dioxide	SO_2	007446-09-5	damp	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	with H2O->sulfurous acid
Sulfur dioxide	SO_2	007446-09-5	liquid	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	with H2O->sulfurous acid
Sulfur hexafluoride	SF_6	002551-62-4		—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)	
Sulfur trioxide	SO_3	007446-11-9		C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	
Sulfur, melted, 121 °C	S_8	007704-34-9		?		0	0	(4)	(3)	0	4	4	4	4	0	0	0	4	0	0	(1)	0	4	1	4	0	(3)	1	1	
Sulfuric acid	H_2SO_4	007664-93-3	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	
Sulfuric acid	H_2SO_4	007664-93-3	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	
Sulfuric acid	H_2SO_4	007664-93-3	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	
Sulfuric acid	H_2SO_4	007664-93-3	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	
Sulfuric acid	H_2SO_4	007664-93-3	fuming	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	oleum
Sulfuric acid	H_2SO_4	007664-93-3	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	
Sulfuric acid	H_2SO_4	007664-93-3	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3	
Sulfuric acid	-> see: Battery acid																												
Sulfurous acid	H_2SO_3	007782-99-2	saturated	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	
Sulfurous acid, disodium salt	-> see: Sodium sulfite																												
Sulfuryl chloride	Cl_2SO_2	007791-25-5	techn. pure	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0	
Tallow	—	—	techn. pure	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	
Tannic acid	$C_{76}H_{52}O_{46}$	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	
Tannic acid	$C_{76}H_{52}O_{46}$	001401-55-4		Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	
Tanning extracts	—	—		?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	
Tanning extracts, vegetable	—	—	techn. usually	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	
Tar	—	—		T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)	
Tartaric acid	$C_4H_6O_6$	000087-69-4	aqueous	Xi		1/1	1/1	3/3	1/2	0/0	0/0	(3)	1/1	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	
Tartaric acid	$C_4H_6O_6$	000087-69-4		Xi		1/1	1/1	4/4	1/2	0/0	1/1	(3)	1/1	2/2	1/1	1/2	1/3	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	
Tetrabromoethane (TBE)	$C_2H_2Br_4$	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	isomer not indicated in the source
Tetrachloroethane	$C_2H_2Cl_4$	—	techn. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	isomer not indicated in the source
Tetrachlorodifluoroethane	$C_2Cl_4F_2$	000076-12-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0	
Tetrachloroethylene	C_2Cl_4	000127-18-4		Xn		4/4	4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	(3)	0/0	0/0	Perchloroethylene; Tetrachloroethene
Tetrahydrofuran (THF)	C_4H_8O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	
Tetrahydrofurfuryl alcohol	$C_5H_{10}O_2$	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)	
Tetrahydronaphthalene	$C_{10}H_{12}$	000119-64-2	techn. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	
Thiocyanic acid, ammonium salt	-> see: Ammonium thiocyanate																												
Thioglycolic acid	$C_2H_4SO_2$	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	
Thionyl chloride	Cl_2SO	007719-09-7	techn. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	
Thiophene	C_4H_4S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	
Thymol	$C_{10}H_{14}O$	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)	
Titanium (tetra)chloride	$TiCl_4$	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0	
Toluene	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1	
Train oil	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)	
Transformer oil	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	
Triacetin	$C_9H_{14}O_6$	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)	
Tribromomethane	$CHBr_3$	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	
Tributyl citrate (TBC)	$C_{18}H_{32}O_7$	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)	
Tributyl phosphate (TBP)	$C_{12}H_{27}PO_4$	000126-73-8	techn. pure	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Trichloroacetaldehyde	C_2HCl_3O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	
Trichloroacetic acid (TCA)	$C_2HCl_3O_2$	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	
Trichlorobenzene	$C_6H_3Cl_3$	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	isomer not indicated in the source
Trichloroethane	$C_2H_3Cl_3$	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	isomer not indicated in the source
Trichloroethylene (TRI)	C_2HCl_3	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	1/1L	1/1L	
Trichlorofluoromethane	CCl_3F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	
Trichlorophenol	$C_6H_3Cl_3O$	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0	isomer not indicated in the source
Trichlorotrifluoroethane	$C_2Cl_3F_3$	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0	
Trichlorotrifluoroethane	$C_2Cl_3F_3$	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0	isomer not indicated in the source
Tricresyl phosphate (TCF)	$C_{21}H_{21}PO_4$	—	techn. pure	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	isomer not indicated in the source
Triethanolamine (TEA)	$C_6H_{15}NO_3$	000102-71-6	techn. pure	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	
Triethylamine (TEA)	$C_6H_{15}N$	000121-44-8	techn. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	
Triethylene glycol	$C_6H_{14}O_4$	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	

серная кислота

						thermoplastics														fluoroplastics			elastomers			metals		
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL	V2A	V4A	COMMENT
Triethylene glycol diacetate	$C_{10}H_{18}O_6$	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	
Trihydroxypropane, 1,2,3-	-> see: Glycerol																												
Triiodomethane	-> see: Iodoform																												
Triisopropylbenzene	$C_{15}H_{24}$	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	
Trimethylbenzene, 1,2,4-	C_9H_{12}	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1	
Trimethylolpropane	$C_6H_{14}O_3$	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)	
Trimethylpentane, 2,2,4-	C_8H_{18}	000540-84-1	techn. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	Iso-octane; Isobutyltrimethylmethane
Trioctyl phosphate	$C_{24}H_{54}PO_4$	000078-42-2	techn. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	Tris(2-ethylhexyl) phosphate
Tripropylene glycol (TPG)	$C_9H_{20}O_4$	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)	
Trisodium phosphate	Na_3PO_4	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1	
Turbine oil (based on mineral oil)	—	—		?		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1	
Turpentine surrogate	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	
Two-stroke oil	—	—	100 %	—		0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	
Undecanol	$C_{11}H_{24}O$	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)	
Urea	CH_4N_2O	000057-13-6	aqueous	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	
Urea	CH_4N_2O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	
Uric acid	$C_5H_4N_4O_3$	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	
Urine	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	
Urotropin	-> see: Hexamethylenetetramine																												
Valerian drops	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)	
Vaseline	—	008009-03-8	techn. pure	(—)		3/4	2/3	1/0	1/0	1/0	0/0		1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	petrolatum
Vaseline oil	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0		1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	paraffin oil
Vaseline oil	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	paraffin oil
Vegetable oils	—	—		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	
Vinegar	$C_2H_4O_2$	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	
Vinyl acetate	$C_4H_6O_2$	000108-05-4	techn. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)		1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	
Vinyl carbinol	-> see: Allyl alcohol																												
Vinyl chloride (VCM)	C_2H_3Cl	000075-01-4	techn. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	Chloroethene; Chloroethylene
Vinyl cyanide	-> see: Acrylonitrile																												
Vinylidene chloride	$C_2H_2Cl_2$	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	
Vitamin C	$C_6H_8O_6$	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)	
Walnut oil	—	008024-09-7		—		0/0	0/0	(2)	(2)	1/0	0/0		1/3	3/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	(1)	1/1	1/1	
Washingup liquid	—	—	aqueous	?		1/1	1/1	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	
Water	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Water, distilled ~	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Wax alcohol	—	—	techn. pure	(—)		3/4	3/4	(2)	(2)	1/0	0/0		3/4	0/0	0/0	1/1	3/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	(1)	(1)	
Waxes	—	—		—		0/0	1/3	1/1	1/1	1/1	0/0		1/3	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	(4)	1/0	(1)	0/0	1/1	1/1	1/1	
Wetting agent	—	—	5 %	?		1/0	0/0	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(2)	0/0	0/0	K	K	detergents
Whey	—	—		—		1/1	0/0	(2)	(1)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(2)	1/1	1/1	
Whiskey	—	—		—		0/0	0/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	whisky, scotch, bourbon
White Spirit	—	008042-47-5		Xn		1/0	1/0	(1)	(3)	1/0	(4)	1/0	1/3	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	4/4	1/0	(2)	0/0	1/1	1/1	1/1	
Wines	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	
Wort for fermentation	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(1)	1/0	4/4	0/0	(2)	(1)	(1)	
Xenon	Xe	007440-63-3		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	
Xylene	C_8H_{10}	001330-20-7		(F), Xn	X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	
Yeast	—	—	each	—		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)	
Zinc acetate	$C_4H_6ZnO_4$	000557-34-6	aqueous	Xn, Xi		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	3/3	0/0	(3)	(1)	(1)	
Zinc bromide	$ZnBr_2$	007699-45-8		C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0	
Zinc carbonate	$ZnCO_3$	003486-35-9	saturated	?		1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	small solubility - no chemical effect expected
Zinc chloride	$ZnCl_2$	007646-85-7	aqueous	(C, Xn)		1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	
Zinc nitrate	$Zn(NO_3)_2$	007779-88-6		O, C, Xn		1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)	
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	1/1	small solubility - no chemical effect expected
Zinc oxide ointment	—	—		?		0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)	
Zinc phosphate	$Zn_3(PO_4)_2$	007779-90-0	saturated	?		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	
Zinc sludge	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0	
Zinc stearate	$C_{36}H_{70}ZnO_4$	000557-05-1		Xi		1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)	
Zinc sulfate	$ZnSO_4$	007733-02-0	10 %	—		1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	
Zinkchlorid	$ZnCl_2$	007646-85-7	10 %	C, Xn		1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	

Chemical resistance

Two values are given per substance
left number = value at +20℃ / right number = value at +50℃.

Два значения приведены для вещества
левое число = значение при +20 ° C / правое число = значение при +50 ° C.

0	no data available	0 нет данных
1	resistant	1 устойчивы
2	practically resistant	2 практически устойчивы
3	partially resistant	3 частично устойчивы
4	not resistant	4 не устойчивы
K	no general information available	K нет общей информации
L	danger of pitting or stress-cracking corrosion	L опасность точечной или растрескивание коррозии
( )	estimated value	() Оценочная стоимость

Hazard notes

E	explosive
O	oxidizing
F	highly flammable
F+	extremely flammable
T	toxic
T+	very toxic
C	corrosive
Xn	harmful
Xi	irritant
N	dangerous for the environment

Description of the materials

Thermoplastics

HDPE	Polyethylene (high density)
LDPE	Polyethylene (low density)
PA	Polyamide (Nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (PET copolymer)
PMP	Polymethylpentene (TPX®)
POM	Polyoxymethylene, polyacetal
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene-acrylnitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar®)
ETFE	Ethylene-tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon® FEP)
PTFE	Polytetrafluoroethylene (Teflon®)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene-propylene-diene rubber	
FPM, FKM	Fluorinated rubber (Viton®)	?
NBR	Acryl-nitrile-butadiene rubber	
SI	Silicone rubber	?

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)