

# On Interface and Oxide Degradation in VLSI MOSFETs—Part I: Deuterium Effect in CHE Stress Regime

David Esseni, Jeff D. Bude, *Associate Member, IEEE*, and Luca Selmi

**Abstract**—This paper analyzes in detail the generation of interface states ( $N_{it}$ ) and stress-induced leakage current (SILC) during channel hot electron (CHE) stress experiments in the context of a possible hydrogen/deuterium (H/D) isotope effect.

Our results show that  $N_{it}$  generation is related to the hydrogen release (HR) at the Si-SiO<sub>2</sub> interface at relatively high  $V_G$  where a large isotope effect is found. Instead, for gate voltages ( $V_G$ ) favorable for hot hole injection (HHI) the  $N_{it}$  creation becomes a unique function of hole fluence and the isotope effect disappears.

In the studied stress conditions, we found no experimental evidence supporting a causal relation between SILC generation and HR because no isotope effect is observed even when the corresponding  $N_{it}$  measurements reveal a very different D/H release rate. Similar to  $N_{it}$  generation, we found that SILC becomes a unique function of hole fluence at low stress  $V_G$ .

Relevant implications and extensions of these results to the Fowler-Nordheim (FN) tunneling stress conditions are discussed in the companion paper [47].

**Index Terms**—Channel hot electron (CHE) degradation, hydrogen/deuterium (H/D) isotope effect, interface states, MOSFETs reliability, stress-induced leakage current (SILC).

## I. INTRODUCTION

THE reduction of the gate oxide thickness has been systematically used as an essential ingredient for device downscaling in the evolution of MOS technologies [1]–[3], and the amount of work directed to thin oxide reliability in recent years is very remarkable. When stressed at high electric fields, thin oxides develop a progressive low voltage stress-induced leakage current (SILC) [4], [5] which is a serious concern for data retention of nonvolatile memories and represents the main obstacle for oxide scaling in these devices [6]–[10]. At larger charge fluences, oxides eventually experience a breakdown and their insulating properties are suddenly compromised. It has been recently pointed out that oxide breakdown may impose a limit to its scaling and this fact might in turn prevent silicon technology from attaining the SIA roadmap [11].

The significant research effort has led to a consensus on some important points concerning thin oxide reliability. It is quite generally accepted that the generation of the damage is correlated to electron energy at the anode [12]–[14] and it is thus




Fig. 1. Schematic representation of the process of interface states  $N_{it}$  generation related to the release of a H atom (right) from the Si-SiO<sub>2</sub> interface. In the HR model, the released H is involved in the subsequent generation of a bulk oxide trap  $N_{ot}$ . If the rate of release for deuterium (left) is slower than for hydrogen, then a slower creation of  $N_{ot}$  is expected in the HR model picture.

governed by the gate voltage ( $V_G$ ) rather than by the oxide field [15]–[18]. The conduction mechanism responsible for SILC is generally assumed to be a trap-assisted tunneling [19]–[21], [8], [22] that is most probably inelastic [23]–[27]; however, it is not completely clear yet whether oxide sites are mainly neutral or positively charged traps [28]. Furthermore, according to the percolation theory, breakdown occurs when oxide traps reach a critical density [29], [11], [30], [31] and SILC can thus be effectively used as a sensitive monitor of oxide degradation [8], [21].

Although it is generally accepted that the damage generation is governed by the electron energy at the anode, as mentioned above, two different models have been proposed for the mechanism that links electron energy to degradation. According to the hydrogen release (HR) model [21], [32] hot electrons at the anode cause the release of hydrogen (H) atoms from Si-SiO<sub>2</sub> interface and the migration of H species within the oxide results in the creation of the bulk-oxide traps ( $N_{ot}$ ) (see Fig. 1). The anode hole injection (AHI) model, instead, identifies the culprit in the injection of hot holes generated at the anode by energetic electrons [33], [14].

A tempting means to test the HR model is provided by recent experiments showing that using deuterium (D) instead of H for device passivation suppresses interface state ( $N_{it}$ ) generation in channel hot electron (CHE) stress conditions because D exhibits a much slower desorption yield than H in the electronic excitation regime [34], [35]. According to the HR model the desorption of hydrogen is also responsible for  $N_{ot}$  generation so that a D/H isotope effect on SILC is expected (see Fig. 1). Consequently, whether or not D annealing is also effective to reduce SILC [36]–[38], besides the clear applicative interest, can remarkably help enlighten the dominant cause of SILC generation.

Manuscript received March 12, 2001; revised July 30, 2001. The review of this paper was arranged by Editor G. Groeseneken.

D. Esseni is with Agere Systems, Murray Hill, NJ 07974 USA, on leave from DIEGM, University of Udine, I-33100 Udine, Italy.

J. D. Bude is with the Agere Systems, Murray Hill, NJ 07974 USA.

L. Selmi is with the DIEGM, University of Udine, I-33100 Udine, Italy.

Publisher Item Identifier S 0018-9383(02)00836-5.

Recent experiments [36] have reported that samples exhibiting a clear D/H isotope effect for  $N_{it}$  generation during CHE stress experiments show essentially no isotope effect for SILC produced by a Fowler-Nordheim (FN) stress. However, FN and CHE stress may not probe the same D concentration if the diffusion length of D from the spacers is small [34], [39], [36] because FN stress is spatially uniform along the channel whereas CHE damage is localized at the drain-end of the channel where the D concentration might be larger than elsewhere. Furthermore, since the isotope effect on  $N_{it}$  generation in FN stress conditions is much smaller than during CHE stress [40], [38], it is only using this latter stress regime that SILC generation can be studied in the context of a clearly different rate of D/H release at Si-SiO<sub>2</sub> interface.

In this paper, we systematically study the generation of  $N_{it}$  and SILC in CHE stress experiments in the context of a possible D/H isotope effect. Our results show that no isotope effect is observed on SILC even when a large effect is simultaneously observed on  $N_{it}$ . By exploring a variety of electron and hole injection conditions, we discuss the possible correlation of  $N_{it}$  and SILC generation to the D/H release at the interface and to hot hole injection (HHI).

In the companion paper [47], we will first use these results to compare the efficiency of a HR mechanism with experimental data of SILC produced by conventional high field stress conditions and then investigate in depth a possible AHI mechanism at low stress gate voltages.

## II. DEVICE TECHNOLOGY AND EXPERIMENTAL TECHNIQUES

The devices used in this work are n-MOS transistors fabricated with a 0.25- $\mu\text{m}$  technology. The oxide thickness is  $T_{ox} = 5 \text{ nm}$ , the device width and length are  $W = 39$  and  $L = 0.32 \mu\text{m}$ , respectively, and the threshold voltage is  $V_T \approx 600 \text{ mV}$ . The use of transistors is obviously necessary for CHE stress experiments, however also in the companion paper [47] (dealing with the FN stress regime) we will make use of n- and p-MOS transistors instead of capacitors because they provide more experimental knobs and degradation monitors that prove useful for our analysis.

Two otherwise identical wafers were annealed either in a 10% H<sub>2</sub> ambient at 425 °C for 2 h (H<sub>2</sub> devices) or in a 10% D<sub>2</sub> ambient at 450 °C for 5 h (D<sub>2</sub> devices). The drain current and transconductance characteristics of the *virgin*, as fabricated devices were virtually indistinguishable despite the different temperature and duration of the anneal, thus indicating that the only relevant difference between H<sub>2</sub> and D<sub>2</sub> samples is the substitution of deuterium to hydrogen in the passivation of the Si-SiO<sub>2</sub> interface.

CHE stress experiments were performed in a variety of drain voltage ( $V_D$ ) and  $V_G$  conditions and  $N_{it}$  generation was monitored using both linear drain current ( $I_D$ ) versus  $V_G$  characteristics and charge pumping (CP) measurements [41] performed at a frequency of 160 kHz. The main experimental hurdle related to SILC measurements in CHE conditions is the detection of extremely small values of gate current ( $I_G$ ). In fact, the extension of the damaged area during CHE conditions is confined to a small length close to the drain end of the channel which makes




Fig. 2. Typical  $I_G$  measurements obtained with the FG technique and comparison with direct measurements. The working principle of the technique is sketched:  $I_G$  was calculated from  $I_D$  drop as  $I_G \simeq [\Delta I_D / (G_m \cdot \Delta t)] \cdot C_G$ . Very good agreement between FG (open symbols) and direct measurements (filled symbols) is obtained in the  $V_G$  range where both are possible.

SILC proportional to device width rather than to device area. It is also worth noting that, for the relatively short devices necessary for CHE stress experiments, the width cannot be arbitrarily increased because the very large drain currents drawn during the stress make it difficult to accurately control the *intrinsic*  $V_D$  applied to the device due to possible voltage drops on *nonscaling* parasitic resistances such as the contact resistance between the tips and the pads.

In order to greatly improve  $I_G$  sensitivity over conventional direct measurements, we made use of the floating-gate (FG) technique. This characterization procedure was initially conceived for small  $I_G$  measurements during CHE stress experiments [42], [43] and it has been more recently used for the measurement of low tunneling currents [44], [45]. The basic idea of this technique is to use the MOS device as a very sensitive electrometer to convert small gate currents in  $V_G$  variations that can be in turn detected as  $I_D$  change (see the schematic description in the inset of Fig. 2).

In practice, after every stress step the  $I_D$  versus gate  $V_G$  characteristic was measured for a very small  $V_D = 10 \text{ mV}$  and the transconductance  $G_m$  was determined in the  $V_G$  range of interest. Then the gate electrode was charged to a suitable  $V_G$  value (slightly above the sensing  $V_G$  value which is to be probed), and subsequently floated by lifting up the gate probe. The average  $I_G$  value is proportional to the variation of  $V_G$  and can be readily calculated from the  $I_D$  drop as

$$I_G \simeq C_G \times \left[ \frac{\Delta I_D}{G_m \cdot W \Delta t} \right] \quad (1)$$

where  $C_G$  is the total gate capacitance. The capacitance  $C_G$  was measured to be approximately 0.5 pF (essentially the capacitance of the pad) and this value led to a very good agreement between FG and direct measurements when both were possible (see Fig. 2).

During all experiments a flux of dry nitrogen was present in the micro-chamber of the probe station [43] that suppressed any leakage current component at the surface of the wafer well below the minimum  $I_G$  that will be reported as a measurement




Fig. 3.  $I_{CP}$  and  $G_m$  variations versus  $T_{STR}$  for a stress  $V_D = 5.5$  and  $V_G = 2.5$  V corresponding to maximum substrate current. The results for two pairs of  $H_2$  and  $D_2$  devices are shown. Approximately the same 20 times isotope effect is observed for both monitors.




Fig. 4. SILC evolution corresponding to the same experiment of Fig. 3 and for three different sensing  $V_G$  values. The results for two pairs of  $H_2$  and  $D_2$  devices are shown. Essentially no isotope effect is observed.

result. To be conservative we can say that all data for  $I_G$  values above  $10^{-16}$  A were stable and reliable.

Since SILC is known to have a transient component [46], [28], in all measurements we carefully isolated the steady state SILC by performing preliminary  $I_G$  versus  $V_G$  characteristics with a very slow sweep rate also when SILC was to be measured with the FG technique.

### III. MEASUREMENT RESULTS

Fig. 3 shows CP current ( $I_{CP}$ ) and  $G_m$  variations for stress  $V_D = 5.5$  and  $V_G = 2.5$  corresponding to maximum substrate current. Consistently with previous studies [34], [35], a large isotope effect on both  $I_{CP}$  and  $G_m$  is observed showing approximately a 20 times slower rate of  $N_{it}$  generation in  $D_2$  devices. The corresponding SILC measurements are shown in Fig. 4 for three different sensing  $V_G$  and it is apparent that, in spite of the much slower rate of D desorption at the interface proved by  $N_{it}$  generation in Fig. 3, SILC measurements exhibit essentially no isotope effect. This comparison clearly points out that the generation of SILC cannot be causally related to H or D release in these stress conditions.

Fig. 5 shows  $I_G$  versus  $V_G$  characteristics of the devices used for our experiments: at large  $V_G$  a positive gate current due to hot electron injection is observed whereas for lower  $V_G$  values




Fig. 5. Measured  $I_G$  characteristics as a function of  $V_G$  and for  $V_D$  from 4.0 to 5.5 V in step of 0.25 V. At low  $V_G$  a negative  $I_G$  (open symbols) corresponding to HHI is clearly observed.




Fig. 6.  $I_{CP}$  variations for a stress  $V_D = 5.5$  V and  $V_G = 1$  V corresponding to the maximum HHI ( $I_G < 0$ ) or  $V_G = 3.25$  corresponding to hot-electron injection ( $I_G > 0$ ) (see Fig. 5). No isotope effect is observed in the early stage of the stress in the HHI stress condition.




Fig. 7. SILC evolution for a stress  $V_D = 5.5$  V and different  $V_G$  voltages corresponding to different  $I_G$  values (Fig. 5). SILC is dramatically increased when  $V_G$  is reduced and becomes progressively more favorable for HHI. No isotope effect is observed for any stress condition.

a negative  $I_G$  produced by HHI is found, consequently, the ratio between electron and hole injection during the stress can be changed by orders of magnitude adjusting the values of  $V_D$  and  $V_G$ .

The effect of the stress  $V_G$  is illustrated in Figs. 6 and 7 for  $I_{CP}$  and SILC, respectively. When  $V_G$  is reduced and becomes progressively more favorable for HHI, a very fast  $N_{it}$  creation is observed in Fig. 6, where the release of hydrogen from the




Fig. 8.  $I_{CP}$  evolution (circle, bottom and left axes) for a stress  $V_G = 1$  V and  $V_D = 5.5$  or  $4.5$  V. When  $V_D$  is reduced a clear isotope effect on  $I_{CP}$  emerges. SILC evolution (i.e.,  $\Delta I_G$  at a sensing  $V_G = 3.5$  V) for stress  $V_G = 1$  V and  $V_D = 4.5$  V is also reported (triangles, top and right axes) where no isotope effect is found.

interface is not presumably involved because no isotope effect is observed (at least in the early stage of the stress). The effect of stress  $V_G$  on SILC is much stronger than on interface states and Fig. 7 shows that oxide degradation is dramatically increased with decreasing  $V_G$ : the stress time ( $T_{STR}$ ) to reach a given  $\Delta I_G$  varies by more than six orders of magnitude when  $V_G$  changes between 1.0 and 3.25 V and, furthermore, no isotope effect on SILC is observed in any stress condition. The data of Fig. 7 strongly suggest that HHI plays an important role in the degradation of the oxide.

As for the correlation between HHI and the isotope effect on  $N_{it}$ , similar results as in Fig. 6 are obtained by varying  $V_D$  instead of  $V_G$ . In fact, Fig. 8 shows that if  $V_D$  is reduced from 5.5 to 4.5 V for  $V_G = 1.0$  V (thus drastically suppressing HHI—Fig. 5), then  $N_{it}$  creation is slowed and an isotope effect appears. On the contrary SILC still exhibits no correlation to the different rate of D and H release from the interface.

Since most SILC measurements have been obtained with the indirect FG technique, we have double-checked the results using conventional direct measurements. In fact, depending on the stress conditions, a direct measurement of SILC (i.e., not obtained with the FG technique) was also possible at large stress times. The insensitivity of SILC to D annealing could thus be also confirmed by direct measurements of post-stress  $I_G$  characteristics, as shown in Fig. 9.

#### IV. DISCUSSION

##### A. Possible Correlation Between $N_{it}$ and SILC Generation

The results reported so far demonstrate that in the CHE stress conditions there is no correlation between  $N_{it}$  and SILC generation and this is best illustrated by Fig. 10 where  $\Delta I_G$  is plotted as a function of the corresponding  $\Delta I_{CP}$  for different  $V_G$  and for both H<sub>2</sub> and D<sub>2</sub> devices. In fact, for a given amount of  $\Delta I_{CP}$  very different  $\Delta I_G$  are observed and, furthermore, when the isotope effect reduces  $N_{it}$  generation in D<sub>2</sub> devices, yet essentially the same  $I_G$  variations are found.

Fig. 11 illustrates the stress time  $T_{STR}$  necessary to reach a given  $I_{CP}$  or  $I_G$  increase and indicates a very different depen-




Fig. 9. Direct measurements (non-FG) of  $I_G$  versus  $V_G$  characteristics for virgin and stressed devices. Stress  $V_D = 5.5$  while  $V_G$  is 1.0 (with a  $T_{STR} = 2000$ ), 1.75 and 2.5 (with  $T_{STR} = 40000$ ). No isotope effect on SILC is observed.




Fig. 10. Stress-induced  $I_G$  variations (sensing  $V_G = 3.5$  V) plotted as a function of corresponding  $I_{CP}$  variations for stress  $V_D = 5.5$  and different stress  $V_G$  values. For a given amount of  $\Delta I_{CP}$  SILC is greatly increased for decreasing  $V_G$ . For a given stress condition D<sub>2</sub> devices exhibit essentially the same  $\Delta I_G$  for lower  $\Delta I_{CP}$ .




Fig. 11. Stress time to reach either an  $I_G$  increase of 0.5 fA (for a sensing  $V_G = 3.5$  V) or an  $I_{CP}$  increase of 2 nA as a function of the stress  $V_G$  and for stress  $V_D = 5.5$ . A very different  $V_G$  dependence of SILC and  $N_{it}$  generation is found and, furthermore, in the case of  $N_{it}$  a 20 times isotope effect is observed whereas in the case of SILC it is not. We verified that the qualitative behavior of  $T_{STR}$  versus stress  $V_G$  does not significantly depend on the target values used for  $\Delta I_{CP}$  and  $\Delta I_G$ .

dence of the two degradation monitors on the stress  $V_G$ . In the case of SILC,  $T_{STR}$  decreases by orders of magnitudes when  $V_G$  is reduced and HHI is favored and, furthermore, no clear improvement is observed in D<sub>2</sub> with respect to H<sub>2</sub> devices. As for  $\Delta I_{CP}$ , the  $V_G$  dependence of  $T_{STR}$  is much weaker and up to a 20 times lifetime increase is observed in D<sub>2</sub> devices.






Fig. 12. Stress-induced  $I_{CP}$  and  $I_G$  variations (for a sensing  $V_G = 3.5$  V) in the HHI regime versus hole fluence  $Q_h$  (i.e., the integral of  $I_G$  during the stress). Hot Hole gate current  $I_G$  is approximately 35, 115, and 550 fA for  $V_D = 5.0$ , 5.25, and 5.5 V, respectively (see Fig. 5).

The above results identify a clearly different behavior for SILC and  $N_{it}$  generation and, furthermore, two different mechanisms for  $N_{it}$  generation itself: at relatively large  $V_G$ ,  $N_{it}$  is related to the HR caused by CHE and a clear isotope effect is observed, whereas for small  $V_G$  a different mechanism dominates which is largely insensitive to the different D or H desorption rates.

#### B. The Hot Hole Injection Regime

In order to investigate more quantitatively the possible role of HHI on  $N_{it}$  and SILC generation we performed experiments in the HHI stress regime varying the drain voltage and, consequently, the hot hole gate current. As can be seen in Fig. 5,  $I_G$  changes by more than one order of magnitude when  $V_D$  is varied between 5.0 and 5.5 V for a gate voltage of approximately 1.0 V. The corresponding stress experiments reveal that the generation of both  $N_{it}$  and SILC scale fairly well with the gate current so that, as shown in Fig. 12, both  $\Delta I_{CP}$  and  $\Delta I_G$  are approximately unique functions of the hole fluence  $Q_h$  (i.e., the integral of  $I_G$  during the stress). The correlation between the damage generation and  $Q_h$  shown in Fig. 12 demonstrates that in this stress regime both interface and bulk oxide degradation are rate limited by HHI. The common origin of  $\Delta I_{CP}$  and  $\Delta I_G$  is best illustrated by Fig. 13 showing a one to one proportionality between the two degradation monitors. This correlation between  $N_{it}$  and SILC generation is peculiar to the HHI stress regime and represents a clear difference with respect to CHE conditions as can be easily seen comparing Figs. 13 to 10.

As for the high  $V_G$  range, it is worth noting that when  $V_G$  increases (for a given  $V_D$ ) hot electron injection increases by orders of magnitude as can be seen in Fig. 5. The dramatic reduction of SILC with increasing  $V_G$  (see Fig. 7) demonstrates that hot electrons cannot be the dominant cause of the oxide degradation. This latter fact is not completely surprising because in the CHE stress conditions the maximum of electron injection is most likely taking place in the region of the channel close to the inflection point of the oxide field  $E_{OX}$  (i.e., where  $E_{OX}$  changes its sign), so that electrons in the oxide typically experience a small field (with respect to values typical of the FN stress regime) and reach the poly electrode with only a small energy above  $\text{SiO}_2$  conduction band minimum. Consequently, as long




Fig. 13. Stress-induced  $I_G$  variations (for a sensing  $V_G = 3.5$  V) versus  $I_{CP}$  variations in the HHI regime. Hot Hole gate current  $I_G$  is approximately 35, 115, and 550 fA for  $V_D = 5.0$ , 5.25, and 5.5 V, respectively (see Fig. 5).

as the electron energy at the anode is the critical parameter for the oxide degradation, CHE injection is expected to induce a much smaller damage than FN tunneling for a given electron fluence.

As for holes, instead, for a given  $V_D$ , the injection into the oxide exponentially decreases with increasing  $V_G$  and the suppression of SILC with progressively larger  $V_G$  shown in Figs. 7 and 11 suggests that SILC generation might be rate limited by HHI also for relatively large  $V_G$ . This picture ascribing the generation of SILC to a mechanism which is not directly related to the HR could also explain why SILC never exhibits an isotope effect in the whole bias range explored in this work.

#### V. CONCLUSION

In the general framework of a possible assessment of the mechanisms responsible for thin oxide degradation, here quantified as SILC, in this paper we have exploited the recently pointed out D/H isotope effect [34], [35] to test the correlation between the desorption of hydrogen at  $\text{Si-SiO}_2$  and the creation of  $N_{it}$  and SILC.

Our results show that  $N_{it}$  generation is evidently related to stress-induced leakage current (H/D) release at relatively large stress gate voltages where the well known isotope effect is unambiguously observed [34], [35], whereas at low stress  $V_G$  it is rate limited by HHI because  $I_{CP}$  variations become a unique function of hole fluence  $Q_h$  and, furthermore, the beneficial effect of D annealing almost disappears.

In the studied stress conditions, we found no experimental evidence supporting the causal relation between SILC generation and H release at the  $\text{Si-SiO}_2$ . Instead, at low  $V_G$  the generation of SILC seems to have the same origin as  $N_{it}$  and it is rate limited by hole injection. At relatively large  $V_G$  SILC is greatly suppressed but no isotope effect is observed even when the corresponding  $N_{it}$  generation measurements reveal a very different D/H desorption rate.

In the companion paper [47], we will show that using these results obtained for CHE conditions it is possible to establish a reasonable upper boundary for the efficiency of a possible HR mechanism for SILC generation in the conventional high oxide field stress configuration. The possible role of AHI in these FN stress conditions will be also investigated in details.

## REFERENCES

- [1] R. H. Dennard, F. H. Gaensslen, L. Kuhn, N. Y. Yu, V. L. Ridout, E. Bas-sous, and A. LeBlanc, "Design of ion-implanted MOSFETs with very small physical dimensions," *IEEE J. Solid-State Circuits*, vol. SC-9, pp. 256–268, 1974.
- [2] G. Baccarani, M. R. Wordeman, and R. H. Dennard, "Generalized scaling theory and its application to a 1/4 micrometer MOSFET design," *IEEE Trans. Electron Devices*, vol. ED-31, pp. 452–462, 1984.
- [3] J. R. Brews, "The submicron MOSFET," in *High-Speed Semiconductor Devices*, S. Sze, Ed. New York: Wiley, 1990, ch. 3, p. 139.
- [4] J. Maserjian and N. Zamani, "Behavior of the Si/SiO<sub>2</sub> interface observed by Fowler-Nordheim tunneling," *J. Appl. Phys.*, vol. 53, pp. 559–567, 1982.
- [5] P. Olivo, T. N. Nguyen, and B. Riccò, "High-field induced degradation in ultrathin SiO<sub>2</sub> films," *IEEE Trans. Electron Devices*, vol. 35, pp. 2259–2267, Dec. 1988.
- [6] N. Naruke, S. Taguchi, and M. Wada, "Stress-induced leakage current limiting to scale down EEPROM tunnel oxide thickness," in *IEDM Tech. Dig.*, 1988, pp. 424–427.
- [7] M. Kato, N. Miyamoto, H. Kume, A. Satoh, T. Adachi, M. Ushiyama, and K. Kimura, "Read-disturb degradation mechanism due to electron trapping in the tunnel oxide for low-voltage flash memories," in *IEDM Tech. Dig.*, 1994, pp. 45–48.
- [8] J. De Blauwe, J. Van Houdt, D. Wellekens, G. Groeseneken, and H. E. Maes, "SILC related effects in flash E<sup>2</sup>PROMs—Part I: A quantitative model for steady-state SILC," *IEEE Trans. Electron Devices*, vol. 45, pp. 1745–1750, Aug. 1998.
- [9] —, "SILC related effects in flash E<sup>2</sup>PROMs—Part II: Prediction of steady-state SILC-related disturb characteristics," *IEEE Trans. Electron Devices*, vol. 45, pp. 1751–1760, Aug. 1998.
- [10] S. Satoh, G. Hemink, K. Hatakeyama, and S. Aritome, "Stress-induced leakage current of tunnel oxide derived from flash memory read-disturb characteristics," *IEEE Trans. Electron Devices*, vol. 45, pp. 482–486, Feb. 1998.
- [11] J. Stathis and D. J. DiMaria, "Reliability projection for ultra-thin oxides at low voltage," in *IEDM Tech. Dig.*, 1998, pp. 167–170.
- [12] D. J. DiMaria and J. Stasiak, "Trap creation in silicon dioxide produced by hot electrons," *J. Appl. Phys.*, vol. 65, no. 6, pp. 2342–2356, 1989.
- [13] N. Patel and A. Toriumi, "Stress-induced leakage current in ultrathin SiO<sub>2</sub> films," *Appl. Phys. Lett.*, vol. 64, no. 14, pp. 1809–1811, 1994.
- [14] J. Bude, B. Weir, and P. Silverman, "Explanation of stress-induced damage in thin oxides," in *IEDM Tech. Dig.*, 1998, pp. 179–182.
- [15] D. J. DiMaria, "Defect generation under substrate-hot-electron injection into ultra-thin silicon dioxide layers," *J. Appl. Phys.*, vol. 86, no. 4, pp. 2100–2109, 1999.
- [16] P. E. Nicollian, W. R. Hunter, and J. C. Hu, "Experimental evidence for voltage driven breakdown models in ultrathin gate oxides," in *Proc. Int. Reliability Physics Symp.*, 2000, pp. 7–15.
- [17] J. M. McKenna, E. Y. Wu, and S.-H. Lo, "Tunneling current characteristics and oxide breakdown in P+ poly gate PFET capacitors," in *Proc. Int. Reliability Physics Symp.*, 2000, pp. 16–20.
- [18] M. A. Alam, J. D. Bude, and A. Ghetti, "Field acceleration for oxide breakdown—Can an accurate anode hole injection model resolve the  $E$  versus  $1/E$  controversy?," in *Proc. Int. Reliability Physics Symp.*, 2000, pp. 21–26.
- [19] R. Rofan and C. Hu, "Stress-induced oxide leakage," *IEEE Electron Device Lett.*, vol. ED-12, pp. 632–634, Nov. 1991.
- [20] D. J. Dumin and J. R. Maddux, "Correlation of stress-induced leakage current in thin oxides with trap generation inside the oxides," *IEEE Trans. Electron Devices*, vol. 40, pp. 986–992, May 1993.
- [21] D. J. DiMaria and E. Cartier, "Mechanism for stress-induced leakage currents in thin silicon dioxide films," *J. Appl. Phys.*, vol. 78, no. 6, pp. 3883–3894, 1995.
- [22] B. Riccò, G. Gozzi, and M. Lanzoni, "Modeling and simulation of stress-induced leakage current in ultra thin SiO<sub>2</sub> films," *IEEE Trans. Electron Devices*, vol. 45, pp. 1554–1560, July 1998.
- [23] S. Takagi, N. Yasuda, and A. Toriumi, "Experimental evidence of inelastic tunneling and new I-V model for stress-induced leakage current," in *IEDM Tech. Dig.*, 1996, pp. 323–326.
- [24] E. Rosenbaum and L. F. Register, "Mechanism of stress-induced leakage current in MOS capacitors," *IEEE Trans. Electron Devices*, vol. 44, pp. 317–323, Feb. 1997.
- [25] S. Takagi, N. Yasuda, and A. Toriumi, "Experimental evidence of inelastic tunneling in stress-induced leakage current," *IEEE Trans. Electron Devices*, vol. 46, pp. 335–341, Feb. 1999.
- [26] —, "A new  $I-V$  model for stress-induced leakage current including inelastic tunneling," *IEEE Trans. Electron Devices*, vol. 46, pp. 348–354, Feb. 1999.
- [27] A. Ghetti, M. A. Alam, J. D. Bude, D. Monroe, E. Sangiorgi, and H. Vaidya, "Stress-induced leakage current analysis via quantum yield experiments," *IEEE Trans. Electron Devices*, vol. 47, pp. 1341–1348, July 2000.
- [28] D. Ielmini, A. Spinelli, M. A. Rigamonti, and A. L. Lacaita, "Modeling of SILC based on electron and hole tunneling—Part I: Transient effects," *IEEE Trans. Electron Devices*, vol. 47, pp. 1258–1265, June 2000.
- [29] R. Degraeve, G. Groeseneken, R. Bellens, J. L. Ogier, M. Depas, P. J. Roussel, and H. E. Maes, "New insights in the relation between electron trap generation and the statistical properties of oxide breakdown," *IEEE Trans. Electron Devices*, vol. 45, pp. 904–911, Apr. 1998.
- [30] M. A. Alam, B. E. Weir, J. D. Bude, P. J. Silverman, and D. Monroe, "Explanation of soft and hard breakdown and its consequences for area scaling," in *IEDM Tech. Dig.*, 1999, pp. 449–452.
- [31] J. H. Stathis, "Percolation models for gate oxide breakdown," *J. Appl. Phys.*, vol. 86, p. 5757, 1999.
- [32] D. J. DiMaria, "Electron energy dependence of metal-oxide-semiconductor degradation," *Appl. Phys. Lett.*, vol. 75, no. 16, pp. 2427–2428, 1999.
- [33] K. F. Schuegraf and C. Hu, "Hole injection SiO<sub>2</sub> breakdown model for very low voltage lifetime extrapolation," *IEEE Trans. Electron Devices*, vol. 41, pp. 761–767, May 1994.
- [34] K. Hess, I. C. Kizilyalli, and J. W. Lyding, "Giant isotope effect in hot electron degradation of metal oxide silicon devices," *IEEE Trans. Electron Devices*, vol. 45, pp. 406–416, Feb. 1998.
- [35] K. Hess, J. Lee, Z. Chen, J. W. Lyding, Y.-K. Kim, B.-S. Kim, Y.-H. Lee, Y.-W. Kim, and K.-P. Suh, "An alternative interpretation of hot electron interface degradation in NMOSFETs: Isotope results irreconcilable with major defect generation by holes?," *IEEE Trans. Electron Devices*, vol. 46, pp. 1914–1916, Sept. 1999.
- [36] J. Wu, E. Rosenbaum, B. MacDonald, E. Li, J. Tao, B. Tracy, and P. Fang, "Anode hole injection versus hydrogen release: The mechanism for gate oxide breakdown," in *Proc. Int. Reliability Physics Symp.*, 2000, pp. 27–32.
- [37] B. C. Lin, Y. C. Cheng, A. Chin, T. Wang, and C. Tsai, "Deuterium effect on stress-induced leakage current," *Jpn. J. Appl. Phys.*, vol. 38, no. 4B, pp. 2337–2340, 1999.
- [38] Y. Mitani, H. Satake, H. Ito, and A. Toriumi, "Deuterium effect on both interface-state generation and stress-induced-leakage-current under Fowler-Nordheim electron injection," in *Proc. Solid State Devices and Materials*, 2000, pp. 40–41.
- [39] T. G. Ference, J. S. Burnham, W. F. Clark, T. B. Hook, S. W. Mittl, K. M. Watson, and L. K. Han, "The combined effects of deuterium anneals and deuterated barrier-nitride processing on hot-electron degradation in MOSFETs," *IEEE Trans. Electron Devices*, vol. 46, pp. 747–753, Apr. 1999.
- [40] Z. Chen, K. Hess, J. Lee, J. W. Lyding, E. Rosenbaum, I. Kizilyalli, S. Chetlur, and R. Huang, "On the mechanism for interface trap generation in MOS transistors due to channel hot carrier stressing," *IEEE Electron Device Lett.*, vol. ED-21, pp. 24–26, Jan. 2000.
- [41] G. Groeseneken, H. E. Maes, N. Beltran, and R. Keersmaecker, "A reliable approach to charge-pumping measurements in MOS transistors," *IEEE Trans. Electron Devices*, vol. ED-31, pp. 42–53, Jan. 1984.
- [42] Y. Nissan-Cohen, "A novel floating-gate method for measurement of ultra-low hole and electron gate currents in MOS transistors," *IEEE Electron Device Lett.*, vol. ED-7, pp. 561–563, Oct. 1986.
- [43] N. S. Saks, P. L. Heremans, L. Van Den Hove, H. E. Maes, R. F. De Keersmaecker, and G. J. Declerck, "Observation of hot-hole injection in NMOS transistors using a modified floating-gate technique," *IEEE Trans. Electron Devices*, vol. 33, pp. 1529–1533, Oct. 1986.
- [44] B. Fishbein, D. Krakauer, and B. Doyle, "Measurements of very low tunneling current density in SiO<sub>2</sub> using the floating-gate technique," *IEEE Electron Device Lett.*, vol. 12, pp. 713–715, Dec. 1991.
- [45] B. De Salvo, G. Ghibaudo, G. Pananakakis, and B. Guillaumot, "Investigation of low field and high temperature SiO<sub>2</sub> and ONO leakage currents using the floating gate technique," *J. Non-Cryst. Solids*, vol. 245, pp. 104–109, 1999.
- [46] R. Moazzami and C. Hu, "Stress-induced current in thin silicon dioxide films," in *IEDM Tech. Dig.*, 1992, pp. 139–142.
- [47] D. Esseni, J. D. Bude, and L. Selmi, "On interface and oxide degradation in VLSI MOSFETs—Part II: Fowler-Nordheim stress regime," in *IEEE Trans. Electron Devices*, vol. 49, Feb. 2002, pp. 254–263.



**David Esseni** received the Laurea degree and the Ph.D. degrees in electronic engineering from the University of Bologna, Bologna, Italy, in 1994 and 1998, respectively.

In 1999, he became an Assistant Professor with the University of Udine, Udine, Italy. In 2000, he was a Visiting Scientist with Bell Labs, Murray Hill, NJ, now Lucent Technologies. His research interests include characterization techniques for electrical parameters in MOS devices and several aspects related to hot-electron in MOSFETs and Flash EEPROMs. In particular, he has investigated low-voltage and substrate-enhanced hot electron phenomena with an emphasis on their practical implications for Flash EEPROM devices. More recently, he was involved in the experimental characterization and modeling of low-field mobility in ultra-thin SOI MOSFETs and in the experimental investigation of the physical mechanisms responsible for thin oxides degradation.

**Jeff D. Bude** (A'93), photograph and biography not available at the time of publication.



**Luca Selmi** was born in 1961.

In 2000, he became Full Professor of electronics with the University of Udine, Udine, Italy. During 1989–1990, he was a Visiting Scientist with Hewlett Packard's Microwave Technology Division, Santa Rosa, CA. In 1995–1996, he was a Member of the IEDM technical subcommittee on "Modeling and Simulation." Since 2001, he has held the same position on the "Circuit and Interconnect Reliability" subcommittee. His research interests include characterization and simulation of silicon devices with emphasis on Monte Carlo transport techniques and hot carrier effects in MOSFETs and Nonvolatile memory cells, leakage currents, and reliability of ultrathin oxides and device optimization. These activities have been conducted in cooperation with international research centers such as Bell Labs, the IBM T.J.Watson Research Center, Philips Research Laboratories, INPG, and LETI Grenoble. He has co-authored approximately 90 papers, including 18 IEDM papers.