

Defect engineering of oxide surfaces: dream or reality?

Gianfranco Pacchioni^{1,*}  and Talat S Rahman^{2,3} 

¹ Dipartimento di Scienza dei Materiali, Università di Milano-Bicocca, via R. Cozzi 55, 20125, Milano, Italy

² Department of Physics, University of Central Florida, Orlando, FL 32816, United States of America

³ Renewable Energy and Chemical Transformation Cluster, University of Central Florida, Orlando, FL 32816, United States of America

E-mail: gianfranco.pacchioni@unimib.it

Received 2 March 2022, revised 25 April 2022

Accepted for publication 3 May 2022

Published 19 May 2022



Abstract

In this brief perspective we analyze the present status of the field of defect engineering of oxide surfaces. In particular we discuss the tools and techniques available to generate, identify, quantify, and characterize point defects at oxide surfaces and the main areas where these centers play a role in practical applications.

Keywords: vacancies, point defects, oxides, surfaces

1. Introduction and definitions

Defects, with their variable nature, concentration, and complex kinetic behavior, largely determine the functionality, durability, and properties of oxide-based devices [1]. This holds true for both extended and point defects. These latter are particularly difficult to identify due to their reduced dimensionality and low concentrations. Defects can exist in various charge states and can act as electrons/holes traps or recombination centers [2], thus altering the electrical, optical, magnetic, and chemical properties of a material. Even mechanical and thermal properties can be affected by the presence of defects [3]. On the side of applications, the nature and concentration of defects in oxides affect the efficiency, stability, and lifetime of a device. For instance, ion segregation to surfaces and interfaces may depend on the presence of point defects and can lead to performance degradation. Particularly relevant is the role of point defects at the surface of oxides (solid/gas or solid/liquid interface) [4–6] or at the junction between two materials (solid/solid interface) [7].

In this perspective article we discuss the present status of use, creation, and characterization of defects on oxide surfaces, with particular attention to new approaches and techniques. The focus is on point defects: cation or anion vacancies, anti-site defects, impurity atoms, surface irregularities,

low-coordinated atoms (corners, kinks), hydroxyl or peroxo groups, etc. Extended defects, dislocations, grain boundaries, etc are not included in the discussion. We reiterate that the focus here is not on the emerging area of defects in two dimensional materials which has already shown to lead to very interesting chemical (see e.g. reference [8]) and physical (see e.g. reference [9]) consequences. Finally, one has also to mention that a distinction between surface and bulk defects is often difficult at the experimental level, and that many properties are determined by bulk more than by surface defects.

The article does not have the ambition to provide a comprehensive view of the field, but rather to focus on the state-of-the-art knowledge with a concise analysis of the tools available for the study and use of point defects at oxide surfaces. The aim is to establish where we are in terms of capability of identifying and counting point defects at oxide surfaces and of exploiting them in practical applications. The article is organized in three sections: (a) role and use, (b) generation, and (c) characterization of surface defects. For each section we provide a list of examples and a brief description, including a few representative references.

2. Potential use of defects at oxide surfaces

The most relevant impact of surface defects is on the chemistry, table 1. Not surprisingly, the largest part of studies dealing with this topic refer to modifications of catalytic,

* Author to whom any correspondence should be addressed.

Table 1. Processes related to point defects at oxide surfaces.

	Brief description of role of defects	References
Chemical properties		
Thermal catalysis	Change of surface reactivity Charging of adsorbed species Induce presence of radical species or sites Doping with heteroatoms (including single-atom catalysts) Promoting (or inhibiting) effects Stabilize surface species (supported metal particles)	[10, 11, 16]
Photocatalysis	Change optical absorption Affect electron–hole recombination Increase photocatalytic activity	[11, 13]
Electrocatalysis	Charging and activation of adsorbed species Induce band bending	[14, 15]
Electrodes for fuel cells, batteries, supercapacitors	Modify ionic and electronic conductivity Enhances oxygen reduction	[17–20]
Gas sensors	Modulate amount of surface adsorbed species Modify electrical conductivity	[22, 23]
Defect passivation	Passivation by adsorbed functional groups	[24, 25]
Physical properties		
Conductivity, semiconductors	Introduce donor levels in the gap; free electrons are produced by thermal activation Formation of bands at high vacancy concentration Introduce high mobility species	[26, 27]
Memristors	Ion or vacancy diffusion processes for resistive switches	[28, 29]
Metal/insulator transition	Induce sharp change in resistivity as function of temperature Reversible transition as a function of vacancies concentration Band gap opening	[30–32]
Ferroelectric domain walls	Induce local bending in domain walls Act as charge traps Tune transport properties	[33]

photocatalytic or electrocatalytic properties of oxide materials [10–15]. As McFarland and Metiu wrote in a seminal review on this subject ‘it is very likely that doped oxide catalysts have been used before the concept was formulated explicitly [...] it is possible that catalysis by doped oxides is as old as catalysis by oxides, but we were not aware of the fact’ [16]. In recent years the interest towards controlling surface defects for chemical properties has increased and has involved defects engineering for cathode materials for fuel cells [17], properties of photocatalytic systems [11, 13], electrodes in batteries and supercapacitors [18–20], etc.

A separate discussion should be dedicated to the exploding field of single atom catalysts (SAC). These are catalytic systems consisting of a transition metal atom bound to an oxide support either by new chemical bonds or directly replacing a lattice atom [21]. Before the introduction of the term SAC, these entities were simply classified as impurity atoms or extrinsic defects, as they possess the typical characteristics of dopants in a host material. The reader is referred to the abundant literature on this specific topic [21].

The other classical field where surface defects play a dominant role is gas sensors [22, 23]. For instance, the ability of the surface to incorporate oxygen depends on the availability of oxygen-accommodating vacant lattice or interstitial defect sites [22]. But more in general, the adsorption of gas-phase molecules largely depends on the presence of active sites related to surface defects. These can also affect the electrical conductivity of the material, another essential characteristic of sensors [23].

The presence of surface defects is not always beneficial and may result in deterioration of the properties. Recently, new approaches have been proposed to passivate surface defects by adsorption of specific molecular complexes [24, 25]. For instance, this is relevant to reduce perovskite defects and suppress ion movement, improving the performances [24].

Not less important from a technological point of view, are the studies of surface defects that affect conductive properties [26, 27]. Here particularly relevant is the role of oxygen vacancies at the interface of materials forming the active

part of memristor devices; ion diffusion processes are relevant for resistive switches and memristors [28, 29]. An interesting possibility is the use of external electric fields to induce formation of oxygen vacancies with direct effects on the metal/insulator transition [30–32]. Finally, oxide point defects have an important role for ferroelectric domain walls nanoelectronics [33].

3. Generation of surface defects

When talking of ‘defects engineering’ one should not forget that the preferential sites where defects form in a material depend on their thermodynamic stability. For instance, while an oxygen vacancy prefers to form on the surface layer of the rutile $\text{TiO}_2(110)$ surface, the same defect forms preferentially in sub-surface layers of the (101) surface of the anatase TiO_2 polymorph [34]. Thus, the idea of ‘defect engineering’ cannot be disjoint from the intrinsic preference of some defects to segregate in the bulk rather than on the surface. Another aspect to consider is that methods to generate defects may result in high damage of the surface, with moderate control on the final structure, amorphization, formation of voids, etc.

Classical approaches to generate defects are based on chemical methods, some of which are summarized in table 2. These include introduction of aliovalent atoms with consequent formation of vacancies to keep charge neutrality [35, 36], oxygen desorption by thermal treatment in vacuum or in hydrogen atmosphere [12, 37], chemical or electrochemical reduction [38, 39], etc. Oxygen vacancies can also form as a result of chemical etching with reductive agents such as sodium borohydride and hydrazine hydrate [40]. In recent years it has become increasingly clear that oxygen vacancies may form in the course of a reaction at the periphery of supported metal particles, indicating a preferential removal of oxygen from these sites [41].

Other approaches to create defects imply irradiating the surface with UV-light [42, 43] or with electrons [44–46], bombarding the surface with ions of variable kinetic energy [47–50], or by mechanical action with consequent rupture of chemical bonds [51, 52]. These techniques lead to a variable level of control of position and number of oxygen defects at the surface. For instance, by UV-irradiation one can remove just a few O atoms from the surface or can reduce the system to the point that a two-dimensional electron gas forms, as for UV-irradiated SrTiO_3 [42]. Using ion bombardment or mechanical activation the surface is often highly damaged [53].

Completely different is the case of surface manipulation with scanning tunneling microscopy (STM) and atomic force microscopy (AFM) tips, an area where substantial progress has been made in recent years [54]. For instance, using the tip of a non-contact AFM oxygen vacancies can be reversibly created on rutile TiO_2 by means of a voltage pulse [55], a process that can be simulated using accurate pair potentials [56]. These techniques are highly sensitive and site-specific but can be applied only to well defined surfaces and are relevant for model studies. Nevertheless, they provide information on the atomistic structure of defects and on their mobility that were simply unthinkable up to twenty years ago.

4. Characterization of surface defects

Point defects are, by definition, elusive species. Since they are present in small amounts, their detection requires sophisticated and very sensible techniques (see table 3). Of the three areas discussed in this perspective, characterization is probably where progress has been most substantial. For instance, it has become common practice to combine a variety of techniques, each providing a specific piece of information, and to compare the results with supporting theoretical modeling, mostly based on DFT [57, 58] leading to an atomistic representation of the defect and of its properties.

Impressive advances have been made in the imaging of materials with high-resolution microscopies. Aberration correction TEM [59, 60] and scanning transmission electron microscopy (STEM) [61, 62] have become standard approaches to visualize defects in the bulk or at the interface of materials. On model systems, the use of STM and AFM microscopies [63, 64], sometimes in a combined mode, produce spectacular views of point defects and their surroundings. With an STM tip one can also do single-site spectroscopy, invaluable to study the spectroscopic features of an isolated defect [65].

On the non-local scale, beside the widely adopted UV–vis [66, 67], photoluminescence [68, 69], Fourier transform infrared (FT-IR) [70–72], infrared reflection absorption spectroscopy (IRAS) [73] and Raman [74, 75] techniques, relevant information on the dynamics of surface defects can be obtained with photo-induced enhanced Raman spectroscopy (PIERS) [76]. Surface vibrations associated to defects can be detected using electron energy loss spectroscopy (EELS) [77, 78] and reflection electron energy loss spectroscopy (REELS) [79, 80] in which the electron beam does not strike the sample but interacts with it via the long-ranged Coulomb interaction. A novel sophisticated vibrational technique to detect defects is surface action spectroscopy (SAS) [81]. This is based on the exposure of a surface at low-temperature and in UHV conditions to a messenger species (e.g. Ne or Ar); this species is then desorbed via absorption of IR light from a free-electron laser. The desorption rate at a given IR frequency provides specific information on surface structure and defect sites.

The role of electron paramagnetic resonance (EPR) to identify paramagnetic impurities on oxide surfaces has grown since, beside the classical continuous wave EPR, high spectral resolution can be attained with pulse EPR at Q band frequency [82, 83]. Recently even NMR spectra have been used to identify surface defects with high precision [84, 85].

Widely used are x-ray absorption, x-ray emission [86–88], and photoemission (XPS, UPS) spectroscopies [87–90]. In particular, x-ray absorption fine structure (EXAFS) is essential to determine the bond length and coordination number of atoms in the lattice while x-ray absorption near edge structure (XANES) provides invaluable information about the coordination number and oxidation state of impurity atoms.

Information on defects can also be obtained with less common techniques such as the positron annihilation lifetime spectroscopy (PALS) [91, 92] and the metastable impact

Table 2. Methods and techniques to generate surface point defects.

Method or technique	Brief description	References
Chemical methods		
Metal/non metal doping	Generate charge unbalance; defects form to keep electroneutrality Introduce heteroatoms at the surface (surface segregation) Deposition of surface atomic species from impregnation/reduction	[35, 36]
Vacuum thermal annealing	Oxygen desorption and O vacancies formation	[37]
Hydrogen thermal treatment	H ₂ adsorption followed by H ₂ O desorption and O vacancies formation	[12]
Chemical reduction	Molecular adsorption followed by thermal annealing with formation of O vacancies Microwave assisted hydrothermal treatment Electrochemical reduction	[38, 39]
Chemical etching	Reductive chemical agents (NaBH ₄)	[40]
Reaction produced defects (metal/oxide interfaces)	Reduced O vacancy formation energy at periphery of supported metal particles Formation of O vacancies due to O incorporation in an organic substrate (MvK mechanism of oxidation in catalysis)	[41]
Light irradiation		
UV-irradiation	UV-induced O vacancy formation Change in resistance and 2D electron-gas from O desorption	[42, 43]
Surface damage		
Electron irradiation and electron bombardment	Selective removal of surface ions (formation of O vacancies)	[44–46]
Swift-ion bombardment	Bombardment with ions with high kinetic energy Induce damage, amorphization, defects clustering Modulate defect formation by tuning energy of impacting ions	[47, 48]
Ar ⁺ ion bombardment	Bombardment with low-energy Ar ⁺ ions Selective formation of O vacancies Formation of sub-oxides in surface region	[49, 50]
Mechanical activation (mechanochemistry)	Electron release under ball milling due to vacancy formation (even in nonreducible oxides) Solvent-free, low temperature treatment	[51, 52]
Atomistic manipulation		
STM and AFM induced defects	Atoms selectively removed or displaced by STM or AFM tip Works for model studies only	[54, 55]

electron spectroscopy (MIES) [93, 94]. This latter is particularly relevant since it is highly sensitive to surface species. The panorama is completed by diffraction and scattering techniques (x-ray [95, 96] and neutron [97] diffraction, He scattering [98]).

Of particular relevance is the study of the dynamics of oxygen vacancies, a phenomenon crucial in catalysis [99],

memristor devices [100], dielectric breakdown in insulating oxides [101], etc. There are various methods to follow the dynamical behavior of vacancies. PIERS allows for the evaluation of atomic V_o dynamics in metal oxide surfaces [76]. Dielectric spectroscopy is employed to probe high and low resistance states related to oxygen migration and to understand the dynamics of oxygen vacancies in memristors [100].

Table 3. Characterization methods of surface defects.

Method or technique	Brief description	References
Microscopies		
Aberration corrected high-resolution transmission electron microscopy	Atomic resolution, imaging of surfaces, including dopants and vacancies	[59, 60]
STEM	Atomic resolution (with annular dark field and annular bright field detectors)	[61, 62]
STM and scanning tunneling spectroscopy	Atomic resolution, vacancies and impurities Requires a conducting planar support Allows manipulation of defects Not only microscopy, also spectroscopy	[63, 65]
AFM	Atomic resolution, vacancies and impurities Can be used also with insulating supports	[54, 64]
Spectroscopies		
UV–visible (UV–vis)	Coordinatively unsaturated sites, trapped charges	[66, 67]
Photoluminescence	Intra-band-gap states associated with localized defects	[68, 69]
FT-IR, IRAS	Adsorbed probe molecules (CO, CO ₂ , phosphines), functional groups (OH, peroxy, etc)	[70–73]
Raman spectroscopy	Highly sensitive to local coordination Lattice defects Vibrational properties of molecules adsorbed on surface defects	[74, 75]
PIERS, surface enhanced Raman spectroscopy	Evaluation of atomic dynamics of O vacancies in oxide surfaces Stability of atomic defects at ambient pressure and under operando conditions	[76]
EELS, REELS	Surface vibrations Oxidation states of host cations	[77–80]
SAS	Detect localized electronic states in band gap Structural information independent of long-range order of the sample	[81]
EPR	Requires a free-electron laser Trapped electrons, transition metal impurities, paramagnetic F centers Surface radical species	[82, 83]
Solid state nuclear magnetic resonance	Highly sensitive to electron localization Magic-angle spinning NMR spectroscopy of adsorbed probe molecules	[84, 85]
X-ray absorption spectroscopy, EXAFS, XANES, etc	Highly sensitive to low amounts of dopants Info on local structure, coordination, bond distances SAC, dopants	[86–88]
X-ray photoemission spectroscopy (XPS), ultraviolet photoemission spectroscopy (UPS), resonant photoemission	Vacancies, interstitials, dopants Chemical composition, oxidation state Not very sensitive to low amounts of defects	[87–90]
PALS	Electron–positron annihilation photons allow measurement of the lifetime of positrons, providing information on defects	[91, 92]
MIES	Surface sensitive technique, uses excited helium atoms as a surface probe Sensitive to small amounts of defects	[93, 94]
Diffraction, scattering		
X-ray diffraction, synchrotron x-ray diffraction	Atomically resolved structural model for oxide surface, lattice constants Defect induced lattice strain	[95, 96]

(continued on next page)

Table 3. Continued

Method or technique	Brief description	References
Microscopies		
Neutron diffraction	Hydrogen impurities, oxygen defects, oxygen sublattice	[97]
He atom scattering	Hydrogen on oxide surfaces	[98]
Quantum theory		
Periodic approaches (density functional theory, DFT)	Electronic structure of vacancies and impurities Theoretical spectroscopic properties Defect formation energies	[36, 103]
Local cluster model approaches (<i>ab initio</i> methods)	High-level computational spectroscopy	[104, 105]

One can track the dynamic oxygen vacancy behavior with STEM, obtaining atomic-level quantitative information on phase transformation and oxygen diffusion [102]. Recently, specific doping by Gd ions of CeO₂ has been used to transform mobile oxygen vacancies into clustered or immobile vacancies [99], showing the possibility to control, to a certain extent, the mobility of these centers.

All these methods are complemented and supported by increasingly sophisticated quantum-chemical approaches either based on periodic [36, 103] or on local cluster models [104, 105]. Probably, the combined use of spectroscopic and microscopic measurements with well-defined structural models represents the most relevant advance in the field of defects engineering in recent years.

5. Computational studies of surface defects

Computational characterization of defects on oxide surfaces has relied on methods based on density functional theory with the aim of increasing the accuracy of the approach [57, 103–107]. While DFT has had amazing success in providing insights into factors that control the nature of point defects at surfaces, it has well known limitations such as underestimation of band gaps and overestimation of electron delocalization and metallic character of systems, as summarized in reference [106]. These limitations are particularly important for materials with *f* electrons, as the role of electron correlation becomes increasingly important and methods beyond DFT need to be invoked. A number of beyond DFT methods have thus been introduced to overcome these limitations for oxides, including DFT + *U*, application of a variety of hybrid functionals, a quantum many-electron approach [108] and dynamical mean field theory combined with DFT [109] with good success in describing characteristics of oxides that have long alluded researcher. The computational demand set by the beyond DFT approaches (except for DFT + *U*), however, still poses technical challenges in addressing inhomogeneities in the computational super cell as introduced by surfaces with point defects. The recent successful application of the multireference density matrix embedding theory to point defects on several oxides [101] is very encouraging.

6. What next?

Novel and advanced preparation, characterization, and simulation tools offer the potential to investigate defects in great detail, not only identifying their local environment, but also their temporal evolution during chemical reactions, the kinetics of formation and annealing, the electronic properties, the associated gap states, the absorption and emission characteristics, the capability to trap charges, etc. While this provides an unprecedented arsenal of approaches to generate and characterize point defects, it becomes increasingly clear that, due to their small dimensionality, defect properties are highly sensitive to the chemical surrounding. This is the essence of coordination chemistry, where the features of a transition metal atom can be modified by changing the ligands around the metal center. Impurity atoms or missing ions (vacancies can be considered as pseudo-atoms) may exhibit radically different properties depending on the specific structure. Even the smallest change of coordination, for instance by displacing the defect from a terrace to a step, can produce radically different properties. Despite the enormous progress done in the past twenty years, the precise identification of the defect structure still represents a challenge for theory and experiment.

Even more difficult is to generate defects with a specific and desired chemical environment. Here the progress has been marginal. Most of the methods used largely rely on tuning the preparation conditions to obtain a more or less defective sample or require to severely damage the surface with post-synthetic treatments in order to generate the defects. On the other hand, great advances have been made in model systems thanks to the use of scanning probe spectroscopies or microscopies.

There is growing evidence that defects at oxide surfaces can be exploited to improve a variety of properties, both chemical and physical. For the future what is needed is to improve measurement techniques for operation at high temperatures and complex environments, thereby enabling characterization under *in situ* conditions in which oxides are often used.

In summary, the capability to control defects at oxide surfaces, which is the basis of the defect engineering concept, has done significant progress but can be further improved. Given the importance that these species have in several applied fields, there is little doubt that this objective will be at the center of research interest in the next years.

Acknowledgments

Prof. Hajo Freund (FHI Berlin) and Prof. Elio Giamello (University of Torino) are gratefully acknowledged for critical reading of the manuscript. The work of GP was supported by the Italian Ministry of University and Research (MIUR) through the PRIN Project 20179337R7, and the Grant Dipartimenti di Eccellenza-2017 ‘Materials For Energy’ and that of TSR by US National Science Foundation through Grant CHE-1955343.

Data availability statement

No new data were created or analysed in this study.

ORCID iDs

Gianfranco Pacchioni  <https://orcid.org/0000-0002-4749-0751>

Talat S Rahman  <https://orcid.org/0000-0003-3889-7776>

References

- [1] Tuller H L and Bishop S R 2011 Point defects in oxides: tailoring materials through defect engineering *Annu. Rev. Mater. Res.* **41** 369–98
- [2] Pacchioni G and Freund H 2013 Electron transfer at oxide surfaces. The MgO paradigm: from defects to ultrathin films *Chem. Rev.* **113** 4035–72
- [3] Wang J, Xiang M, Xu Y, Liu F, Lu T, Liu H, Zhou H, Luo G-n and Qi Q 2017 The influences of deuterium irradiation defects on mechanical properties for ceramic breeder material Li_2TiO_3 *Fusion Eng. Des.* **121** 182–7
- [4] Jupille J and Thornton G (ed) 2015 *Defects at Oxide Surfaces* vol 58 (Berlin: Springer)
- [5] Rousseau R, Glezakou V-A and Selloni A 2020 Theoretical insights into the surface physics and chemistry of redox-active oxides *Nat. Rev. Mater.* **5** 460–75
- [6] Pacchioni G 2003 Oxygen vacancy: the invisible agent on oxide surfaces *ChemPhysChem* **4** 1041–7
- [7] Buckner H B and Perry N H 2019 *In situ* optical absorption studies of point defect kinetics and thermodynamics in oxide thin films *Adv. Mater. Interfaces* **6** 1900496
- [8] Chagoya K L *et al* 2021 Mechanically enhanced catalytic reduction of carbon dioxide over defect hexagonal boron nitride *ACS Sustain. Chem. Eng.* **9** 2447–55
- [9] Ren S, Tan Q and Zhang J 2019 Review on the quantum emitters in two-dimensional materials *J. Semicond.* **40** 071903
- [10] Campbell C T and Peden C H F 2005 Oxygen vacancies and catalysis on ceria surfaces *Science* **309** 713–4
- [11] Maleki F and Pacchioni G 2021 Iso-valent doping of reducible oxides: a comparison of rutile (110) and anatase (101) TiO_2 surfaces *J. Phys.: Condens. Matter* **33** 494001
- [12] Pan X, Yang M-Q, Fu X, Zhang N and Xu Y-J 2013 Defective TiO_2 with oxygen vacancies: synthesis, properties and photocatalytic applications *Nanoscale* **5** 3601–14
- [13] Zhang X, Qin J, Xue Y, Yu P, Zhang B, Wang L and Liu R 2014 Effect of aspect ratio and surface defects on the photocatalytic activity of ZnO nanorods *Sci. Rep.* **4** 4596
- [14] Zhu K, Shi F, Zhu X and Yang W 2020 The roles of oxygen vacancies in electrocatalytic oxygen evolution reaction *Nano Energy* **73** 104761
- [15] Sood A *et al* 2021 Electrochemical ion insertion from the atomic to the device scale *Nat. Rev. Mater.* **6** 847–67
- [16] McFarland E W and Metiu H 2013 Catalysis by doped oxides *Chem. Rev.* **113** 4391–427
- [17] Sun C, Hui R and Roller J 2010 Cathode materials for solid oxide fuel cells: a review *J. Solid State Electrochem.* **14** 1125–44
- [18] Bredar A R C, Chown A L, Burton A R and Farnum B H 2020 Electrochemical impedance spectroscopy of metal oxide electrodes for energy applications *ACS Appl. Energy Mater.* **3** 66–98
- [19] Zhang Y, Tao L, Xie C, Wang D, Zou Y, Chen R, Wang Y, Jia C and Wang S 2020 Defect engineering on electrode materials for rechargeable batteries *Adv. Mater.* **32** 1905923
- [20] Kasap S, Kaya I I, Repp S and Erdem E 2019 Superbat: battery-like supercapacitor utilized by graphene foam and zinc oxide (ZnO) electrodes induced by structural defects *Nanoscale Adv.* **1** 2586–97
- [21] Lang R *et al* 2020 Single-atom catalysts based on the metal-oxide interaction *Chem. Rev.* **120** 11986–2043
- [22] Dey A 2018 Semiconductor metal oxide gas sensors: a review *Mater. Sci. Eng. B* **229** 206–17
- [23] Al-Hashem M, Akbar S and Morris P 2019 Role of oxygen vacancies in nanostructured metal-oxide gas sensors: a review *Sensors Actuators B* **301** 126845
- [24] Gao F, Zhao Y, Zhang X and You J 2020 Recent progresses on defect passivation toward efficient perovskite solar cells *Adv. Energy Mater.* **10** 1902650
- [25] Akin S, Arora N, Zakeeruddin S M, Grätzel M, Friend R H and Dar M I 2020 New strategies for defect passivation in high-efficiency perovskite solar cells *Adv. Energy Mater.* **10** 1903090
- [26] Gillet M, Lemire C, Gillet E and Aguir K 2003 The role of surface oxygen vacancies upon WO_3 conductivity *Surf. Sci.* **532–535** 519–25
- [27] Ide K, Nomura K, Hosono H and Kamiya T 2019 Electronic defects in amorphous oxide semiconductors: a review *Phys. Status Solidi a* **216** 1800372
- [28] Di Martino G *et al* 2020 Real-time *in situ* optical tracking of oxygen vacancy migration in memristors *Nat. Electron.* **3** 687–93
- [29] Liu C, Zhang C-C, Cao Y-Q, Wu D, Wang P and Li A-D 2020 Optimization of oxygen vacancy concentration in $\text{HfO}_2/\text{HfO}_x$ bilayer-structured ultrathin memristors by atomic layer deposition and their biological synaptic behavior *J. Mater. Chem. C* **8** 12478–84
- [30] Jeong J, Aetukuri N, Graf T, Schladt T D, Samant M G and Parkin S S P 2013 Suppression of metal-insulator transition in VO_2 by electric field-induced oxygen vacancy formation *Science* **339** 1402–5
- [31] Wang L *et al* 2016 Oxygen vacancy induced room-temperature metal–insulator transition in nickelate films and its potential application in photovoltaics *ACS Appl. Mater. Interfaces* **8** 9769–76

- [32] Xia C, Chen Y and Chen H 2021 Pressure-induced metal–insulator transition in oxygen-deficient LiNbO_3 -type ferroelectrics *J. Phys.: Condens. Matter* **34** 025501
- [33] Meier D and Selbach S M 2022 Ferroelectric domain walls for nanotechnology *Nat. Rev. Mater.* **7** 157–73
- [34] Li H, Guo Y and Robertson J 2015 Calculation of TiO_2 surface and subsurface oxygen vacancy by the screened exchange functional *J. Phys. Chem. C* **119** 18160–6
- [35] Sohal M K, Mahajan A, Gasso S, Nahiriak S V, Dontsova T A and Singh R C 2021 Modification of SnO_2 surface oxygen vacancies through Er doping for ultralow NO_2 detection *Mater. Res. Bull.* **133** 111051
- [36] Richter N A, Sicolo S, Levchenko S V, Sauer J and Scheffler M 2013 Concentration of vacancies at metal–oxide surfaces: case study of MgO (100) *Phys. Rev. Lett.* **111** 045502
- [37] Wei Y, Chen C, Yuan G and Gao S 2016 SnO_2 nanocrystals with abundant oxygen vacancies: preparation and room temperature NO_2 sensing *J. Alloys Compd.* **681** 43–9
- [38] Yazdani S, Kashfi-Sadabad R, Huan T D, Morales-Acosta M D and Pettes M T 2018 Polyelectrolyte-assisted oxygen vacancies: a new route to defect engineering in molybdenum oxide *Langmuir* **34** 6296–306
- [39] Cheng X, Cheng Q, Deng X, Wang P and Liu H 2016 A facile and novel strategy to synthesize reduced TiO_2 nanotubes photoelectrode for photoelectrocatalytic degradation of diclofenac *Chemosphere* **144** 888–94
- [40] Wang Y *et al* 2014 Reduced mesoporous Co_3O_4 nanowires as efficient water oxidation electrocatalysts and supercapacitor electrodes *Adv. Energy Mater.* **4** 1400696
- [41] Ruiz Puigdollers A, Schlexer P, Tosoni S and Pacchioni G 2017 Increasing oxide reducibility: the role of metal/oxide interfaces in the formation of oxygen vacancies *ACS Catal.* **7** 6493–513
- [42] Suwanwong S *et al* 2015 The dynamics of ultraviolet-induced oxygen vacancy at the surface of insulating SrTiO_3 (001) *Appl. Surf. Sci.* **355** 210–2
- [43] Wang Y, Lai X, Liu B, Chen Y, Lu Y, Wang F and Zhang L 2019 UV-induced desorption of oxygen at the TiO_2 surface for highly sensitive room temperature O_2 sensing *J. Alloys Compd.* **793** 583–9
- [44] Sterrer M, Fischbach E, Risse T and Freund H-J 2005 Geometric characterization of a singly charged oxygen vacancy on a single-crystalline MgO (001) film by electron paramagnetic resonance spectroscopy *Phys. Rev. Lett.* **94** 186101
- [45] Pang C L and Thornton G 2009 Manipulation of oxide surfaces *Surf. Sci.* **603** 3255–61
- [46] Onda K, Li B and Petek H 2004 Two-photon photoemission spectroscopy of TiO_2 (110) surfaces modified by defects and O_2 or H_2O adsorbates *Phys. Rev. B* **70** 045415
- [47] Borgersen J, Magnus Johansen K, Vines L, von Wenckstern H, Grundmann M and Kuznetsov A Y 2021 Fermi level controlled point defect balance in ion irradiated indium oxide *J. Appl. Phys.* **130** 085703
- [48] Yablinsky C A, Devanathan R, Pakarinen J, Gan J, Severin D, Trautmann C and Allen T R 2015 Characterization of swift heavy ion irradiation damage in ceria *J. Mater. Res.* **30** 1473–84
- [49] Saini C P *et al* 2017 Impact of self-trapped excitons on blue photoluminescence in TiO_2 nanorods on chemically etched Si pyramids *J. Phys. Chem. C* **121** 11448–54
- [50] Zhou X, Liu N and Schmuki P 2014 Ar^+ -ion bombardment of TiO_2 nanotubes creates co-catalytic effect for photocatalytic open circuit hydrogen evolution *Electrochem. Commun.* **49** 60–4
- [51] Cagnetta G, Huang J, Lu M, Wang B, Wang Y, Deng S and Yu G 2017 Defect engineered oxides for enhanced mechanochemical destruction of halogenated organic pollutants *Chemosphere* **184** 879–83
- [52] Li R, Wang J, He Y, Dong F, Bian L and Li B 2019 Mechanochemical synthesis of defective molybdenum trioxide, titanium dioxide, and zinc oxide at room temperature *ACS Sustain. Chem. Eng.* **7** 11985–9
- [53] Jiang N 2015 Electron beam damage in oxides: a review *Rep. Prog. Phys.* **79** 016501
- [54] Setvín M, Wagner M, Schmid M, Parkinson G S and Diebold U 2017 Surface point defects on bulk oxides: atomically-resolved scanning probe microscopy *Chem. Soc. Rev.* **46** 1772–84
- [55] Zhang Q, Wen H F, Adachi Y, Miyazaki M, Sugawara Y, Xu R, Cheng Z H and Li Y J 2019 Electrical engineering of the oxygen adatom and vacancy on rutile TiO_2 (110) by atomic force microscopy at 78 K *J. Phys. Chem. C* **123** 28852–8
- [56] Watkins M B and Shluger A L 2006 Manipulation of defects on oxide surfaces via barrier reduction induced by atomic force microscope tips *Phys. Rev. B* **73** 245435
- [57] Paier J, Penshke C and Sauer J 2013 Oxygen defects and surface chemistry of ceria: quantum chemical studies compared to experiment *Chem. Rev.* **113** 3949–85
- [58] Sarkar A and Khan G G 2019 The formation and detection techniques of oxygen vacancies in titanium oxide-based nanostructures *Nanoscale* **11** 3414–44
- [59] Yoshida K, Kawai T, Nambara T, Tanemura S, Saitoh K and Tanaka N 2006 Direct observation of oxygen atoms in rutile titanium dioxide by spherical aberration corrected high-resolution transmission electron microscopy *Nanotechnology* **17** 3944
- [60] Lawrence N J *et al* 2011 Defect engineering in cubic cerium oxide nanostructures for catalytic oxidation *Nano Lett.* **11** 2666–71
- [61] Yang R, Ren C, Teng X, Chen Z, Wu S and Zhang W 2017 Study of the surface oxygen vacancies involvement on the single and Bi-components manganese oxide precursors and their catalytic performance *Catal. Lett.* **147** 727–37
- [62] Muller D A 2009 Structure and bonding at the atomic scale by scanning transmission electron microscopy *Nat. Mater.* **8** 263–70
- [63] Han Z K, Yang Y Z, Zhu B, Ganduglia-Pirovano M V and Gao Y 2018 Unraveling the oxygen vacancy structures at the reduced CeO_2 (111) surface *Phys. Rev. Mater.* **2** 035802
- [64] König T, Simon G H, Martinez U, Giordano L, Pacchioni G, Heyde M and Freund H-J 2010 Direct measurement of the attractive interaction forces on F^0 color centers on MgO (001) by dynamic force microscopy *ACS Nano* **4** 2510–4
- [65] Sterrer M, Heyde M, Novicki M, Nilius N, Risse T, Rust H-P, Pacchioni G and Freund H-J 2006 Identification of color centers on MgO (001) thin films with scanning tunneling microscopy *J. Phys. Chem. B* **110** 46–9
- [66] Guo M, Lu J, Wu Y, Wang Y and Luo M 2011 UV and visible Raman studies of oxygen vacancies in rare-earth-doped ceria *Langmuir* **27** 3872–7
- [67] Ricci D, Di Valentin C, Pacchioni G, Sushko P V, Shluger A L and Giamello E 2003 Paramagnetic defect centers at the MgO surface. An alternative model to oxygen vacancies *J. Am. Chem. Soc.* **125** 738–47
- [68] Knorr F J, Zhang D and McHale J L 2007 Influence of TiCl_4 treatment on surface defect photoluminescence in pure and mixed-phase nanocrystalline TiO_2 *Langmuir* **23** 8686–90

- [69] Cerrato E, Paganini M C and Giamello E 2020 Photoactivity under visible light of defective ZnO investigated by EPR spectroscopy and photoluminescence *J. Photochem. Photobiol. A* **397** 112531
- [70] Siedl N, Gügel P and Diwald O 2013 First combined electron paramagnetic resonance and FT-IR spectroscopic evidence for reversible O₂ adsorption on In₂O_{3-x} nanoparticles *J. Phys. Chem. C* **117** 20722–9
- [71] Wang M, Shen M, Jin X, Tian J, Zhou Y, Shao Y, Zhang L, Li Y and Shi J 2020 Mild generation of surface oxygen vacancies on CeO₂ for improved CO₂ photoreduction activity *Nanoscale* **12** 12374–82
- [72] Xu M, Noei H, Fink K, Muhler M, Wang Y and Wöll C 2012 The surface science approach for understanding reactions on oxide powders: the importance of IR spectroscopy *Angew. Chem., Int. Ed.* **51** 4731–4
- [73] Li X, Paier J, Sauer J, Mirabella F, Zaki E, Ivars-Barceló F, Shaikhutdinov S and Freund H-J 2018 Surface termination of Fe₃O₄ (111) films studied by CO adsorption revisited *J. Phys. Chem. B* **122** 527–33
- [74] Wu Z, Li M, Howe J, Meyer H M III and Overbury S H 2010 Probing defect sites on CeO₂ nanocrystals with well-defined surface planes by Raman spectroscopy and O₂ adsorption *Langmuir* **26** 16595–606
- [75] Wachs I E and Roberts C A 2010 Monitoring surface metal oxide catalytic active sites with Raman spectroscopy *Chem. Soc. Rev.* **39** 5002–17
- [76] Glass D *et al* 2019 Dynamics of photo-induced surface oxygen vacancies in metal-oxide semiconductors studied under ambient conditions *Adv. Sci.* **6** 1901841
- [77] Choi M, Ibrahim I A M, Kim K, Koo J Y, Kim S J, Son J-W, Han J W and Lee W 2020 Engineering of charged defects at perovskite oxide surfaces for exceptionally stable solid oxide fuel cell electrodes *ACS Appl. Mater. Interfaces* **12** 21494–504
- [78] Bart F, Gautier M, Jollet F and Duraud J P 1994 Electronic structure of the (0001) and (1010) quartz surfaces and of their defects as observed by reflection electron energy loss spectroscopy (REELS) *Surf. Sci.* **306** 342–58
- [79] Ibach H and Mills D L 2013 *Electron Energy Loss Spectroscopy and Surface Vibrations* (New York: Academic)
- [80] Astašauskas V, Bellissimo A, Kuksa P, Tomastik C, Kalbe H and Werner W S 2020 Optical and electronic properties of amorphous silicon dioxide by single and double electron spectroscopy *J. Electron Spectrosc. Relat. Phenom.* **241** 146829
- [81] Liu Y, Wu Z, Kühlenbeck H and Freund H J 2021 Surface action spectroscopy: a review and a perspective on a new technique to study vibrations at surfaces *Chem. Rec.* **21** 1270–83
- [82] Anpo M, Costentin G, Giamello E, Lauron-Pernot H and Sojka Z 2021 Characterisation and reactivity of oxygen species at the surface of metal oxides *J. Catal.* **393** 259–80
- [83] Chiesa M, Paganini M C, Giamello E, Murphy D M, Di Valentin C and Pacchioni G 2006 Excess electrons stabilized on ionic oxide surfaces *Acc. Chem. Res.* **39** 861–7
- [84] Yu K, Lou L L, Liu S and Zhou W 2020 Asymmetric oxygen vacancies: the intrinsic redox active sites in metal oxide catalysts *Adv. Sci.* **7** 1901970
- [85] Peng Y-K, Fu Y, Zhang L, Teixeira I F, Ye L, He H and Tsang S C E 2017 Probe-molecule-assisted NMR spectroscopy: a comparison with photoluminescence and electron paramagnetic resonance spectroscopy as a characterization tool in facet-specific photocatalysis *ChemCatChem* **9** 155–60
- [86] Luo Y, Zheng Y, Feng X, Lin D, Qian Q, Wang X, Zhang Y, Chen Q and Zhang X 2020 Controllable P doping of the LaCoO₃ catalyst for efficient propane oxidation: optimized surface Co distribution and enhanced oxygen vacancies *ACS Appl. Mater. Interfaces* **12** 23789–99
- [87] Zhao J, Liu C, Li J, Wu R, Wang J, Qian H, Guo H, Li J and Ibrahim K 2019 Oxygen vacancy induced electronic structure variation in the La_{0.2}Sr_{0.8}MnO₃ thin film *AIP Adv.* **9** 055208
- [88] Xiao Z *et al* 2020 Operando identification of the dynamic behavior of oxygen vacancy-rich Co₃O₄ for oxygen evolution reaction *J. Am. Chem. Soc.* **142** 12087–95
- [89] Yim C M, Pang C L and Thornton G 2010 Oxygen vacancy origin of the surface band-gap state of TiO₂ (110) *Phys. Rev. Lett.* **104** 036806
- [90] Krüger P *et al* 2008 Defect states at the TiO₂ (110) surface probed by resonant photoelectron diffraction *Phys. Rev. Lett.* **100** 055501
- [91] Jiang X, Zhang Y, Jiang J, Rong Y, Wang Y, Wu Y and Pan C 2012 Characterization of oxygen vacancy associates within hydrogenated TiO₂: a positron annihilation study *J. Phys. Chem. C* **116** 22619–24
- [92] Siemek K, Olejniczak A, Korotkov L N, Konieczny P and Belushkin A V 2022 Investigation of surface defects in BaTiO₃ nanopowders studied by XPS and positron annihilation lifetime spectroscopy *Appl. Surf. Sci.* **578** 151807
- [93] Wendt S, Kim Y D and Goodman D W 2003 Identification of defect sites on oxide surfaces by metastable impact electron spectroscopy *Prog. Surf. Sci.* **74** 141–59
- [94] Borodin A and Reichling M 2011 Characterizing TiO₂ (110) surface states by their work function *Phys. Chem. Chem. Phys.* **13** 15442–7
- [95] Chen Y, Fong D D, Herbert F W, Rault J, Rueff J-P, Tsvetkov N and Yildiz B 2018 Modified oxygen defect chemistry at transition metal oxide heterostructures probed by hard x-ray photoelectron spectroscopy and x-ray diffraction *Chem. Mater.* **30** 3359–71
- [96] Fell C R, Qian D, Carroll K J, Chi M, Jones J L and Meng Y S 2013 Correlation between oxygen vacancy, microstrain, and cation distribution in lithium-excess layered oxides during the first electrochemical cycle *Chem. Mater.* **25** 1621–9
- [97] Luo S, Li M, Fung V, Sumpter B G, Liu J, Wu Z and Page K 2021 New insights into the bulk and surface defect structures of ceria nanocrystals from neutron scattering study *Chem. Mater.* **33** 3959–70
- [98] Traeger F 2006 Helium atom scattering from oxide surfaces *ChemPhysChem* **7** 1006–13
- [99] Younis A, Shirsath S E, Shabbir B and Li S 2018 Controllable dynamics of oxygen vacancies through extrinsic doping for superior catalytic activities *Nanoscale* **10** 18576–85
- [100] Guo F *et al* 2019 Evidence for the dynamic relaxation behavior of oxygen vacancies in Aurivillius Bi₂MoO₆ from dielectric spectroscopy during resistance switching *J. Mater. Chem. C* **7** 8915–22
- [101] Munde M S, Gao D Z and Shluger A L 2017 Diffusion and aggregation of oxygen vacancies in amorphous silica *J. Phys.: Condens. Matter* **29** 245701
- [102] Jang J H *et al* 2017 *In situ* observation of oxygen vacancy dynamics and ordering in the epitaxial LaCoO₃ system *ACS Nano* **11** 6942–9
- [103] Pacchioni G 2008 Modeling doped and defective oxides in catalysis with density functional theory methods: room for improvements *J. Chem. Phys.* **128** 182505

- [104] Logsdail A J, Downing C A, Keal T W, Sherwood P, Sokol A A and Catlow C R A 2018 Hybrid-DFT modeling of lattice and surface vacancies in MnO *J. Phys. Chem. C* **123** 8133–44
- [105] Mitra A, Pham H Q, Pandharkar R, Hermes M R and Gagliardi L 2021 Excited states of crystalline point defects with multireference density matrix embedding theory *J. Phys. Chem. Lett.* **12** 11688–94
- [106] Ganduglia-Pirovano M V, Hofmann A and Sauer J 2007 Oxygen vacancies in transition metal and rare earth oxides: current state of understanding and remaining challenges *Surf. Sci. Rep.* **62** 219–70
- [107] Ganduglia-Pirovano M V 2015 Oxygen defects at reducible oxide surfaces: the example of ceria and vanadia *Defects at Oxide Surfaces (Springer Series in Surface Sciences vol 58)* ed J Jupille and G Thornton (Berlin: Springer)
- [108] Schäfer T, Daelman N and López N 2021 Cerium oxides without U : the role of many-electron correlation *J. Phys. Chem. Lett.* **12** 6277–83
- [109] Galicia-Hernandez J M, Turkowski V, Hernandez-Cocoletzi G and Rahman T S 2020 Electron correlations and memory effects in ultrafast electron and hole dynamics in VO₂ *J. Phys.: Condens. Matter* **32** 20LT01