



A: Poly(acrylonitrile-co-*N*-vinyl-2-pyrrolidone)




$M_n = 1.8 \times 10^5$ g/mol
 $\bar{D} = 1.668$

B: Poly(butyl acrylate-co-vinyl acetate)



$M_n = 8.5 \times 10^4$ g/mol
 $\bar{D} = 1.186$

C: Poly(acrylonitrile-co-ethyl methacrylate)



$M_n = 6.1 \times 10^4$ g/mol
 $\bar{D} = 1.657$