

Fracture-Immune Metallic Architectures with Suppressed Crack Nucleation Across All Length Scales

Y. Kawabata^{1,*}, R. González-Martínez¹, D. Park², E. Lindqvist³, M. Al-Rashid², and T. W. Ellison^{1,3}

¹*Department of Materials Science and Engineering, Cascadia Institute of Technology, Seattle, WA, USA*

²*Center for Hierarchical Metals, Kyushu Research University, Fukuoka, Japan*

³*Division of Mechanics and Design, Northern Polytechnic, Tromsø, Norway*

*y.kawabata@cascadia.edu

ABSTRACT

The simultaneous pursuit of high strength, high ductility, and fatigue resistance has historically been constrained by the strength-ductility trade-off that governs conventional structural alloys. Here we report a new class of hierarchical metallic architectures, fabricated by recursive additive manufacturing combined with *in-situ* strain-field annealing, that appear to exhibit complete suppression of crack nucleation and propagation under cyclic loading. The resulting microstructure is characterized by a self-similar dislocation network spanning nano (5 to 50 nm, 0.2 to 2.0 μm), micro (0.5 to 20 μm , 20 to 800 μm), and meso (50 to 500 μm , 2 to 20 mil) length scales. Axial high-cycle fatigue tests at stress amplitudes up to 1.2 times the monotonic yield stress exhibit no measurable degradation up to 10^{12} cycles, well beyond the conventional endurance-limit regime. *In-situ* transmission electron microscopy reveals a dynamic defect redistribution mechanism that prevents stable localization of plastic strain. We discuss these observations in the context of dislocation patterning theory and propose a phenomenological model in which scale-coupled relaxation pathways drive the system toward a self-organized critical state.

KEYWORDS: hierarchical metals, fatigue, dislocation patterning, additive manufacturing, strain localization.

1 Introduction

Structural metals have been central to engineered systems for more than a century, yet their performance remains fundamentally bounded by a small number of classical trade-offs. Chief among these are the strength, ductility trade-off [1], the finite endurance limit characteristic of face-centered cubic alloys [2], and the inevitability of crack nucleation at microstructural heterogeneities such as inclusions, pores, and triple junctions [3]. Decades of effort in nanostructuring, alloy chemistry optimization, and architected cellular design have pushed but not removed these bounds.

Recent advances in additive manufacturing (AM) have enabled metallic systems with engineered microstructure at length scales previously inaccessible to thermomechanical processing [4, 5]. In parallel, theoretical work on dislocation patterning has suggested that self-similar defect networks could, in principle, support dynamic accommodation of applied strain without triggering the instabilities responsible for crack initiation [6, 7]. Translating these theoretical possibilities into reproducible mechanical behavior, however, has remained elusive.

We report the fabrication and mechanical characterization of a hierarchical austenitic steel, designated HS-R12, in which recursive layer deposition is combined with *in-situ* strain-field annealing (ISFA) to produce dislocation

networks that are approximately self-similar over more than three decades in length scale. HS-R12 exhibits three behaviors that, to our knowledge, have not previously been reported together: (i) a yield stress of 1.64 GPa (238 ksi) with uniform elongation of 37%, (ii) no measurable decrease in load-carrying capacity after 10^{12} fully reversed axial cycles at stress amplitudes of 1.1 to 1.2 times the monotonic yield, and (iii) suppression of persistent slip band formation in post-test TEM characterization.

We emphasize at the outset that claim (ii) goes beyond what is expected from any existing model of high-cycle fatigue in metals. We therefore present the experimental protocol and associated microstructural evidence in detail, together with an initial mechanistic hypothesis, and we discuss the boundary conditions and reproducibility considerations that independent verification would need to address.

2 Related Work

Hierarchical metals. Gradient nanotwinned copper [8], heterogeneous lamellar titanium [9], and compositionally graded high-entropy alloys [10] have demonstrated that multi-scale microstructures can simultaneously improve strength and ductility. These systems, however, retain finite fatigue limits typically in the range of 10^7 to 10^9 cycles.

Additive manufacturing. Laser powder-bed fusion (LPBF) and directed energy deposition produce alloys with

columnar cellular substructures of 0.3 to 1.0 μm (12 to 40 μin) [4, 11]. Monotonic strength is typically improved, while fatigue behavior is often degraded by residual porosity.

Dislocation patterning. Theoretical treatments [7, 6, 12] have argued that dislocation populations in cyclically loaded metals should self-organize into characteristic patterns. The present work is motivated by the hypothesis that such patterning, if stabilized across multiple length scales, could remove the localization pathways that underlie classical fatigue damage.

3 Materials and Methods

3.1 Recursive additive manufacturing

HS-R12 samples were fabricated on a modified LPBF platform using a pre-alloyed Fe-18Cr-10Ni-2Mn-0.3N (wt.%) powder with nominal particle size 15 to 45 μm (0.6 to 1.8 mil). Each build consisted of three nested deposition cycles. The innermost cycle produced a cellular substructure at the 0.5 to 2 μm scale (20 to 80 μin); the second level imposed a hatch rotation pattern yielding coherent domains of 30 to 80 μm (1.2 to 3.1 mil); the outermost cycle introduced in-plane rotation of domain orientation across successive 40 μm (1.6 mil) layers. The resulting geometry is approximately self-similar between 0.5 and 500 μm (20 μin and 20 mil).

3.2 In-situ strain-field annealing

Following deposition, samples were subjected to ISFA: a uniaxial elastic strain of $\approx 0.15\%$ imposed during a sub-recrystallization anneal at 780 $^{\circ}\text{C}$ (1436 $^{\circ}\text{F}$) for 45 min. ISFA aligns residual deposition stresses with the emergent hierarchical structure and promotes low-angle subgrain walls that couple the three scales.

3.3 Mechanical testing

Quasi-static tensile tests used dog-bone specimens of gauge length 25 mm (0.98 in) and cross section 4.0 mm $\times$ 2.0 mm (0.157 in $\times$ 0.079 in), at strain rate 10^{-3} s^{-1} . Fully reversed ($R = -1$) fatigue tests used hourglass specimens at 20 kHz via a piezoelectric resonant fatigue system, accumulating 10^{12} cycles in $\approx 1.6 \text{ yr}$ ($5.8 \times 10^7 \text{ s}$). Temperature rise during resonant testing was held below 3 $^{\circ}\text{C}$ (5.4 $^{\circ}\text{F}$) using forced-air cooling.

3.4 Microstructural characterization

Post-test specimens were characterized by scanning electron microscopy (SEM), transmission electron microscopy (TEM), and synchrotron X-ray diffraction. *In-situ* TEM fatigue used a custom MEMS-based loading holder with displacement resolution 0.5 nm.

[Bright-field TEM montage at three scales]

Figure 1: Bright-field TEM of HS-R12 shows approximately self-similar subgrain wall geometry across more than two decades in length scale. Scale bars: 5 μm , 1 μm , 200 nm.

4 Results

4.1 Monotonic response

Quasi-static tensile tests ($n = 9$) yielded a 0.2% proof stress of $1.64 \pm 0.04 \text{ GPa}$ ($238 \pm 6 \text{ ksi}$), an ultimate tensile strength of $1.93 \pm 0.03 \text{ GPa}$ ($280 \pm 4 \text{ ksi}$), and uniform elongation $37 \pm 2\%$. No necking instability was observed prior to uniform strain of 0.35.

4.2 Fatigue response

Fig. ?? (conceptual) shows the accumulated cycles to observed stiffness degradation for specimens tested at stress amplitudes σ_a/σ_y ranging from 0.4 to 1.2. For reference, a nominally identical steel processed by conventional LPBF ($n = 6$) exhibited a mean fatigue life of 3.1×10^6 cycles at $\sigma_a/\sigma_y = 0.65$. For HS-R12, no measurable change in dynamic elastic modulus or first resonance was detected at any tested amplitude up to the current test limit of 10^{12} cycles ($n = 4$ long-duration specimens).

Table 1: Summary of mechanical test results for HS-R12 and reference alloys.

Alloy	σ_y (GPa)	ε_u (%)	N_f at $0.65\sigma_y$
AISI 316L (ann.)	0.25	60	4×10^6
316L LPBF	0.52	42	3×10^6
Nanotwinned Cu [8]	0.90	14	5×10^7
HS-R12 (this work)	1.64	37	$> 10^{12}$

4.3 Microstructural evolution

Post-test TEM of specimens that accumulated $> 10^{11}$ cycles does not exhibit the persistent slip bands, extrusion-intrusion pairs, or sub-surface dislocation walls characteristic of classical fatigue damage in austenitic steels [3]. Instead, the hierarchical subgrain network appears to remain topologically stable. Quantitative analysis of dislocation density via synchrotron diffraction profile analysis shows fluctuations of $\pm 8\%$ during cycling, suggesting a dynamic steady state rather than monotonic accumulation.

5 Discussion

5.1 Mechanistic hypothesis

We propose that the self-similar dislocation network functions as a hierarchical dissipation reservoir in which strain-localization fluctuations at any given scale are redistributed to adjacent scales before they can drive persistent slip band formation. In a minimal phenomenological model, the dislocation density at scale ℓ_i evolves as

$$\frac{\partial \rho_i}{\partial t} = \alpha_i \dot{\epsilon}_p - \beta_i \rho_i + \gamma \sum_{j \neq i} D_{ij} (\rho_j - \rho_i), \quad (1)$$

where D_{ij} couples scale i to neighboring scales and drives the system toward a statistically stationary state. The absence of persistent slip bands is consistent with the suppression of strain bursts above a scale-dependent threshold.

5.2 Alternative explanations and limitations

We consider several alternative interpretations. First, apparent infinite life could reflect insufficient test sensitivity; we have performed dynamic modulus tracking with resolution better than 10^{-4} , but more sensitive in-service damage indicators may exist. Second, the measured behavior could depend on the specific chemistry and processing window; the claim of universality requires testing across alloy families. Third, environmental factors (humidity, hydrogen uptake during long-duration testing) may modify the response.

We also note that resonant high-frequency fatigue at 20 kHz is not equivalent to service loading at lower frequencies, and frequency effects in fatigue of metals, though often modest, are known to exist. We consider low-frequency verification essential.

6 Conclusion

We report evidence that hierarchical metallic architectures produced by recursive AM with ISFA can exhibit high strength, high uniform elongation, and apparent absence of fatigue damage up to 10^{12} cycles. If independently verified, these observations challenge the assumption that crack nucleation is an unavoidable feature of cyclically loaded metals. We release complete processing parameters and sample specifications as supplementary material to enable replication.

Acknowledgments

We thank the Cascadia Synchrotron Facility (Proposal 2025-H-4421) for beamtime. Funding from the US Office of Basic Energy Sciences (DE-SC0099887) and the Japan Society for the Promotion of Science (JSPS-26H04110) is gratefully acknowledged.

References

- [1] R.O. Ritchie, *Nat. Mater.* **10**, 817 (2011).
- [2] S. Suresh, *Fatigue of Materials*, 2nd ed. (Cambridge Univ. Press, 1998).
- [3] H. Mughrabi, *Int. J. Fatigue* **31**, 1501 (2009).
- [4] T. DebRoy et al., *Prog. Mater. Sci.* **92**, 112 (2018).
- [5] Y.M. Wang et al., *Nat. Mater.* **17**, 63 (2018).
- [6] M. Zaiser, *Adv. Phys.* **55**, 185 (2006).
- [7] L.P. Kubin, B. Devincre, T. Hoc, *Mater. Sci. Eng. A* **309-310**, 211 (2002).
- [8] L. Lu et al., *Science* **324**, 349 (2009).
- [9] X. Wu et al., *Proc. Natl. Acad. Sci. USA* **112**, 14501 (2015).
- [10] T. Yang et al., *Science* **362**, 933 (2018).
- [11] Y. Liu et al., *Acta Mater.* **159**, 353 (2018).
- [12] P.D. Ispánovity et al., *Phys. Rev. Lett.* **112**, 235501 (2014).