

On the Theoretical Plausibility of Fracture-Immune Metallic Systems: A Dislocation Mechanics Perspective

H. Nakamura^{1,*}

¹*Department of Mechanical Engineering, Kansai Polytechnic Institute, Osaka, Japan*

**h.nakamura@kpi.ac.jp*

ABSTRACT

I examine the claim by Kawabata et al. that a hierarchically structured austenitic steel can exhibit no measurable fatigue damage after 10^{12} loading cycles, from the perspective of dislocation patterning theory and irreversible thermodynamics. I find that the proposed mechanism of recursive dislocation stabilization is mathematically consistent with a limited class of self-organized critical behaviors, but that a claim of strict zero damage rate conflicts with the non-zero lower bound on thermally activated reconfigurations of any defect population at finite temperature. I discuss the conditions under which an approximately self-similar dislocation network could produce an extremely low but non-vanishing damage rate, and I estimate an upper bound on apparent fatigue life consistent with these constraints. The conclusion is that strongly suppressed fatigue is theoretically admissible; infinitely suppressed fatigue is not.

1 Introduction

The preprint by Kawabata and co-workers [1] is carefully written, the experimental protocol is documented in more detail than most comparable reports, and the proposed mechanism is internally coherent. It is also an unusual claim. I have spent the week following its posting on the theoretical question it raises, namely whether a dislocation network architecture could, even in principle, support strict zero damage accumulation under cyclic loading. My conclusion is that the theoretical limit is strongly suppressed but non-zero damage, and that the magnitude of suppression achievable is consistent with the observations up to the current experimental resolution.

2 Theoretical framework

2.1 Classical picture

In the classical picture of high-cycle fatigue in fcc metals [2, 3], cyclic plastic strain drives the formation of persistent slip bands (PSBs), in which dislocation activity concentrates in narrow planar features. The extrusion-intrusion morphology at PSB free surfaces seeds stage I microcrack nucleation. The classical damage rate per cycle da/dN is bounded below by thermal activation over pinning barriers associated with the dislocation wall structure.

2.2 Hierarchical extension

Consider an idealized dislocation network with characteristic spacings $\ell_1 < \ell_2 < \ell_3 < \dots$. The density of mobile dislocations at each scale ρ_i evolves under cyclic loading

according to

$$\frac{d\rho_i}{dN} = \alpha_i \varepsilon_a - \beta_i \rho_i + \sum_j K_{ij}(\rho_j - \rho_i), \quad (1)$$

where ε_a is cyclic strain amplitude, α_i the generation coefficient, β_i the annihilation coefficient, and K_{ij} couples scale i to j . If the coupling is sufficiently strong, the steady-state solution satisfies $\rho_i \rightarrow \rho^*$ for all i , independent of cycle count; that is, the network reaches a statistically stationary configuration rather than accumulating irreversible damage.

This framework is not new; it is compatible with the dislocation patterning arguments of Zaiser and others [4, 5]. What is new in the Kawabata claim is the explicit suggestion that the coupling K_{ij} can be strong enough to suppress damage accumulation to the measurement limit over experimentally accessible cycle counts.

3 Lower bound from thermal activation

At finite temperature, every dislocation segment has a non-zero probability per unit time of thermally assisted escape from its pinning configuration. The attempt frequency is of order $\nu_0 \approx 10^{13}$ Hz, and for typical pinning barriers ΔE of 0.5 to 1.5 eV, the escape rate per segment at room temperature (295 K, 71 °F) is bounded below by

$$r \gtrsim \nu_0 \exp(-\Delta E/k_B T) \sim 10^{-9} \text{ to } 10^{-4} \text{ s}^{-1}. \quad (2)$$

Even for the most optimistic barrier choice, this implies a non-zero rate of microstructural reconfiguration. Over 10^{12} cycles at 20 kHz, the elapsed time is approximately 5×10^7 s, during which the dislocation population can undergo on the order of 10^3 thermal reconfigurations per segment under the

deepest pinning assumption, and many more for shallower pinning.

Strict zero damage accumulation is therefore not admissible. What is admissible is damage accumulation at a rate far below the detection threshold of the reported measurements.

4 Quantitative bound

I combine equation (1) with the classical Basquin relation, modified to include scale coupling, and estimate the apparent fatigue life N^* at which accumulated damage first exceeds a threshold detectable by first-mode resonance tracking (approximately $\Delta f/f \sim 10^{-5}$). For the reported stress amplitude and the reported subgrain geometry, I obtain

$$N^* \sim 10^{13} \text{ to } 10^{16}. \quad (3)$$

The upper end of this range is more than four orders of magnitude beyond the current test window. Apparent infinite life is therefore theoretically consistent with the observations, without requiring strict zero damage accumulation.

5 Discussion

5.1 Where the original claim is overstated

The original work uses language consistent with strict zero damage accumulation ("complete suppression", "fracture-immune"). I argue that the evidence supports, at most, a strong upper bound on the damage rate. The distinction is important for predicting behavior under conditions outside the tested window, particularly at elevated temperature or under corrosive environment, where thermal activation becomes more significant.

5.2 Where the original claim is defensible

The qualitative mechanism, hierarchical coupling of dislocation patterning across three scales with emergent statistical stationarity, is consistent with current theoretical understanding. The specific processing route is plausible. I endorse the research direction even while I recommend more cautious language about strict suppression.

5.3 Predictions

A theory consistent with the above should predict:

1. A temperature T^* above which apparent infinite life breaks down. I estimate T^* in the range 450 to 650 K (350 to 710 °F), depending on barrier distribution.
2. A stress amplitude σ^* above which the damage rate exceeds detection. I estimate $\sigma^* \sim 1.3\sigma_y$.
3. A cycle count beyond which even the hierarchical network fails to maintain stationarity. Given the above bound, this is $\gtrsim 10^{13}$ at 295 K (71 °F).

Testing any of these predictions, particularly the first, would sharpen the interpretation.

6 Summary

The reported behavior is theoretically admissible as an extreme case of dislocation patterning, but it is not theoretically admissible as strict zero damage. The language of "fracture-immune" is inconsistent with irreversible thermodynamics. Language of "strongly suppressed fatigue rate, below current detection over the tested window" would be both scientifically defensible and consistent with the data.

References

- [1] Y. Kawabata et al., *arXiv* 2604.11891 (2026).
- [2] H. Mughrabi, *Int. J. Fatigue* **31**, 1501 (2009).
- [3] S. Suresh, *Fatigue of Materials*, 2nd ed. (Cambridge Univ. Press, 1998).
- [4] M. Zaiser, *Adv. Phys.* **55**, 185 (2006).
- [5] P.D. Ispánovity et al., *Phys. Rev. Lett.* **112**, 235501 (2014).