Polymeric Chemistry
DSC and TGA

Universität Stuttgart

Author 1:	Laurens Viehoff
Author 2:	Felix Roth
E-Mail 1:	st183688@stud.uni-stuttgart.de
E-Mail 2:	st188157@stud.uni-stuttgart.de
Student ID 1:	3676761
Student-ID 2:	3711192

Assistentin:

Abstract

Inhaltsverzeichnis

1 Theory Part **2**

1.1 DSC 2

1.1.1 Glass transition temperature (T_g) and meltingtemperature (T_m) 2

2 Results **2**

3 Questions **3**

3.1 Question 1 3

3.2 Question 2 3

3.3 Question 3 3

3.4 Question 4 3

3.5 Question 5 3

3.6 Question 6 4

3.7 Question 7 4

3.8 Question 8 4

1 Theory Part

1.1 DSC

The DSC (Differential Scanning Calorimetry) uses the principle of the isotherm calorimetry. The Sample and a references get heated in two separate crucibles. The absorbed energy is measured, and in case of different absorption the one with less gets more power while this added power is being measured and plotted against time (t). The Integral of dW/dt is the difference between the sample and the reference, also shown in picture (1) is the Integral underneath the curve which defines the smelting enthalpy which is calculated by using equation (1). This curve is influenced by the spectrum of lengths the polymer provides, meaning if the polymer has many chains with different lengths the peak gets wider to the right. The reference is always a known Sample or something, the heat capacity is known. In our case the reference was the empty crucible.

$$\Delta H_m = \Delta H_{Sample} - \Delta H_{Reference} \tag{1}$$



Abb. 1: This picture shows the thermogram of a Polymer, the differential signal in [mV] is plotted against time in [s]. xxx

1.1.1 Glass transition temperature (T_g) and meltingtemperature (T_m)

The Glass transition temperature is the temperature range where a complete coupled segment movement of chains (10-15 chain links) is possible. These chains were frozen before that temperature and can only be defined if the polymer is amorphous. This can also be seen in a change of the heat capacity.

The smelting temperature is only present in semi crystalline polymers. These have a lamellar structure

2 Results

Two different samples were prepared, and analyzed, using DSC and TGA. The Data of the samples (PET and it-PS) are listed in the Table below 1

Tab. 1: These are the meltingtemperatures(T_m), glastemperatures(T_g) and the meltingenthalpie (Δ H$_m$)

Sample	Δ H$_m$	T$_m$	T$_g$
PE			
it-PS	-		

3 Questions

3.1 Question 1

The "Big"number indicates how many monomers are needed to make one full 360° rotation. The small number in the index says how many 360° rotations are needed until the order gets repeated. For example in the case of 8_5 Polybutene. It needs 8 monomers to complete one 360° rotation and 5 full rotation until the order starts from the start.

3.2 Question 2

i-PP can be made by using the Ziegler-Natta-catalysis. In this case catalysts like $TiCl_3$ on $MgCl_2$-carrier are used in combination with aluminumalkenes. It can also be done via Metallocene-catalysis, this technique is specially used to control the tacticity and results in high graded i-PP. i-PS can also be synthesized using the Metallocene-catalysis. But can also be synthesized via Anionic-Polymerization.

3.3 Question 3

Commonly the degree of crystallization decides how stiff a polymer is. The higher the degree of crystallization, the harder and stiffer the polymer. It also gets less ductile and more dense because crystalline parts can be packed better than amorphous parts.

3.4 Question 4

The Polymer is divided in different sections a back folding section(black), which would be the PS in our case and a amorphous section(red), which in our case would be the PE sections.



Abb. 2: The picture shows the part-.crystalline

3.5 Question 5

To get an semi-crystalline polymer out of an polymerglass it has to be reheated. By reheating the polymer the molecular mobility gets high enough to form crystals. This process is also known

as cold crystallization.

3.6 Question 6

The increase in mass can be explained by oxidation. While increasing the temperature in the TGA the polymer oxidizes, the added Oxygen increases the mass of the polymer (molecule if the polymer gets destroyed).

3.7 Question 7

3.8 Question 8

Due to the residual moisture, the PET decomposes to Ethylenglycol and Terephthalic acid. The Ethylenglycol eliminates water which results in vinylalcohol, which can tautomerize to Ethanal.

Filename:	C:\Users\DSC\Desktop\MD\G...\G8-pet-tga.t6d
Operator ID:	MD
Sample ID:	G8-PET
Sample Weight:	3.597 mg
Comment:	



10.03.2026 10:42:27

1) Heat from 30.00℃ to 600.00℃ at 20.00℃/min

Filename:	C:\Users\DSC\Desktop\MD\G...\ps-iso-dsc.d6d
Operator ID:	MD
Sample ID:	G8-ps-iso
Sample Weight:	5.418 mg
Comment:	



10.03.2026 11:26:12

1) Heat from 30.00°C to 300.00°C at 20.00°C/min
2) Cool from 300.00°C to 30.00°C at 20.00°C/min
3) Heat from 30.00°C to 300.00°C at 20.00°C/min

Filename:	C:\Users\DSC\Desktop\MD\G...\ps-iso-dsc.d6d
Operator ID:	MD
Sample ID:	G8-ps-iso
Sample Weight:	5.418 mg
Comment:	



10.03.2026 11:25:16

1) Heat from 30.00℃ to 300.00℃ at 20.00℃/min
2) Cool from 300.00℃ to 30.00℃ at 20.00℃/min
3) Heat from 30.00℃ to 300.00℃ at 20.00℃/min

Filename:	C:\Users\DSC\Desktop\MD\G...\ps-iso-dsc.d6d
Operator ID:	MD
Sample ID:	G8-ps-iso
Sample Weight:	5.418 mg
Comment:	



10.03.2026 11:27:53

1) Heat from 30.00℃ to 300.00℃ at 20.00℃/min
2) Cool from 300.00℃ to 30.00℃ at 20.00℃/min
3) Heat from 30.00℃ to 300.00℃ at 20.00℃/min

Filename:	C:\Users\DSC\Desktop\MD\G8\pet-dsc.d6d
Operator ID:	MD
Sample ID:	G8-PET
Sample Weight:	5.787 mg
Comment:	



10.03.2026 10:26:23

1) Heat from 30.00℃ to 300.00℃ at 20.00℃/min
2) Cool from 300.00℃ to 30.00℃ at 20.00℃/min
3) Heat from 30.00℃ to 300.00℃ at 20.00℃/min

Filename:	C:\Users\DSC\Desktop\MD\G8\pet-dsc.d6d
Operator ID:	MD
Sample ID:	G8-PET
Sample Weight:	5.787 mg
Comment:	



10.03.2026 10:27:39

1) Heat from 30.00℃ to 300.00℃ at 20.00℃/min
2) Cool from 300.00℃ to 30.00℃ at 20.00℃/min
3) Heat from 30.00℃ to 300.00℃ at 20.00℃/min

Filename:	C:\Users\DSC\Desktop\MD\G8\pet-dsc.d6d
Operator ID:	MD
Sample ID:	G8-PET
Sample Weight:	5.787 mg
Comment:	



10.03.2026 10:29:27

1) Heat from 30.00℃ to 300.00℃ at 20.00℃/min
2) Cool from 300.00℃ to 30.00℃ at 20.00℃/min
3) Heat from 30.00℃ to 300.00℃ at 20.00℃/min