# Internal Test Report

| Lot no. | S25120803-7 | Product ID: | D5-N01AA1K-BO | Weight | 345.5 | g/m$^2$ | Overall Thickness | | 0.46 mm | Temperature | 24 ℃ | Humidity | 64.0 | %RH | Date | 2025/12/25 |

| Item | Tensile Strength(N/5cm) | | | | Peel Strength(N/5cm) | | | | Bursting (lb/in$^2$) | | | - | | - | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Standard | Warp | | Weft | | Warp | | Weft | | | | | | | | |
| | 1800.0 | | 1200.0 | | 30.0 | | 30.0 | | | | | | | | |
| Roll no. | Result | Decided | Result | Decided | Result | Decided | Result | Decided | Result | Decided | | | | | |
| 1 | 2412.4 | Qualified | 2033.0 | Qualified | 36.5 | Qualified | 37.8 | Qualified | - | Qualified | | | | | |

| Item | Adhesion Strength(N/5cm)-B/B | | | | Adhesion Strength(N/5cm)-F/B | | | | Tear Strength(N) | | | | Flex-creaking | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Standard | Warp | | Weft | | Warp | | Weft | | Warp | | Weft | | Warp | | Weft | |
| | 200.0 | | 200.0 | | 120.0 | | 120.0 | | 60.0 | | 60.0 | | 30K'S | | 30K'S | |
| Roll no. | Result | Decided | Result | Decided | Result | Decided | Result | Decided | Result | Decided | Result | Decided | Result | Decided | Result | Decided |
| 1 | 340.3 | Qualified | 298.9 | Qualified | 245.8 | Qualified | 271.1 | Qualified | 66.6 | Qualified | 83.9 | Qualified | ≧30K | Qualified | ≧30K | Qualified |
| | | | | | | | | | | | | | 50K'S | | 50K'S | |
| | | | | | | | | | | | | | Result | Decided | Result | Decided |
| 1 | | | | | | | | | | | | | ≧50K | Qualified | ≧50K | Qualified |

Operator : 顏玉滋