Internal Test Report

Lot no.	25010903-1	Product ID:	UE218	Weight	347.5	g/m²	Overall Thickness		0.44 mm	Temperature	20 ℃	Humidity	68.0	%RH	Date	2025/2/21

Item	Tensile Strength(N/5cm)				Peel Strength(N/5cm)				Bursting (lb/in²)				-		Warp		Weft
Standard	Warp		Weft		Warp		Weft										
	1800.0		1200.0														
Roll no.	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided
2	2462.7	Qualified	2039.3	Qualified	-	Qualified	-	Qualified	-	Qualified						

Item	Adhesion Strength(N/5cm)-B/B				Adhesion Strength(N/5cm)-F/B				Tear Strength(N)				Peel Strength(N/5cm)			
Standard	Warp		Weft		Warp		Weft		Warp		Weft		Warp		Weft	
	200.0		200.0		120.0		120.0		60.0		60.0		30.0		30.0	
Roll no.	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided
1	312.8	Qualified	294.0	Qualified	244.0	Qualified	144.9	Qualified	112.6	Qualified	171.1	Qualified	46.2*	Qualified	45.0*	Qualified
2	311.3	Qualified	214.4	Qualified	199.5	Qualified	142.0	Qualified	108.9	Qualified	205.6	Qualified	46.7*	Qualified	45.3*	Qualified

Operator : 顏玉梅