Internal Test Report

Lot no.	25121101-5	Product ID	UE173	Weight	95.0	g/m²	Overall Thickness		0.13 mm	Temperature	18 ℃	Humidity	54.0	%RH	Date	2026/1/8

Item	Tensile Strength(N/5cm)				Peel Strength(N/5cm)				Bursting(lb/in²)		Water Repellant		—			
Standard	Warp		Weft		Warp		Weft		200.0							
	500.0		400.0		ND		ND									
Roll no.	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Decided
3	831.1	Qualified	683.2	Qualified	ND	Qualified	ND	Qualified	284	Qualified	—	Qualified				

Item	Adhesion Strength (N/5cm)-B/B				Tapping Strength (N/2cm)-F/F				Hydrostatic (mmH₂O)			Tear Strength (N)			
Standard	Warp		Weft		Warp		Weft		10000	8000 mm/Min		Warp		Weft	
	70.0		70.0		12.0		12.0					12.0		12.0	
Roll No.	Result	Decided	Result	Decided	Result	Decided	Result	Decided	Result	Glob	Decided	Result	Decided	Result	Decided
1	174.4	Qualified	157.8*	Qualified	12.1	Qualified	13.0	Qualified	12000	0	Qualified	7.6	Unqualified	9.0	Unqualified
2	126.3	Qualified	149.8	Qualified	12.5	Qualified	14.3	Qualified	12000	0	Qualified	8.4	Unqualified	10.8	Unqualified
3	137.0	Qualified	127.6	Qualified	15.5	Qualified	14.2	Qualified	12000	0	Qualified	8.3	Unqualified	10.0	Unqualified
4	133.4	Qualified	160.2	Qualified	17.6	Qualified	13.9	Qualified	12000	0	Qualified	8.7	Unqualified	10.1	Unqualified
5	128.7	Qualified	115.0	Qualified	18.6	Qualified	17.0	Qualified	12000	0	Qualified	8.8	Unqualified	10.5	Unqualified

Hydrostatic (mmH₂O)

									10000	600 mm/Min					
									Result	Glob	Decided				
5									12000	0	Qualified				

operator :

ISO NO.：F0803