

Customer: **CONSTANTIA FROMM GMBH, Germany**

Material Specification and Regulatory Information


Application: Aluminium lidding foil sealable to aPET, PP, PVC, PVdC for solid pharmaceutical products

Material: Print Primer /Alu 20 µm /Heat-Seal Lacquer

CONSTANTIA PATZ GES. M. B. H.

PATZ 42192/ALU-H 20 dull – unprinted

Material description (from the outer to the inner layer):



LAYER	CHEMICAL BASE	GRAMMAGE	TOLERANCES
PRINT PRIMER	Polyester	0.8 g/m ²	±0.3 g/m ²
ALU 20 µm HARD, MATTE ↑	DIN EN 573-3 min. EN AW 8079	54.0 g/m ²	±4.3 g/m ²
HEAT-SEAL LACQUER	Methacrylate olefin copolymer	7.0 g/m ²	±1.0 g/m ²
TOTAL GRAMMAGE	-	61.8 g/m ²	±6.2 g/m ²
CALCULATED TOTAL THICKNESS		27.8 µm	±10 %

Permeation: Moisture (MVTR); according to ISO 15106-3 [38°C; 90% r.h.]: < 0.001 g/(m² x d)
Oxygen (OTR); according to ISO 15105-2, Annex A [23°C; 50% r.h.]: < 0.005 cm³/(m² x d x bar)

Warranty: Sealability: max. 2 years from production date
Printability: max. 18 months from production date

Storage cond.: 15°C to 35°C, relative humidity 30% to 70%; no direct sunlight; reels to be left in original packing until usage; reels to be repacked after use.

Drug Master File: Material is listed in the US DMF: **4889**

Certificates: the Constantia Flexibles group is certified for ISO9001;
site-specific certificate can be seen under:
<http://www.cflex.com/quality/certificates-letters-of-conformity/>

Compliance Status: PATZ 42192/ALU-H 20 dull – unprinted

General

The product fulfils the applicable requirements of:

- EU "Framework" Regulation (EC) No. 1935/2004
- Regulation (EC) No. 2023/2006 on good manufacturing practice
- Directive 94/62/EC and the Model Toxics in Packaging Legislation (as drafted by the Toxics in Packaging Clearinghouse/ Source Reduction Council of CONEG) regarding the sum of concentration levels of lead, cadmium, mercury and hexavalent chromium < 100 ppm.

LAYER	COUNTRY	LEGAL PROVISIONS (RECOMMENDATIONS, CODE OF PRACTICE, DECREES) FOR PLASTICS, PAPER, ADHESIVES, COATINGS AND OTHER COMPONENTS
PRINT PRIMER	EU	The lacquer fulfils the requirements of Article 3 of the EU-Framework Regulation 1935/2004/EC if applied on the non-food contact surface of food packaging..
ALUMINUM	EU	EN 602 "Aluminium and aluminium alloys – Wrought products – Chemical composition of semi products used for the fabrication of articles for use in contact with food."
	USA	FDA 21 CFR § 178.3910 (a)
		Aluminum foils > 6 µm are regarded as a functional barrier.
HEAT-SEAL LACQUER	EU	All starting monomers and additives are listed in the union list of EU Regulation No. 10/2011 as amended
	USA	FDA 21 CFR § 175.300

Bisphenol A and other bisphenols and bisphenol derivatives are no compositional component of the used raw materials and we do not add them during the manufacture of the product.

Thus, the product complies with the applicable requirements of EU Regulation 2024/3190/EC and with the requirements set out in Articles 3, 15 and 17 of Regulation (EC) No 1935/2004.

TSE/BSE Risk

According to statements by our suppliers, the raw materials used for the above-mentioned complex do not contain animal derived products as a constituent. This information is based on a theoretical evaluation of the recipe and the confirmations from our raw material suppliers. We do not analyze for this substance in the delivered products.

Disclaimer: This specification is confidential and should not be duplicated or distributed without expressed permission of Constantia Flexibles.

This information is correct to the best of our knowledge. However, the manufacturing sites make no warranties, express or implied, and assumes no liability in connection with any use of this knowledge.

The given information describes the status of the product specified in this document. The packer is responsible for verifying possible interactions of the products or its components with the pharmaceutical product which are to be checked prior to use and in function of the end-uses and to ensure the general appropriateness of the packaging material for the intended use.

i.A. Regulatory Affairs:

i.A. Application Engineer: